


DARSHAN

DYE CHEM





ACID DYES


ACID DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON NYLON		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Milling
0.5%	2.0%					
		ACID YELLOW 5G ACID YELLOW 186	3-4	3	3	3
		ACID YELLOW 5GN ACID YELLOW E110	5	5	4-5	4
		ACID YELLOW 5GNX ACID YELLOW 64	6-7	5	5	-
		ACID TARTARZINE YELLOW N ACID YELLOW 23	5	4-5	3-4	5
		ACID LIGHT FAST YELLOW G ACID YELLOW 11	4-5	4-5	4	2-3
		ACID LIGHT FAST YELLOW 2G ACID YELLOW 17	4-5	4-5	3-4	3-4
		ACID FAST YELLOW FGL/4GL ACID YELLOW 49	5-6	4	3	3
		ACID YELLOW MR ACID YELLOW 42	4	5	4-5	3
		ACID METANIL YELLOW G ACID YELLOW 36	3	4-5	3	4


ACID DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON NYLON		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Milling
0.5%	2.0%					
		ACID YELLOW GL ACID YELLOW 114	5-6	4-5	4-5	3-4
		ACID YELLOW 2GLN ACID YELLOW 59	7	4-5	4-5	4-5
		ACID YELLOW GR ACID YELLOW 99	4-5	4-5	4-5	4
		ACID FAST YELLOW 3RL ACID YELLOW 194	5-6	4-5	4-5	3-4
		ACID YELLOW 2RL ACID ORANGE 80	7	5	5	3-4
		ACID LIGHT FAST ORANGE 2G ACID ORANGE 10	3-4	4-5	3	4-5
		ACID ORANGE II ACID ORANGE 7	3-4	4	2-3	3
		ACID ORANGE SGR ACID ORANGE 56	7	4-5	4-5	3-4
		ACID ORANGE G ACID ORANGE 74	5-6	4-5	4-5	5




ACID DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON NYLON		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Milling
0.5%	2.0%					
		ACID ORANGE RL ACID ORANGE 86	7	4-5	4-5	3-4
		ACID ORANGE MRL ACID ORANGE 142	6	4-5	4-5	6-4
		ACID SCARLET G ACID RED 97	3	4-5	4-5	4
		ACID CROCINE SCARLET MOO ACID RED 73	5	3-4	2-3	2-3
		ACID RED MBL ACID RED 362	5-6	4-5	5	3
		ACID FAST SCARLET GL ACID RED 357	6	4-5	4-5	3-4
		ACID RED G ACID RED 183	5-6	5	4	5
		ACID SCARLET 3R ACID RED 18	4	5	3-4	4
		ACID FAST RED RS ACID RED 114	4	5	3	4

ACID DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON NYLON		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Milling
0.5%	2.0%					
		ACID RED F2R ACID RED 151	4	4	3-4	4
		ACID FAST RED A ACID RED 88	2-3	3	1	2
		ACID BRILLIANT CARMOISINE WS ACID RED 14	3-4	4-5	3	4
		ACID RED GERAMINE RED 2G/ROSE/ 2G ACID RED 1	4-5	4-5	3	2-3
		ACID PINK RED EB ACID RED 195	4-5	4-5	4	4
		ACID PINK B ACID RED 186	4-5	5	4-5	3-4
		ACID SULPHO RHODAMINE B ACID RED 52	3-4	4-5	3-4	4
		ACID RED 3BN ACID RED 131	4-5	4-5	4-5	3-4
		ACID FAST BRILLIANT RED 8 ACID RED 249	3-4	4-5	4-5	3-4

ACID DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON NYLON		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Milling
0.5%	2.0%					
		ACID CRIMSON RED (MIX)	4-5	4-5	4	3
		ACID RED NG (MIX)	3	4-5	4-5	4
		ACID MAROON V ACID RED 119	4-5	5	4-5	3-4
		ACID RED SRS	3	4-5	4-5	4
		ACID BORDEAUX MB ACID VIOLET 90	5	4-5	4-5	3
		ACID BRILLIANT RED 10B ACID VIOLET 54	4-5	5	5	5
		ACID VIOLET RL ACID VIOLET 92	5	4-5	4-5	5
		ACID BROWN VIOLET L ACID VIOLET 78	6-7	5	4-5	4-5
		ACID VIOLET 4BN/5BN ACID VIOLET 17	1-2	5	4-5	4

ACID DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON NYLON		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Milling
0.5%	2.0%					
		ACID VIOLET 4BS ACID VIOLET 49	1-2	5	4-5	4
		ACID PATENT BLUE VS ACID BLUE 1	2-3	4	2-3	3-4
		ACID BRILLIANT BLUE FCF ACID BLUE 9	1-2	2	3-4	3-4
		ACID PATENT BLUE AS ACID BLUE 7	1-2	5	4-5	4-5
		ACID CORNASSIVE BLUE FF ACID BLUE 15	1	5	4	4
		ACID ROYAL BLUE N (MIX)	2-3	4	4-5	4
		ACID BRILLIANT COMASSE FAST BLUE 2R ACID BLUE 92	5-6	4	3-4	1-2
		ACID BLUE 2G ACID BLUE 158	4-5	4-5	4	4-5
		ACID FAST NAVY BLUE S5R/2RNS ACID BLUE 113	5	4-5	4-5	3-4

ACID DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON NYLON		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Milling
0.5%	2.0%					
		ACID DARK BLUE MTR ACID BLUE 193	6-7	5	4-5	3-4
		ACID BLUE AG ACID BLUE 25	5-6	3	3	2-3
		ACID VEPORAIDE PXE ACID GREEN 1	6	3-4	3-4	2-3
		ACID GREEN 3GR (MIX) PARROT GREEN	4-5	4-5	3	4
		ACID GREEN V ACID GREEN 16	3	4-5	3	3-4
		ACID FAST GREEN B ACID GREEN 9	1-2	4-5	3-4	2-3
		ACID ALAZARINE NATURAL GREEN G ACID GREEN 25	5-6	4-5	4	3-4
		ACID GREEN BS ACID GREEN 111	4-5	4-5	4	4
		ACID DARK GREEN N ACID GREEN 68	4	4	3	3

ACID DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON NYLON		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Milling
0.5%	2.0%					
		ACID DARK GREEN B ACID GREEN 20	4-5	4	4	4
		ACID BROWN RL ACID BROWN 425	5	4-3	4	4
		ACID BROWN HTG B ACID BROWN 422	4	3-4	3	3
		ACID BROWN CG ACID BROWN 83	4	3	4	3
		ACID BROWN GBP ACID BROWN 420	4-5	4	3	4
		ACID BROWN NT ACID BROWN 165	4-5	4	3	4
		ACID BROWN 2RL ACID BROWN 45	6-7	4-5	4-5	3-4
		ACID BROWN 3R ACID BROWN 75	4	4	3	4
		ACID BROWN RL ACID BROWN 365	6-7	4-5	4-5	4

ACID DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON NYLON		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Milling
0.5%	2.0%					
		ACID FAST BROWN ESR ACID BROWN 348	4-5	4	3	2-3
		ACID BROWN ESG ACID BROWN 349	4	4	3-4	4
		ACID BROWN MBL ACID BROWN 355	6-7	4-5	4-5	4
		ACID BROWN GR ACID BROWN 282	6-7	5	5	4
		COFEE BROWN (MIX)	4	4	3-4	4
		ACID BLACK AB ACID BLACK 210	3-4	3-4	4	4
		ACID BLACK 10BX ACID BLACK 1	5-6	2	2-3	3
		ACID FAST GREY BGL ACID BLACK 58	6-7	5	4-5	4-5
		ACID BLACK NBR ACID BLACK 234	3-4	3-4	4	4

ACID DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON NYLON		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Milling
0.5%	2.0%					
		ACID BLACK WA ACID BLACK 52	7-8	4-5	3-4	3-4
		ACID BLACK LDN ACID BLACK 172	7	4-5	4	4
		ACID BLACK MSRL ACID BLACK 194	7	4	4	4
		CROME BLACK T BORDANT BLACK 11	7-8	5	4	5
		ACID BLACK BX (MIX)	-	-	-	-
		GREEN LP	4-5	4-5	3	5
		BOTTLE GREEN	-	-	-	-
		DARK GREEN (MIX)	-	-	-	-