




DARSHAN

DYE CHEM

DIRECT DYES

DIRECT DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON COTTON		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Milling
0.5%	2.0%					
		DIRECT LEMON YELLOW 6G/CFG DIRECT YELLOW 8	2	2-3	2-3	40
		DIRECT FAST LEMON YELLOW 5GLL DIRECT YELLOW 44	5	3-4	4-5	60
		DIRECT FAST YELLOW 3GX DIRECT YELLOW 6	6	3	2	60
		DIRECT CHRYSOPENINE G DIRECT YELLOW 12	5	1	1	40
		DIRECT SUN YELLOW RCH DIRECT YELLOW 99	4	2	2	60
		DIRECT FAST YELLOW RL DIRECT YELLOW 86	6	3	3-4	80
		DIRECT FAST ORANGE TGLL (Y) DIRECT ORANGE 34	6	7	2-3	80
		DIRECT FAST ORANGE TGLL (R) DIRECT ORANGE 39	6-7	2-3	4-5	80
		DIRECT VISCOSE ORANGE A DIRECT ORANGE 108	2-3	2-3	2-3	80


DIRECT DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON COTTON		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Milling
0.5%	2.0%					
		DIRECT FAST ORANGE SE DIRECT ORANGE 26	3	4	2-3	50
		DIRECT FAST SCARLET 4BS DIRECT RED 23	3-4	2	3-4	60
		DIRECT FAST RED BLN DIRECT RED 80	5	3-4	3-4	80
		DIRECT LIGHT FAST RED 6BL DIRECT RED 79	6	3-4	3-4	70
		DIRECT FAST RED 5BL DIRECT RED 81	4-5	3-4	3-4	70
		DIRECT FAST RED 12B DIRECT RED 31	2	2	3	60
		DIRECT FAST RUBINE VIOLET 2R DIRECT RED 83	7	3-4	2-3	60
		DIRECT BRILLIANT HELIO 2R DIRECT VIOLET 35	4	2	2-3	60
		DIRECT BRILLIANT VIOLET HELIO B DIRECT VIOLET 51	4	2	2-3	60



DIRECT DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON COTTON		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Milling
0.5%	2.0%					
		DIRECT FAST VIOLET MB DIRECT VIOLET 9	2-3	2	2-3	40
		DIRECT FAST TURQUOIES BLUE GL DIRECT BLUE 86	6	4	1-2	80
		DIRECT FAST TURQUOIE FBL DIRECT BLUE 199	6	3	3	60
		DIRECT SKY BLUE FF DIRECT BLUE 15	2	3	3	50
		DIRECT FAST BLUE 2RLL DIRECT BLUE 80	6	3	3	50
		DIRECT FAST BLUE GLL DIRECT BLUE 71	5-6	5-6	3	70
		DIRECT FAST SKY BLUE 7GLL DIRECT BLUE 218	4-5	3-4	2	60
		DIRECT FAST GREEN BLL DIRECT GREEN 96	4-5	3-4	2	60
		DIRECT PAPER BROWN SD DIRECT BROWN 44	4	2-3	2-3	60

DIRECT DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON COTTON		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Milling
0.5%	2.0%					
		DIRECT FAST BROWN MN (MIX)	5	1-2	1-2	60
		DIRECT BLACK OB DIRECT BLACK 80	5-6	3	3	50
		DIRECT FAST BLACK VSF 600 DIRECT BLACK 22	4-5	3-4	3-4	45

DIRECT MATCHING SHADES

		DIRECT SWISS PINK	-	-	-	-
		DIRECT TOMATO RED	-	-	-	-
		DIRECT ROSE	-	-	-	-
		DIRECT MAROON	-	-	-	-
		DIRECT MAGENTA	-	-	-	-

DIRECT DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON COTTON		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Rubbing
0.5%	2.0%					
		DIRECT ROYAL BLUE	-	-	-	-
		DIRECT NAVY BLUE	-	-	-	-
		DIRECT RAMA GREEN	-	-	-	-
		DIRECT AMROL GREEN	-	-	-	-
		DIRECT SHAKUNTALA GREEN	-	-	-	-
		DIRECT MEHANDI GREEN	-	-	-	-
		DIRECT CHATANI GREEN	-	-	-	-
		DIRECT MILITARY GREEN	-	-	-	-
		DIRECT BOTTLE GREEN	-	-	-	-

DIRECT DYES		DARSHAN DYES	FASTNESS PROPERTIES			
SHADE ON COTTON 0.5% 2.0%		DYES (C.I. GENERIC NAME)	Light	Washing	Perspiration	Milling
		DIRECT KHAKHI	-	-	-	-
		DIRECT BROWN GG	-	-	-	-
		DIRECT BROWN 2GLL	-	-	-	-
		DIRECT RUST	-	-	-	-
		DIRECT CHIKU BROWN	-	-	-	-
		DIRECT GREY 2RL	-	-	-	-