

FORMAT NO.- MPS/F&F-5C

TEST REPORT

MEGHA POWER SOLUTIONS

Office & Laboratory: Ground Floor, Sai ganesh Building, Opp Cholegaon Thakurli (East)- 421201 Dist - Thane Mumbai Maharashtra

{ Testing & Diagnostic Solutions } Email - mps.m14@hotmail.com

Registered Office: 201 Hawsa CHS, Cholegoan,

Thakurli(East), Thane ,421201 (MH)

RELIANCE INDUSTRIES LIMITED Issued to :-

Contact No. - 8879883349 / 7506682565

Test Certificate No./ ULR No.:- TC538819000000130F

Dahej Manufacturing Division

Test Report Date :-

30/1/2019

Dahej,Bharuch,Gujrat

Testing Date:-

27.6 °C

18/1/2019

Sample Particular	Bottle No.	M-60					Sampling Method(IS 6855)			
Collected on:-	8/1/2019		Ву :-	MPS	Position:-	Bottom	Last Maint. Date	-	Ambient Temp. (°C):	SUNNY
Eqmt. Detail	Plant	POFL	Sr.No.	Rating	Ratio (KV)	WTI (°C)	OTI (°C)	Make	Mfr Year	Last Maint. Date
1000535992	IOP S/W	GNU-IOP-SUB- SWY-TR001	6800000133	45/60/75 MVA	220/34.5 KV	-	-	NGEF	1995	-

TEST DATA

(IS 1866-2000 Addition 4.1, 2006-08)

		Oil Test			
Test Parameter		Test Method	Limits	Test Value	
Appereance		IS 335	Clear	Yellowish brown Color	
Density at 29.5 ° C		IS 1448(P-16)	Max 0.890 g/cm ³	0.86	
Breakdown Voltage (BDV) a)Type of Electrodes: Spherical b)Frequency of th Test Voltage: 50 Hz c)Oil Temprature: 27.0 °C d)Test Value is the Avg of 6 Reading		IS 6792	Min 50 KV	60	
Water Content		IS 13567	Max 20 ppm	17	
Neutralisation Value (Total Acidity)		IS 1448(P-2)	Max 0.3 mg KOH/g	NA	
Specific Resistivity (* 10 ¹²) # Frequency of Test Voltage: 50 hz	@27°c		Min 1 ^x 10 ¹² ohm-cm	NA	
# Room Temperature: °C # Humidity During Test: % # Three terminal oil cell used # Avg Voltage Gradient in Sample under Test, in V/mm: 500 volt	@90°c	IS 6103	Min 0.1* 10 ¹² ohm-cm	NA	
Dielectric Disipation Factor # Frequency of Test Voltage: 50 hz # Room Temperature: °C # Humidity During Test: % # Three terminal oil cell used # Avg Voltage Gradient in Sample under Test, in V/mm: 500 volt	@27°c	IS 6262		NA	
rest, in v/mm : 500 voit	@90°C		Max 1.0	NA	
Interfacial Tension at 27 °C	<u> </u>	IS 6104	Min 15 mN/m	NA	
Flash Point		IS 1448(P-21)	Min 125 °C	NA	
Sediment & Sludge %		IS 1866 (AP-A)	Min 0.02 % by mass	NA	
Remark: As per tested Perameter oil is fit for use					

Humidity :-42 % Temperature :-

Observation: As per tested Perameter oil is fit for use

Note: 1.Test Result indicates only Tested Sample and Parameter.

2. Liability of Laborartory is limited to tested parameter. 3.Certificate cannot used as Evidence in Court of Law without Prior consent of the laborartary

Mayuresh Sawant(TM) **Authorised Signatory** For Megha Power solutions

