

CVN-69 Milestone 5 — Printing Guide

Validated process

- Primary: Bambu P2S, 0.40 mm nozzle; compatible with X1C, P1S, A1, and these compact type plates are practical on A1 mini.
- Preferred 0.12 mm layer; 0.16 mm independently sliced as the second validation gate; three walls.
- Use Basic Blue Grey for bodies, Charcoal for canopy inserts, Ivory for rotodome/identity inserts, and Silver for rotors/details.
- Body STLs and type plates include 0.80 mm removable belly/engine rails only in print geometry. Clip and sand these rails after cooling; the clean assembly BRep/STEP remains unchanged.
- Do not scale. Do not reduce the 0.60–0.80 mm nozzle-safe features.

Production plates

Plate	Objects	Use
Print_Plate_00_First_Article.3mf	named/material objects	first article
Print_Plate_C2A_VRC40.3mf	named/material objects	type family
Print_Plate_E2C_VAW123.3mf	named/material objects	type family
Print_Plate_EA18G_VAQ130.3mf	named/material objects	type family
Print_Plate_FA18E_VFA105.3mf	named/material objects	type family
Print_Plate_FA18E_VFA131.3mf	named/material objects	type family
Print_Plate_FA18E_VFA83.3mf	named/material objects	type family
Print_Plate_FA18F_VFA32.3mf	named/material objects	type family
Print_Plate_MH60R_HSM74.3mf	named/material objects	type family
Print_Plate_MH60S_HSC7.3mf	named/material objects	type family

Quality checks

- Reject any part with a missing blade, broken folded wing, incomplete tail, or canopy/rotodome seat damage.
- Use a 3–5 mm brim only if local adhesion requires it; no support generation was needed in the validated command-line slices.
- Bambu Studio produced 20 successful real slices with zero floating-region, empty-layer, and faulty-mesh warnings.