


CVN-69 Deck-to-Hull Interface Coupon

ONE-PAGE PRINT / FIT / GLUE TEST · RUN BEFORE THE FULL MILESTONE 2 PRINT



Coupon feature	Actual production value
Male feature	6.00 × 6.00 mm; 1.20 mm protrusion
Female opening	6.50 × 6.50 mm; 1.45 mm depth
Nominal clearance	0.25 mm per side
Female top wall	1.55 mm
Combined print layout	53 × 20 × 5.2 mm

Procedure

- Print `3MF/Interface\_Test\_Coupon.3mf` at 100% scale with the same nozzle, layer height, material, and XY compensation planned for production.
 - Remove brim and elephant foot without filing the nominal male or female walls.
 - Dry-fit: the male must enter by hand, the broad faces must fully touch, and the fit must not rock or require force.
 - Glue-fit: apply the intended adhesive sparingly, fully seat, allow it to cure, and record material, slicer profile, measured gap, and result.
 - Pass: full seating and stable alignment. Fail: force fit, more than 0.30 mm seating gap, cracked wall, or adhesive lock before seating.
- Do not scale the production model to compensate for a failed coupon. Correct printer calibration or slicer XY compensation, then repeat the coupon.