Degreasing agent WF-4316N

Chemical Structure

Special branched-chain surfactant compound

Technical Index

Item	Standard
Appearance	Colorless and transparent microemulsion
Solid Content, %	58.0-62.0%
PH Value (1% water solution)	6.0-8.0
Ionic	Anionic/Nonionic

Features and Advantages

1. In weakly alkaline and neutral baths, when used in combination with the strong oil-removing agent WF-4315C for nylon fabric, it can effectively emulsify and disperse the oil agents on the nylon fabric while removing the oil, preventing the re-contamination of the oil agents.
2. At low temperatures of 70-80°C and in neutral conditions, it has a remarkable effect in removing oil stains from fabrics that are not resistant to alkali (such as fabrics containing gold and silver threads, silk, and wool), without damaging the fibers.
3. In alkaline conditions, in the refining and oil-removing bath of blended fabrics and all-cotton fabrics, it has excellent refining and decontamination effects.
4. It is suitable for the dyeing process of polyester knitted fabric in the same bath dyeing process. It has little effect on color and light, and in weakly acidic and near-neutral baths, it can effectively remove oil stains and fully emulsify and disperse them, and has unique efficacy in removing chemical fiber oil agents.

Application

Low-temperature oil removal process applicable to decorative fabrics, dyeing and bleaching process for synthetic fiber knitted fabrics and other fabrics, as well as refining and oil removal process for cotton and its blended fabrics.

1. Decorative fabric low-temperature oil removal process:
WF-4316N: 0.2 - 0.6g/L, time 30 - 60min, temperature: 70 - 80℃

2. Polyester knitted dyeing and bleaching in one bath process:
WF-4316N: 0.2 - 1g/L, acetic acid: 0.4 - 0.6mL/L, dye: x grams, high-temperature uniforming agent: 0.3 - 1.0g/L, bath ratio: 1:10, time: 30 - 60min, temperature: 130℃.

3. Refining oil removal process (cotton knitted and mixed fabrics):
WF-4316N: 0.2 - 1.5g/L, NaOH: 2g/L, H2O2 (27.5%): 5g/L, bath ratio: 1:10, time: 40 - 60min, temperature: 95 - 98℃

Package

120KG Plastic Drum or other packing on request. Sealed and light-proof storage.