CMA
220009349196

# Test report

**No：CIC-RJ-CC261436-01A**

Product Name：CNT CONDUCTIVE TILE

Model：/

Size：600×600×2(mm)

Applicant：QingDao In Tech Trade Co.,Ltd.

Manufacturer：DOOHA CO.,LTD. (KOREA)

**China Industrial Control Systems Cyber Emergency Response Team**

**MII Anti-Static Products Quality Supervision &Testing Center**

扫描全能王 创建

Note：

1. This report is invalid without "anti-counterfeiting mark", "seal for sewing" and "special seal for testing".

2. This report is invalid without the signature (seal) of the testing, auditing and approving person.

3. This report is invalid if it is altered or copied at will, and cannot be copied without the written approval of the laboratory (except the full copy).

4. The data results in this report are only valid for the tested samples.

5. The sample information of this test report is provided for customers, and our center is not responsible for the authenticity.

6. The report is valid for one year for Scan cover QR code inquiry 10 days after the date of issue.

---

Testing unit：China Industrial Control Systems Cyber Emergency Response Team

MII Anti-Static Products Quality Supervision &Testing Center

Address：No.35 Lugu Road, Shijingshan District Beijing ,China

Postal Code：100040

Tel：+86-10-68869773/68865301

Website：www.cics-cert.org.cn

Email：cicesd@163.com

扫描全能王 创建

| | | | |
|---|---|---|---|
| **Product Name** | CNT CONDUCTIVE TILE | | |
| **Address** | No. 808, Haiyun Dongfang, 15 Qinling Road, Laoshan District, Qingdao City, Shandong Province, China | | |
| **Submitter** | Huang Donglong | **Tel** | 13953291817 |
| **Test category** | Commission test | **Quantity of Samples** | 7 pcs |
| **Date of sample arrival** | Aug.21,2026 | **Date of testing** | Aug.24,2026 |
| **Structure characteristics** | Material: PVC+CNT(Carbon Nanotube) Structure: CNT(Carbon Nanotube) Homogeneous Transparent Network Structure; Color: White carbon grid | | |
| **Test Items** | Surface resistance, Volume resistance, Surface wear resistance, Residual concavity, Surface electrostatic voltage, Surface electrostatic voltage (friction), Person/footwear/flooring system resistance, Body voltage, Static dissipation time | | |
| **Test Standard** | SJ/T 11236-2020,GB/T 4085-2015,SJ/T 10694-2022 | | |
| **Determination Standard** | SJ/T 11236-2020,SJ/T 10694-2022 | | |
| **Apparatus** | 625 temperature and humidity sensor (FJ-69), 152-1 surface resistance tester (FJ-72), 541A-1 electrostatic voltmeter (FJ-38), 268A electrostatic decay meter (FJ-31), digital dial gauge (FJ-118), HP-AXJ residual indentation meter (FJ-111), DK-5612A wear-resistant machine (FJ-103), electronic balance (FJ-94) | | |
| **Testing Environment** | Temperature: 23.0℃<br>Relative Humidity: 51.0%RH | | |
| **Test Conclusion** | The surface resistance, volume resistance, surface wear resistance, and residual concavity meet the requirements of SJ/T 11236-2020. The static dissipation time data can be found in the summary of test results. The remaining test items meet the requirements of SJ/T 10694-2022.<br>Issue Date: Sep.01,2026 | | |
| **Remarks** | The customer requires the surface electrostatic voltage (friction) test: Use a 1kg cylindrical friction electrode wrapped in high insulation nylon cloth, after 20 single directional frictions (for 20 seconds),and test the surface electrostatic voltage of the friction track within 10s. | | |

**Authorized by:** Zhao Guang hui **Approved by:** Fan Zongjie **Tested by:** Lu Liang



扫描全能王 创建

**Summary of Test Results**

**Sample state adjustment:** The sample has been conditioned for 48 hours under environmental conditions of temperature 23.0 ℃ and humidity 50.0% RH.

| S/N | Test Item(s) | Unit | Specification | Test Result(s) | | Conclusion |
|---|---|---|---|---|---|---|
| 1 | Surface resistance | Ω | SJ/T 11236-2020<br>Conductive：$1.0\times10^4$～$1.0\times10^6$Ω<br>Dissipative：$1.0\times10^6$～$1.0\times10^9$Ω | ①<br>②<br>③ | $3.45\times10^5$<br>$4.35\times10^5$<br>$3.44\times10^5$ | Pass |
| 2 | Volume resistance | Ω | SJ/T 11236-2020<br>Conductive：$1.0\times10^4$～$1.0\times10^6$Ω<br>Dissipative：$1.0\times10^6$～$1.0\times10^9$Ω | ①<br>②<br>③ | $1.34\times10^5$<br>$1.54\times10^5$<br>$1.58\times10^5$ | Pass |
| 3 | Residual concavity | mm | SJ/T 11236-2020<br>≤0.15mm | 0.04 | | Pass |
| 4 | Surface wear resistance | g/cm² | SJ/T 11236-2020<br>≤0.02g/cm² | 0.019 | | Pass |
| 5 | Surface electrostatic voltage | V | SJ/T 10694-2022<br>\|U\| < 100V | -10 | | Pass |
| 6 | Surface electrostatic voltage (friction) | V | SJ/T 10694-2022<br>\|U\| < 100V | -72 | | Pass |
| 7 | Person/footwear /flooring system resistance | Ω | SJ/T 10694-2022<br><$1.0\times10^9$Ω | Left foot<br>Right foot<br>Feet | $2.30\times10^6$<br>$2.11\times10^6$<br>$1.88\times10^6$ | Pass |
| 8 | Body voltage | V | SJ/T 10694-2022<br>\|U\|＜100V | Peak<br>Valley | 17<br>9 | Pass |
| 9 | Static dissipation time | s | SJ/T 10694-2022<br>(±1000 ～±100V) | +V<br>0.1 | -V<br>0.1 | / |

Note:The resistance of the body/Footwear system for testing shoes is $2.10\times10^6$Ω.

（The following blanks）



扫描全能王 创建