Consignor/Shipper
TOYOTA TSUSHO KOREA CORPORATION
30F, MIRAE ASSET CENTER 1 WEST TOWER,
67, SUHA-DONG, JUNG-GU, SEOUL 04539, KOREA

COMBINED TRANSPORT BILL OF LADING

B/L No. WBLCH2409005

Reg.No.

WORLD BEST LOGIS

WORLD BEST LOGIS CO., LTD.

TEL. 82-70-7076-8518 FAX. 82-70-7076-9400
E-mail. world@wblkorea.co.kr

Consignee
TOYOTA TSUSHO(THAILAND)CO.,LTD
607 ASOKE-DINDAENG ROAD,KWAENG
DINDAENG,KHET DINDAENG, BANGKOK 10400 THAILAND
MS. NICHAREE
TEL)66-2625-5952

Notify Party
TOYOTA TSUSHO(THAILAND)CO.,LTD
607 ASOKE-DINDAENG ROAD,KWAENG
DINDAENG,KHET DINDAENG, BANGKOK 10400 THAILAND
MS. NICHAREE
TEL)66-2625-5952

For delivery of goods please apply to:
PJ TRANS MILLENNIUM CO., LTD.
1000/57-58 TROKWATJANNAI, RAMA III ROAD
BANGKLO, BANGKORLAEM, BANGKOK 10120, THAILAND.
ATTN : JATURON
TEL : 662-2969599 FAX : 662-683-7945~6

Pre-carriage by	Place of Receipt
	BUSAN, KOREA

Vessel/Voyage No.
KMTC TOKYO 2412S

Port of Loading	Port of Discharge	Place of Delivery	Final Destination(For the Merchant Ref.)
BUSAN, KOREA	LAEM CHABANG, THAILAND	LAEM CHABANG, THAILAND	

PARTICULARS FURNISHED BY CONSIGNOR/SHIPPER

Container No. & Seal No. Marks and No.	No. & Kinds of Containers or P' kgs	Description of Goods	Gross Weight	Measurement
- ATTACHED RIDER -	151 BUNDLES 20`DV x 13	SAID TO CONTAIN: 151 BUNDLES OF HOT ROLLED ALLOY STEEL ROUND BARS HOT ROLLED ALLOY STEEL ROUND BARS PEELED HOT ROLLED STEEL ROUND BARS	303,042.000KG	65.000CBM

COPY
NON-NEGOTIABLE

ON BOARD DATE:
SEP.30,2024

SURRENDED

CFS/CY "FREIGHT PREPAID"

Excess Value Declaration(Refer to § Ⅱ-4.3) :

Total Number of Containers or Packages(in words) SAY : ONE HUNDRED AND FIFTY ONE (151) BUNDLES ONLY.

Freight Payable at SEOUL, KOREA

Freight & Charges	Prepaid	Collect
FREIGHT PREPAID AS ARRANGED		

Received by the Carrier, the Goods specified herein in apparent good order and condition unless otherwise stated, to be transported to such place as agreed, authorized or permitted herein and subject to all the terms and conditions appearing on the front and reverse of this Multimodal Transport Bill of Lading (hereinafter called the 'B/L') to which the Merchant agrees by accepting this B/L, notwithstanding any local privileges, customs or any other agreements between the parties. The particulars of the Goods provided herein were stated by the shipper and the weight, measurements, quantity, condition, contents and value of the Goods are unknown to the Carrier. In witness where of three(3) original B/L(s) have been signed unless otherwise stated herein. If two(2) or more original B/L(s) have been issued and either one(1) has been surrendered, all the other(s) shall be null and void. If required by the Carrier one(1) duly endorsed original B/L must be surrendered in exchange for the Goods or delivery order.

Place and Date of Issue		No. of Original B/L	Signature
SEOUL, KOREA	SEP.30,2024	ZERO(0)	

B/L No. WBLCH2409005

WORLD BEST LOGIS CO., LTD.
ACTING AS A CARRIER

- ATTACHED RIDER -

NTN
GRADE
HEAT NO
SIZE
Q`TY
SEAH BESTEEL

FCIU6151555/PANP769120
STXU2025108/PANP769111
STXU2025710/PANP769113
STXU2030017/PANP769114
STXU2033166/PANP769117
STXU2039204/PANP769112
STXU2040587/PANP769914
STXU2051745/PANP769119
STXU2052361/PANP769916
STXU2066365/PANP769118
STXU2070088/PANP769915
STXU2071680/PANP769116
STXU2072687/PANP769115

Original

1.Goods consigned from (Exporter's business name, address, country)
TOYOTA TSUSHO KOREA CORPORATION
30F, MIRAE ASSET CENTER 1 WEST TOWER, 67, SUHA-DONG, JUNG-GU, SEOUL 04539, KOREA
Tel: 02-6744-6736 Fax: 02-6744-6897

Reference No. C010-24-0043186

Reference code. rnu1-ewm8

KOREA-ASEAN FREE TRADE AREA PREFERENTIAL TARIFF CERTIFICATE OF ORIGIN

(Combined Declaration and Certificate)
FORM AK
Issued in the REPUBLIC OF KOREA
(Country)
See Notes Overleaf

2.Goods consigned to (Consignee's name, address, country)
TOYOTA TSUSHO THAILAND CO LTD
607 ASOKE-DINDAENG ROAD, KWAENG DINDAENG, KHET DINDAENG BANGKOK 10400 THAILAND

3.Means of transport and route(as far as known)
Departure date : 30-SEP-2024
Vessel's name/Aircraft etc : KMTC TOKYO 2412S
Port of Discharge : LAEM CHABANG, Thailand

4. For official use
☐ Preferential Treatment Given Under KOREA-ASEAN Free Trade Area Preferential Tariff
☐ Preferential Treatment Not Given (Please state reason/s)

Signature of Authorized Signatory of the importing Country

5.Item number	6.Marks and numbers on packages	7.Number and type of packages, description of goods (including quantity where appropriate and HS number of the importing country)	8.Origin criterion (see notes overleaf)	9.Gross weight or other quantity, and Value (FOB only when RVC criterion is used)	10.Number and date of invoices
1	NTN GRADE HEAT NO SIZE Q'TY SEAH BESTEEL //////////////////////////	HOT ROLLED ALLOY STEEL ROUND BARS 38B3 29.00MM X 5750MM 33BUNDLES 75.784 MT HS No. 7228.30	CTH	75.784(MT)	TTKT2-NTNTH-240905 23-SEP-2024 ////////////////
2		HOT ROLLED ALLOY STEEL ROUND BARS 38B3 30.50MM X 5600MM 2BUNDLES 4.27 MT HS No. 7228.30	CTH	4.27(MT)	
3		HOT ROLLED ALLOY STEEL ROUND BARS PEELED 38B3 24.00MM X 5600MM 8BUNDLES 10.838 MT HS No. 7228.50	CTH	10.838(MT)	
4		HOT ROLLED ALLOY STEEL ROUND BARS PEELED 38B3 26.10MM X 5600MM 52BUNDLES	CTH	74.958(MT)	

11.Declaration by the exporter
The undersigned hereby declares that the above details and statements are correct, that all the goods were produced in
THE REPUBLIC OF KOREA
(Country)
and that they comply with the origin requirements specified for these goods in the KOREA-ASEAN Free Trade Area Preferential Tariff for goods exported to
THAILAND
(Importing Country)

Seoul, Republic of Korea, 30-SEP-2024
Place and date, signature of authorized signatory

12.Certification
It is hereby certified on the basis of control carried out, that the declaration by the exporter is correct.

YOO YEASEUL

YOO YEA SEUL

SEOUL MAIN CUSTOMS REPUBLIC OF KOREA 관세청 KOREA CUSTOMS SERVICE 1678

30-SEP-2024 SEOUL MAIN CUSTOMS REPUBLIC OF KOREA
Place and date, signature and stamp of certifying authority

13. ☐ Third Country Invoicing ☐ Exhibition ☐ Back-to-Back C/O

※ You can verify the authenticity of this Certificate of Origin at **www.customs.go.kr/co.html**

Reference No. C010-24-0043186
Reference Code. rnu1-ewm8

Original

5.Item number	6.Marks and numbers on packages	7.Number and type of packages, description of goods (including quantity where appropriate and HS number of the importing country)	8.Origin criterion (see notes overleaf)	9.Gross weight or other quantity, and Value (FOB only when RVC criterion is used)	10.Number and date of invoices
		74.958 MT HS No. 7228.50			
5 ////////		HOT ROLLED STEEL ROUND BARS S53C 55.00MM X 5800MM 56BUNDLES 137.192 MT HS No. 7214.99 //	CTH ////////////////	137.192(MT) //////////////////	

11.Declaration by the exporter

The undersigned hereby declares that the above details and statements are correct, that all the goods were produced in

THE REPUBLIC OF KOREA
(Country)

and that they comply with the origin requirements specified for these goods in the KOREA-ASEAN Free Trade Area Preferential Tariff for goods exported to

THAILAND
(Importing Country)

Seoul, Republic of Korea, 30-SEP-2024
Place and date, signature of authorized signatory

12.Certification

It is hereby certified on the basis of control carried out, that the declaration by the exporter is correct.

YOO YEA SEUL

YOO YEA SEUL

SEOUL MAIN CUSTOMS
관세청
KOREA CUSTOMS SERVICE
REPUBLIC OF KOREA

30-SEP-2024 SEOUL MAIN CUSTOMS REPUBLIC OF KOREA
Place and date, signature and stamp of certifying authority

13. ☐ Third Country Invoicing ☐ Exhibition ☐ Back-to-Back C/O

※ You can verify the authenticity of this Certificate of Origin at **www.customs.go.kr/co.html**

Triplicate

1.Goods consigned from (Exporter's business name, address, country)
TOYOTA TSUSHO KOREA CORPORATION
30F, MIRAE ASSET CENTER 1 WEST TOWER, 67, SUHA-DONG, JUNG-GU, SEOUL 04539, KOREA
Tel: 02-6744-6736 Fax: 02-6744-6897

Reference No. C010-24-0043186

Reference code. rnu1-ewm8

KOREA-ASEAN FREE TRADE AREA PREFERENTIAL TARIFF CERTIFICATE OF ORIGIN

(Combined Declaration and Certificate)
FORM AK
Issued in the REPUBLIC OF KOREA
(Country)
See Notes Overleaf

2.Goods consigned to (Consignee's name, address, country)
TOYOTA TSUSHO THAILAND CO LTD
607 ASOKE-DINDAENG ROAD, KWAENG DINDAENG, KHET DINDAENG BANGKOK 10400 THAILAND

3.Means of transport and route(as far as known)
Departure date : 30-SEP-2024
Vessel's name/Aircraft etc : KMTC TOKYO 2412S
Port of Discharge : LAEM CHABANG, Thailand

4. For official use
☐ Preferential Treatment Given Under KOREA-ASEAN Free Trade Area Preferential Tariff
☐ Preferential Treatment Not Given (Please state reason/s)

Signature of Authorized Signatory of the importing Country

5.Item number	6.Marks and numbers on packages	7.Number and type of packages, description of goods (including quantity where appropriate and HS number of the importing country)	8.Origin criterion (see notes overleaf)	9.Gross weight or other quantity, and Value (FOB only when RVC criterion is used)	10.Number and date of invoices
1	NTN GRADE HEAT NO SIZE Q'TY SEAH BESTEEL //////////////////////////	HOT ROLLED ALLOY STEEL ROUND BARS 38B3 29.00MM X 5750MM 33BUNDLES 75.784 MT HS No. 7228.30	CTH	75.784(MT)	TTKT2-NTNTH-240905 23-SEP-2024 ////////////////
2		HOT ROLLED ALLOY STEEL ROUND BARS 38B3 30.50MM X 5600MM 2BUNDLES 4.27 MT HS No. 7228.30	CTH	4.27(MT)	
3		HOT ROLLED ALLOY STEEL ROUND BARS PEELED 38B3 24.00MM X 5600MM 8BUNDLES 10.838 MT HS No. 7228.50	CTH	10.838(MT)	
4		HOT ROLLED ALLOY STEEL ROUND BARS PEELED 38B3 26.10MM X 5600MM 52BUNDLES	CTH	74.958(MT)	

11.Declaration by the exporter
The undersigned hereby declares that the above details and statements are correct, that all the goods were produced in
THE REPUBLIC OF KOREA
(Country)
and that they comply with the origin requirements specified for these goods in the KOREA-ASEAN Free Trade Area Preferential Tariff for goods exported to
THAILAND
(Importing Country)

Seoul, Republic of Korea, 30-SEP-2024
Place and date, signature of authorized signatory

12.Certification
It is hereby certified on the basis of control carried out, that the declaration by the exporter is correct.

YOO YEASEUL

YOO YEA SEUL

SEOUL MAIN CUSTOMS REPUBLIC OF KOREA
관세청 KOREA CUSTOMS SERVICE 1678

30-SEP-2024 SEOUL MAIN CUSTOMS REPUBLIC OF KOREA
Place and date, signature and stamp of certifying authority

13. ☐ Third Country Invoicing ☐ Exhibition ☐ Back-to-Back C/O

※ You can verify the authenticity of this Certificate of Origin at **www.customs.go.kr/co.html**

Reference No. C010-24-0043186
Reference Code. rnu1-ewm8

Triplicate

5.Item number	6.Marks and numbers on packages	7.Number and type of packages, description of goods (including quantity where appropriate and HS number of the importing country)	8.Origin criterion (see notes overleaf)	9.Gross weight or other quantity, and Value (FOB only when RVC criterion is used)	10.Number and date of invoices
		74.958 MT HS No. 7228.50			
5 ////////		HOT ROLLED STEEL ROUND BARS S53C 55.00MM X 5800MM 56BUNDLES 137.192 MT HS No. 7214.99 //	CTH ////////////////	137.192(MT) //////////////////	

11.Declaration by the exporter

The undersigned hereby declares that the above details and statements are correct, that all the goods were produced in

THE REPUBLIC OF KOREA
(Country)

and that they comply with the origin requirements specified for these goods in the KOREA-ASEAN Free Trade Area Preferential Tariff for goods exported to

THAILAND
(Importing Country)

Seoul, Republic of Korea, 30-SEP-2024
Place and date, signature of authorized signatory

12.Certification

It is hereby certified on the basis of control carried out, that the declaration by the exporter is correct.

YOO YEA SEUL

YOO YEA SEUL

SEOUL MAIN CUSTOMS REPUBLIC OF KOREA 관세청 KOREA CUSTOMS SERVICE 1676

30-SEP-2024 SEOUL MAIN CUSTOMS REPUBLIC OF KOREA
Place and date, signature and stamp of certifying authority

13. ☐ Third Country Invoicing ☐ Exhibition ☐ Back-to-Back C/O

※ You can verify the authenticity of this Certificate of Origin at **www.customs.go.kr/co.html**

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006661
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24662
Size : 30.5 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Chemical Composition (wt. %)										
		C	Si	Mn	P	S	Cu	Ni	Cr	Al	Ti	B
		×100	×100	×100	×1000	×1000	×100	×100	×100	×1000	×1000	×10000
Spec.	Min.	37	15	85						20	30	8
	Max.	40	35	110	30	25	25	20	20	50	60	30
Ladle Result		38	23	89	18	13	13	5	13	25	36	22

Inspection Items		Hardenability(End Quenching Method) HRC, mm												
		1.5	3	5	7	9	11	13	15	20	25	30	35	40
Spec.	Min.	52	50	48	39	31	25	20						
	Max.	60	59	58	57	54	48	42	36	30	27	25	23	22
Result		55	55	54	54	49	35	28	25	23	20	18	17	14

Inspection Items		Nonmetallic Inclusion (ASTM E-45)							
		A(T)	A(H)	B(T)	B(H)	C(T)	C(H)	D(T)	D(H)
Spec.	Min.	0	0	0	0	0	0	0	0
	Max.	3	2	2.5	2	2	1	1.5	1
Result		3.0	1.0	.2	.0	.0	.0	1.0	.5

Inspection Items		Macro Structure			
		DENDRITE	PIT	CENTER	PATTERN
Spec.	Min.				
	Max.	3	3	3	2
Result		1	1	1	1

Inspection Items		Austenite Grain Size
Spec.	Min.	5
	Max.	
Result		7.5

Inspection Items		Decarburized Layer (mm)
		DM-T
Spec.	Min.	0
	Max.	.25
Result		.23

Inspection Items		Gas Analysis (ppm)	
		O_2	N_2
Spec.	Min.		
	Max.	20	120
Result		9.13	29.43

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006661
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24662
Size : 30.5 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Macro Streak Flaw		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Micro Structure		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Product Hardness (HB)		
		MID		
Spec.	Min.	172		
	Max.	223		
Result		215		

Inspection Items		Reduction Ratio		
Spec.	Min.	6		
	Max.			
Result		44.3		

Inspection Items		Surface Inspection (mm)		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Ultrasonic Test		
Spec.	Min.			
	Max.			
Result		GOOD		

Bundle	TOTAL									
Quantity(pcs)	133									
Weight(kg)	4,270									
Length(mm)	5,600									

- According to SR2021000492 approved.
- Al killed and Vacuum degassed
- Appropriate cutting of head and tail of casting sequence
- Chamfering of each end

* MADE IN KOREA / * P.O.# : PT647NTN028

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006662
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24527
Size : 29 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Chemical Composition (wt. %)										
		C	Si	Mn	P	S	Cu	Ni	Cr	Al	Ti	B
		×100	×100	×100	×1000	×1000	×100	×100	×100	×1000	×1000	×10000
Spec.	Min.	37	15	85						20	30	8
	Max.	40	35	110	30	25	25	20	20	50	60	30
Ladle Result		40	25	91	17	16	15	8	14	24	33	24

Inspection Items		Hardenability(End Quenching Method) HRC, mm												
		1.5	3	5	7	9	11	13	15	20	25	30	35	40
Spec.	Min.	52	50	48	39	31	25	20						
	Max.	60	59	58	57	54	48	42	36	30	27	25	23	22
Result		55	54	54	53	50	41	32	26	23	21	20	18	16

Inspection Items		Nonmetallic Inclusion (ASTM E-45)							
		A(T)	A(H)	B(T)	B(H)	C(T)	C(H)	D(T)	D(H)
Spec.	Min.	0	0	0	0	0	0	0	0
	Max.	3	2	2.5	2	2	1	1.5	1
Result		2.6	.7	.2	.4	.0	.0	1.0	.5

Inspection Items		Macro Structure			
		DENDRITE	PIT	CENTER	PATTERN
Spec.	Min.				
	Max.	3	3	3	2
Result		1	1	1	1

Inspection Items		Austenite Grain Size
Spec.	Min.	5
	Max.	
Result		7.5

Inspection Items		Decarburized Layer (mm)
		DM-T
Spec.	Min.	0
	Max.	.25
Result		.17

Inspection Items		Gas Analysis (ppm)	
		O_2	N_2
Spec.	Min.		
	Max.	20	120
Result		10.73	43.03

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006662
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24527
Size : 29 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Macro Streak Flaw		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Micro Structure		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Product Hardness (HB)		
		MID		
Spec.	Min.	172		
	Max.	223		
Result		211		

Inspection Items		Reduction Ratio		
Spec.	Min.	6		
	Max.			
Result		49.1		

Inspection Items		Surface Inspection (mm)		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Ultrasonic Test		
Spec.	Min.			
	Max.			
Result		GOOD		

Bundle	TOTAL									
Quantity(pcs)	841									
Weight(kg)	25,162									
Length(mm)	5,750									

- According to SR2021000492 approved.
- Al killed and Vacuum degassed
- Appropriate cutting of head and tail of casting sequence
- Chamfering of each end

* MADE IN KOREA / * P.O.# : PT647NTN028

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006663
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24527
Size : 29 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Chemical Composition (wt. %)										
		C	Si	Mn	P	S	Cu	Ni	Cr	Al	Ti	B
		×100	×100	×100	×1000	×1000	×100	×100	×100	×1000	×1000	×10000
Spec.	Min.	37	15	85						20	30	8
	Max.	40	35	110	30	25	25	20	20	50	60	30
Ladle Result		40	25	91	17	16	15	8	14	24	33	24

Inspection Items		Hardenability(End Quenching Method) HRC, mm												
		1.5	3	5	7	9	11	13	15	20	25	30	35	40
Spec.	Min.	52	50	48	39	31	25	20						
	Max.	60	59	58	57	54	48	42	36	30	27	25	23	22
Result		55	54	54	53	50	41	32	26	23	21	20	18	16

Inspection Items		Nonmetallic Inclusion (ASTM E-45)							
		A(T)	A(H)	B(T)	B(H)	C(T)	C(H)	D(T)	D(H)
Spec.	Min.	0	0	0	0	0	0	0	0
	Max.	3	2	2.5	2	2	1	1.5	1
Result		2.6	.7	.2	.4	.0	.0	1.0	.5

Inspection Items		Macro Structure			
		DENDRITE	PIT	CENTER	PATTERN
Spec.	Min.				
	Max.	3	3	3	2
Result		1	1	1	1

Inspection Items		Austenite Grain Size
Spec.	Min.	5
	Max.	
Result		7.5

Inspection Items		Decarburized Layer (mm)
		DM-T
Spec.	Min.	0
	Max.	.25
Result		.17

Inspection Items		Gas Analysis (ppm)	
		O_2	N_2
Spec.	Min.		
	Max.	20	120
Result		10.73	43.03

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006663
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24527
Size : 29 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Macro Streak Flaw		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Micro Structure		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Product Hardness (HB)		
		MID		
Spec.	Min.	172		
	Max.	223		
Result		215		

Inspection Items		Reduction Ratio		
Spec.	Min.	6		
	Max.			
Result		49.1		

Inspection Items		Surface Inspection (mm)		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Ultrasonic Test		
Spec.	Min.			
	Max.			
Result		GOOD		

Bundle	TOTAL									
Quantity(pcs)	849									
Weight(kg)	25,398									
Length(mm)	5,750									

- According to SR2021000492 approved.
- Al killed and Vacuum degassed
- Appropriate cutting of head and tail of casting sequence
- Chamfering of each end

* MADE IN KOREA / * P.O.# : PT647NTN028

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006664
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24662
Size : 29 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Chemical Composition (wt. %)										
		C	Si	Mn	P	S	Cu	Ni	Cr	Al	Ti	B
		×100	×100	×100	×1000	×1000	×100	×100	×100	×1000	×1000	×10000
Spec.	Min.	37	15	85						20	30	8
	Max.	40	35	110	30	25	25	20	20	50	60	30
Ladle Result		38	23	89	18	13	13	5	13	25	36	22

Inspection Items		Hardenability(End Quenching Method) HRC, mm												
		1.5	3	5	7	9	11	13	15	20	25	30	35	40
Spec.	Min.	52	50	48	39	31	25	20						
	Max.	60	59	58	57	54	48	42	36	30	27	25	23	22
Result		55	55	54	54	49	35	28	25	23	20	18	17	14

Inspection Items		Nonmetallic Inclusion (ASTM E-45)							
		A(T)	A(H)	B(T)	B(H)	C(T)	C(H)	D(T)	D(H)
Spec.	Min.	0	0	0	0	0	0	0	0
	Max.	3	2	2.5	2	2	1	1.5	1
Result		3.0	1.0	.2	.0	.0	.0	1.0	.5

Inspection Items		Macro Structure			
		DENDRITE	PIT	CENTER	PATTERN
Spec.	Min.				
	Max.	3	3	3	2
Result		1	1	1	1

Inspection Items		Austenite Grain Size
Spec.	Min.	5
	Max.	
Result		7.5

Inspection Items		Decarburized Layer (mm)
		DM-T
Spec.	Min.	0
	Max.	.25
Result		.16

Inspection Items		Gas Analysis (ppm)	
		O_2	N_2
Spec.	Min.		
	Max.	20	120
Result		9.13	29.43

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006664
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24662
Size : 29 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Macro Streak Flaw		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Micro Structure		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Product Hardness (HB)		
		MID		
Spec.	Min.	172		
	Max.	223		
Result		207		

Inspection Items		Reduction Ratio		
Spec.	Min.	6		
	Max.			
Result		49.1		

Inspection Items		Surface Inspection (mm)		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Ultrasonic Test		
Spec.	Min.			
	Max.			
Result		GOOD		

Bundle	TOTAL									
Quantity(pcs)	844									
Weight(kg)	25,224									
Length(mm)	5,750									

- According to SR2021000492 approved.
- Al killed and Vacuum degassed
- Appropriate cutting of head and tail of casting sequence
- Chamfering of each end

* MADE IN KOREA / * P.O.# : PT647NTN028

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006665
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24810
Size : 24 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled , As Peeled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Chemical Composition (wt. %)										
		C	Si	Mn	P	S	Cu	Ni	Cr	Al	Ti	B
		×100	×100	×100	×1000	×1000	×100	×100	×100	×1000	×1000	×10000
Spec.	Min.	37	15	85						20	30	8
	Max.	40	35	110	30	25	25	20	20	50	60	30
Ladle Result		38	26	88	16	14	14	7	14	22	35	22

Inspection Items		Hardenability(End Quenching Method) HRC, mm												
		1.5	3	5	7	9	11	13	15	20	25	30	35	40
Spec.	Min.	52	50	48	39	31	25	20						
	Max.	60	59	58	57	54	48	42	36	30	27	25	23	22
Result		55	54	54	53	50	40	31	27	24	21	20	18	16

Inspection Items		Nonmetallic Inclusion (ASTM E-45)							
		A(T)	A(H)	B(T)	B(H)	C(T)	C(H)	D(T)	D(H)
Spec.	Min.								
	Max.	3	2	2.5	2	2	1	1.5	1
Result		3.0	.8	.1	.0	.0	.0	1.0	.5

Inspection Items		Macro Structure			
		DENDRITE	PIT	CENTER	PATTERN
Spec.	Min.				
	Max.	3	3	3	2
Result		1	1	1	1

Inspection Items		Austenite Grain Size
Spec.	Min.	5
	Max.	
Result		8.0

Inspection Items		Decarburized Layer (mm)
		DM-T
Spec.	Min.	0
	Max.	0
Result		.00

Inspection Items		Gas Analysis (ppm)	
		O_2	N_2
Spec.	Min.		
	Max.	20	120
Result		6.30	44.43

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006665
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24810
Size : 24 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled , As Peeled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Macro Streak Flaw		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Micro Structure		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Product Hardness (HB)		
		MID		
Spec.	Min.	172		
	Max.	223		
Result		218		

Inspection Items		Reduction Ratio		
Spec.	Min.	6		
	Max.			
Result		61.0		

Inspection Items		Surface Inspection (mm)		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Ultrasonic Test		
Spec.	Min.			
	Max.			
Result		GOOD		

Bundle	TOTAL									
Quantity(pcs)	544									
Weight(kg)	10,838									
Length(mm)	5,600									

* MADE IN KOREA / * P.O.# : PT646NTN029

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006666
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24807
Size : 26.1 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled , As Peeled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Chemical Composition (wt. %)										
		C	Si	Mn	P	S	Cu	Ni	Cr	Al	Ti	B
		×100	×100	×100	×1000	×1000	×100	×100	×100	×1000	×1000	×10000
Spec.	Min.	37	15	85						20	30	8
	Max.	40	35	110	30	25	25	20	20	50	60	30
Ladle Result		37	23	88	19	12	14	8	15	22	34	22

Inspection Items		Hardenability(End Quenching Method) HRC, mm												
		1.5	3	5	7	9	11	13	15	20	25	30	35	40
Spec.	Min.	52	50	48	39	31	25	20						
	Max.	60	59	58	57	54	48	42	36	30	27	25	23	22
Result		55	55	53	52	51	41	31	27	23	21	19	18	15

Inspection Items		Nonmetallic Inclusion (ASTM E-45)							
		A(T)	A(H)	B(T)	B(H)	C(T)	C(H)	D(T)	D(H)
Spec.	Min.								
	Max.	3	2	2.5	2	2	1	1.5	1
Result		2.6	.9	.0	.0	.0	.0	1.0	.5

Inspection Items		Macro Structure			
		DENDRITE	PIT	CENTER	PATTERN
Spec.	Min.				
	Max.	3	3	3	2
Result		1	1	1	1

Inspection Items		Austenite Grain Size
Spec.	Min.	5
	Max.	
Result		7.5

Inspection Items		Decarburized Layer (mm)
		DM-T
Spec.	Min.	0
	Max.	0
Result		.00

Inspection Items		Gas Analysis (ppm)	
		O_2	N_2
Spec.	Min.		
	Max.	20	120
Result		14.27	38.47

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006666
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24807
Size : 26.1 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled , As Peeled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Macro Streak Flaw		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Micro Structure		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Product Hardness (HB)		
		MID		
Spec.	Min.	172		
	Max.	223		
Result		206		

Inspection Items		Reduction Ratio		
Spec.	Min.	6		
	Max.			
Result		52.6		

Inspection Items		Surface Inspection (mm)		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Ultrasonic Test		
Spec.	Min.			
	Max.			
Result		GOOD		

Bundle	TOTAL									
Quantity(pcs)	189									
Weight(kg)	4,458									
Length(mm)	5,600									

- According to SR2021000938 approved.
- Al killed and Vacuum degassed
- Appropriate cutting of head and tail of casting sequence
- Chamfering of each end

* MADE IN KOREA / * P.O.# : PT647NTN029

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006667
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24807
Size : 26.1 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled , As Peeled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Chemical Composition (wt. %)										
		C	Si	Mn	P	S	Cu	Ni	Cr	Al	Ti	B
		×100	×100	×100	×1000	×1000	×100	×100	×100	×1000	×1000	×10000
Spec.	Min.	37	15	85						20	30	8
	Max.	40	35	110	30	25	25	20	20	50	60	30
Ladle Result		37	23	88	19	12	14	8	15	22	34	22

Inspection Items		Hardenability(End Quenching Method) HRC, mm												
		1.5	3	5	7	9	11	13	15	20	25	30	35	40
Spec.	Min.	52	50	48	39	31	25	20						
	Max.	60	59	58	57	54	48	42	36	30	27	25	23	22
Result		55	55	53	52	51	41	31	27	23	21	19	18	15

Inspection Items		Nonmetallic Inclusion (ASTM E-45)							
		A(T)	A(H)	B(T)	B(H)	C(T)	C(H)	D(T)	D(H)
Spec.	Min.								
	Max.	3	2	2.5	2	2	1	1.5	1
Result		2.6	.9	.0	.0	.0	.0	1.0	.5

Inspection Items		Macro Structure			
		DENDRITE	PIT	CENTER	PATTERN
Spec.	Min.				
	Max.	3	3	3	2
Result		1	1	1	1

Inspection Items		Austenite Grain Size
Spec.	Min.	5
	Max.	
Result		7.5

Inspection Items		Decarburized Layer (mm)
		DM-T
Spec.	Min.	0
	Max.	0
Result		.00

Inspection Items		Gas Analysis (ppm)	
		O_2	N_2
Spec.	Min.		
	Max.	20	120
Result		14.27	38.47

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006667
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24807
Size : 26.1 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled , As Peeled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Macro Streak Flaw		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Micro Structure		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Product Hardness (HB)		
		MID		
Spec.	Min.	172		
	Max.	223		
Result		204		

Inspection Items		Reduction Ratio		
Spec.	Min.	6		
	Max.			
Result		52.6		

Inspection Items		Surface Inspection (mm)		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Ultrasonic Test		
Spec.	Min.			
	Max.			
Result		GOOD		

Bundle	TOTAL									
Quantity(pcs)	474									
Weight(kg)	11,184									
Length(mm)	5,600									

- According to SR2021000938 approved.
- Al killed and Vacuum degassed
- Appropriate cutting of head and tail of casting sequence
- Chamfering of each end

* MADE IN KOREA / * P.O.# : PT647NTN029

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006668
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24807
Size : 26.1 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled , As Peeled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Chemical Composition (wt. %)										
		C	Si	Mn	P	S	Cu	Ni	Cr	Al	Ti	B
		×100	×100	×100	×1000	×1000	×100	×100	×100	×1000	×1000	×10000
Spec.	Min.	37	15	85						20	30	8
	Max.	40	35	110	30	25	25	20	20	50	60	30
Ladle Result		37	23	88	19	12	14	8	15	22	34	22

Inspection Items		Hardenability(End Quenching Method) HRC, mm												
		1.5	3	5	7	9	11	13	15	20	25	30	35	40
Spec.	Min.	52	50	48	39	31	25	20						
	Max.	60	59	58	57	54	48	42	36	30	27	25	23	22
Result		55	55	53	52	51	41	31	27	23	21	19	18	15

Inspection Items		Nonmetallic Inclusion (ASTM E-45)							
		A(T)	A(H)	B(T)	B(H)	C(T)	C(H)	D(T)	D(H)
Spec.	Min.								
	Max.	3	2	2.5	2	2	1	1.5	1
Result		2.6	.9	.0	.0	.0	.0	1.0	.5

Inspection Items		Macro Structure			
		DENDRITE	PIT	CENTER	PATTERN
Spec.	Min.				
	Max.	3	3	3	2
Result		1	1	1	1

Inspection Items		Austenite Grain Size
Spec.	Min.	5
	Max.	
Result		7.5

Inspection Items		Decarburized Layer (mm)
		DM-T
Spec.	Min.	0
	Max.	0
Result		.00

Inspection Items		Gas Analysis (ppm)	
		O_2	N_2
Spec.	Min.		
	Max.	20	120
Result		14.27	38.47

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006668
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24807
Size : 26.1 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled , As Peeled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Macro Streak Flaw		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Micro Structure		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Product Hardness (HB)		
		MID		
Spec.	Min.	172		
	Max.	223		
Result		208		

Inspection Items		Reduction Ratio		
Spec.	Min.	6		
	Max.			
Result		52.6		

Inspection Items		Surface Inspection (mm)		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Ultrasonic Test		
Spec.	Min.			
	Max.			
Result		GOOD		

Bundle	TOTAL									
Quantity(pcs)	947									
Weight(kg)	22,336									
Length(mm)	5,600									

- According to SR2021000938 approved.
- Al killed and Vacuum degassed
- Appropriate cutting of head and tail of casting sequence
- Chamfering of each end

* MADE IN KOREA / * P.O.# : PT647NTN029

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006669
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24811
Size : 26.1 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled , As Peeled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Chemical Composition (wt. %)										
		C	Si	Mn	P	S	Cu	Ni	Cr	Al	Ti	B
		×100	×100	×100	×1000	×1000	×100	×100	×100	×1000	×1000	×10000
Spec.	Min.	37	15	85						20	30	8
	Max.	40	35	110	30	25	25	20	20	50	60	30
Ladle Result		37	26	88	21	14	15	7	16	23	36	21

Inspection Items		Hardenability(End Quenching Method) HRC, mm												
		1.5	3	5	7	9	11	13	15	20	25	30	35	40
Spec.	Min.	52	50	48	39	31	25	20						
	Max.	60	59	58	57	54	48	42	36	30	27	25	23	22
Result		54	54	54	53	50	40	30	25	23	21	19	17	15

Inspection Items		Nonmetallic Inclusion (ASTM E-45)							
		A(T)	A(H)	B(T)	B(H)	C(T)	C(H)	D(T)	D(H)
Spec.	Min.								
	Max.	3	2	2.5	2	2	1	1.5	1
Result		2.9	.7	.2	.0	.0	.0	1.0	.5

Inspection Items		Macro Structure			
		DENDRITE	PIT	CENTER	PATTERN
Spec.	Min.				
	Max.	3	3	3	2
Result		1	1	1	1

Inspection Items		Austenite Grain Size
Spec.	Min.	5
	Max.	
Result		8.0

Inspection Items		Decarburized Layer (mm)
		DM-T
Spec.	Min.	0
	Max.	0
Result		.00

Inspection Items		Gas Analysis (ppm)	
		O_2	N_2
Spec.	Min.		
	Max.	20	120
Result		6.83	41.20

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006669
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24811
Size : 26.1 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled , As Peeled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Macro Streak Flaw		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Micro Structure		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Product Hardness (HB)		
		MID		
Spec.	Min.	172		
	Max.	223		
Result		199		

Inspection Items		Reduction Ratio		
Spec.	Min.	6		
	Max.			
Result		52.6		

Inspection Items		Surface Inspection (mm)		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Ultrasonic Test		
Spec.	Min.			
	Max.			
Result		GOOD		

Bundle	TOTAL									
Quantity(pcs)	940									
Weight(kg)	22,160									
Length(mm)	5,600									

- According to SR2021000938 approved.
- Al killed and Vacuum degassed
- Appropriate cutting of head and tail of casting sequence
- Chamfering of each end

* MADE IN KOREA / * P.O.# : PT647NTN029

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006670
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24811
Size : 26.1 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled , As Peeled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Chemical Composition (wt. %)										
		C	Si	Mn	P	S	Cu	Ni	Cr	Al	Ti	B
		×100	×100	×100	×1000	×1000	×100	×100	×100	×1000	×1000	×10000
Spec.	Min.	37	15	85						20	30	8
	Max.	40	35	110	30	25	25	20	20	50	60	30
Ladle Result		37	26	88	21	14	15	7	16	23	36	21

Inspection Items		Hardenability(End Quenching Method) HRC, mm												
		1.5	3	5	7	9	11	13	15	20	25	30	35	40
Spec.	Min.	52	50	48	39	31	25	20						
	Max.	60	59	58	57	54	48	42	36	30	27	25	23	22
Result		54	54	54	53	50	40	30	25	23	21	19	17	15

Inspection Items		Nonmetallic Inclusion (ASTM E-45)							
		A(T)	A(H)	B(T)	B(H)	C(T)	C(H)	D(T)	D(H)
Spec.	Min.								
	Max.	3	2	2.5	2	2	1	1.5	1
Result		2.9	.7	.2	.0	.0	.0	1.0	.5

Inspection Items		Macro Structure			
		DENDRITE	PIT	CENTER	PATTERN
Spec.	Min.				
	Max.	3	3	3	2
Result		1	1	1	1

Inspection Items		Austenite Grain Size
Spec.	Min.	5
	Max.	
Result		8.0

Inspection Items		Decarburized Layer (mm)
		DM-T
Spec.	Min.	0
	Max.	0
Result		.00

Inspection Items		Gas Analysis (ppm)	
		O_2	N_2
Spec.	Min.		
	Max.	20	120
Result		6.83	41.20

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-23
Cert. No. : 202409-006670
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : 38B3
Heat No. : D24811
Size : 26.1 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled , As Peeled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Macro Streak Flaw		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Micro Structure		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Product Hardness (HB)		
		MID		
Spec.	Min.	172		
	Max.	223		
Result		202		

Inspection Items		Reduction Ratio		
Spec.	Min.	6		
	Max.			
Result		52.6		

Inspection Items		Surface Inspection (mm)		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Ultrasonic Test		
Spec.	Min.			
	Max.			
Result		GOOD		

Bundle	TOTAL									
Quantity(pcs)	628									
Weight(kg)	14,820									
Length(mm)	5,600									

- According to SR2021000938 approved.
- Al killed and Vacuum degassed
- Appropriate cutting of head and tail of casting sequence
- Chamfering of each end

* MADE IN KOREA / * P.O.# : PT647NTN029

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-29
Cert. No. : 202409-006671
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : S53C
Heat No. : D24943
Size : 55 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Chemical Composition (wt. %)																			
		C	Si	Mn	P	S	Cu	Ni	Cr	Al	Ni+Cr										
		×100	×100	×100	×1000	×1000	×100	×100	×100	×1000	×100										
Spec.	Min.	50	15	70					10												
	Max.	56	35	90	25	25	25	20	20	50	35										
Ladle Result		51	23	77	23	3	15	7	16	21	23										

Inspection Items		Macro Structure					
		DENDRITE	PIT	CENTER	PATTERN		
Spec.	Min.						
	Max.	3	3	3	2		
Result		1	1	1	1		

Inspection Items		Test Piece Tensile Test (N /)					
		TS	YS	EL(%)	ROA(%)		
Spec.	Min.	780	590	14	35		
	Max.						
Result		856.22	683.72	19.80	50.87		

Inspection Items		Austenite Grain Size		
Spec.	Min.	5		
	Max.			
Result		7.5		

Inspection Items		Decarburized Layer (mm)		
		DM-T		
Spec.	Min.			
	Max.	.5		
Result		.19		

Inspection Items		Gas Analysis (ppm)		
		O_2		
Spec.	Min.			
	Max.	15		
Result		5.95		

Inspection Items		Macro Streak Flaw		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Micro Structure		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Nonmetallic Inclusion (JIS G 0555)		
		dA	dT	d(B+C)
Spec.	Min.			
	Max.	.1	.2	.1
Result		.04	.05	.01

Inspection Items		Product Hardness (HB)		
		MID		
Spec.	Min.			
	Max.	241		
Result		229		

Inspection Items		Reduction Ratio		
Spec.	Min.	6		
	Max.			
Result		13.6		

Inspection Items		Segregation Test (%)		
Spec.	Min.			
	Max.			
Result		GOOD		

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2024-09-29
Cert. No. : 202409-006671
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade : S53C
Heat No. : D24943
Size : 55 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled

Customer : NTN

Supplier : SeAH Besteel
Serial-No. :

Inspection Items		Surface Inspection (mm)		
Spec.	Min.			
	Max.			
Result		GOOD		

Inspection Items		Test Piece Charpy Impact Test (J /)		
		TEMP.(℃)	L-AVERAGE	
Spec.	Min.	20	59	
	Max.	20		
Result		20	140.97	

Inspection Items		Test Piece Hardness (HB)		
		SURFACE		
Spec.	Min.	229		
	Max.	285		
Result		244		

Inspection Items		Ultrasonic Test		
Spec.	Min.			
	Max.			
Result		GOOD		

Bundle	TOTAL									
Quantity(pcs)	1,267									
Weight(kg)	137,192									
Length(mm)	5,800									

<<Remark>> - According to approved Documenet SRR2020000461
- Specification : Draft for CVJ, HS-D-SC0550HE_2003(1)
- Billet : 180x180
- The result of macro grade of the semi-finished(as casted) product : OK
* MADE IN KOREA / * P.O.# : PT648NTN027

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.

WORLD BEST LOGIS CO., LTD.

RM307, HANARO BLDG., 25, INSA-DONG 5-GIL, JONGNO-GU, SEOUL 03162, KOREA.

Tel : 82-70-7076-8518 Fax : 82-70-7076-9400 world@wblkorea.com

TALLY SHEET

SHIPPER : TOYOTA **DEST.,: LAEM CHABANG, THAILAND** **COMMODITY : STEEL ROUND BAR** **2024-09-24**

NO.	CONTAINER NO.	SEAL NO.	PROD. NO.	LENGTH	G.WT	Q`ty(BUNDLE)	Q'ty(BAR)	PO NO.
1	STXU2040587	PANP769914	E24S8K0374-G009	5,750	2,096	1	70	PT647NTN028
			E24S8K0374-G010	5,750	1,916	1	64	PT647NTN028
			E24S8K0374-G011	5,750	1,916	1	64	PT647NTN028
			E24S8K0374-G002	5,750	2,480	1	83	PT647NTN028
			E24S8K0374-G005	5,750	2,484	1	83	PT647NTN028
			E24S8K0374-G008	5,750	2,096	1	70	PT647NTN028
			E24S8K0374-G007	5,750	2,484	1	83	PT647NTN028
			E24S8K0374-G006	5,750	2,484	1	83	PT647NTN028
			E24S8K0376-G011	5,750	1,822	1	61	PT647NTN028
			E24S8K0376-G008	5,750	2,092	1	70	PT647NTN028
			E24S8J0376-G001	5,750	2,480	1	83	PT647NTN028
			11 BUNDLES		**24,350**	**11**	**814**	
2	STXU2070088	PANP769915	E24S9K0028-0003	5,600	1,486	1	63	PT647NTN029
			E24S9K0029-0001	5,600	1,392	1	59	PT647NTN029
			E24S9K0029-0002	5,600	1,392	1	59	PT647NTN029
			E24S9K0029-0007	5,600	1,416	1	60	PT647NTN029
			E24S9K0029-0004	5,600	1,392	1	59	PT647NTN029
			E24S9K0029-0003	5,600	1,392	1	59	PT647NTN029
			E24S9K0029-0008	5,600	1,416	1	60	PT647NTN029
			E24S9K0029-0006	5,600	1,392	1	59	PT647NTN029
			E24S9K0029-0005	5,600	1,392	1	59	PT647NTN029
			E24S9K0033-0008	5,600	1,416	1	60	PT647NTN029
			E24S9K0033-0005	5,600	1,416	1	60	PT647NTN029
			E24S9K0033-0011	5,600	1,038	1	44	PT647NTN029
			E24S9K0033-0006	5,600	1,416	1	60	PT647NTN029
			E24S9K0033-0007	5,600	1,416	1	60	PT647NTN029

			E24S9K0033-0010	5,600	1,038	1	44	PT647NTN029
			E24S9K0033-0004	5,600	1,416	1	60	PT647NTN029
			E24S9K0033-0003	5,600	1,416	1	60	PT647NTN029
			17 BUNDLES		**23,242**	**17**	**985**	
3	**STXU2052361**	**PANP769916**	E24S8K0393-0007	5,600	1,374	1	69	PT647NTN029
			E24S8K0393-0002	5,600	1,374	1	69	PT647NTN029
			E24S8K0393-0001	5,600	1,374	1	69	PT647NTN029
			E24S8K0393-0005	5,600	1,376	1	69	PT647NTN029
			E24S8K0393-0006	5,600	1,374	1	69	PT647NTN029
			E24S9K0030-0009	5,600	1,486	1	63	PT647NTN029
			E24S9K0030-0006	5,600	1,486	1	63	PT647NTN029
			E24S9K0030-0003	5,600	1,486	1	63	PT647NTN029
			E24S9K0030-0011	5,600	1,486	1	63	PT647NTN029
			E24S9K0030-0010	5,600	1,486	1	63	PT647NTN029
			E24S9K0030-0005	5,600	1,486	1	63	PT647NTN029
			E24S9K0030-0015	5,600	1,510	1	64	PT647NTN029
			E24S9K0032-0013	5,600	1,486	1	63	PT647NTN029
			E24S9K0032-0001	5,600	1,484	1	63	PT647NTN029
			E24S9K0032-0009	5,600	1,486	1	63	PT647NTN029
			E24S9K0032-0010	5,600	1,486	1	63	PT647NTN029
			16 BUNDLES		**23,240**	**16**	**1039**	
4	**STXU2025108**	**PANP769111**	E24S8K0393-0003	5,600	1,374	1	69	PT646NTN029
			E24S8K0393-0004	5,600	1,376	1	69	PT646NTN029
			E24S8K0374-G003	5,750	2,480	1	83	PT647NTN028
			E24S8K0374-G004	5,750	2,482	1	83	PT647NTN028
			E24S8K0376-G003	5,750	2,480	1	83	PT647NTN028
			E24S9K0030-0014	5,600	1,508	1	64	PT647NTN029
			E24S9K0030-0004	5,600	1,486	1	63	PT647NTN029
			E24S9K0030-0002	5,600	1,486	1	63	PT647NTN029
			E24S9K0030-0001	5,600	1,486	1	63	PT647NTN029
			E24S9K0030-0013	5,600	1,486	1	63	PT647NTN029
			E24S9K0030-0007	5,600	1,486	1	63	PT647NTN029

			E24S9K0030-0008	5,600	1,486	1	63	PT647NTN029
			E24S9K0032-0005	5,600	1,486	1	63	PT647NTN029
			E24S9K0032-0006	5,600	1,484	1	63	PT647NTN029
			14 BUNDLES		**23,586**	**14**	**955**	
5	**STXU2039204**	**PANP769112**	E24S8K0393-0008	5,600	1,216	1	61	PT646NTN029
			E24S9K0028-0001	5,600	1,486	1	63	PT647NTN029
			E24S9K0028-0002	5,600	1,486	1	63	PT647NTN029
			E24S9K0030-0012	5,600	1,486	1	63	PT647NTN029
			E24S9K0032-0015	5,600	1,368	1	58	PT647NTN029
			E24S9K0032-0014	5,600	1,484	1	63	PT647NTN029
			E24S9K0032-0012	5,600	1,486	1	63	PT647NTN029
			E24S9K0032-0002	5,600	1,486	1	63	PT647NTN029
			E24S9K0032-0003	5,600	1,484	1	63	PT647NTN029
			E24S9K0032-0004	5,600	1,484	1	63	PT647NTN029
			E24S9K0032-0007	5,600	1,484	1	63	PT647NTN029
			E24S9K0032-0008	5,600	1,486	1	63	PT647NTN029
			E24S9K0032-0011	5,600	1,486	1	63	PT647NTN029
			E24S9K0033-0009	5,600	1,416	1	60	PT647NTN029
			E24S9K0033-0001	5,600	1,416	1	60	PT647NTN029
			E24S9K0033-0002	5,600	1,416	1	60	PT647NTN029
			16 BUNDLES		**23,170**	**16**	**992**	
6	**STXU2025710**	**PANP769113**	E24S8K0373-G001	5,750	2,486	1	83	PT647NTN028
			E24S8K0373-G002	5,750	2,486	1	83	PT647NTN028
			E24S8K0373-G003	5,750	2,484	1	83	PT647NTN028
			E24S8K0373-G007	5,750	2,484	1	83	PT647NTN028
			E24S8K0373-G006	5,750	2,482	1	83	PT647NTN028
			E24S8K0373-G005	5,750	2,484	1	83	PT647NTN028
			E24S8K0373-G009	5,750	2,092	1	70	PT647NTN028
			E24S8K0373-G008	5,750	2,094	1	70	PT647NTN028
			E24S8K0374-G001	5,750	2,480	1	83	PT647NTN028
			E24S8K0376-G004	5,750	2,482	1	83	PT647NTN028
			10 BUNDLES		**24,054**	**10**	**804**	

7	STXU2030017	PANP769114	E24S8K0373-G011	5,750	1,792	1	60	PT647NTN028
			E24S8K0373-G010	5,750	1,794	1	60	PT647NTN028
			E24S8K0373-G004	5,750	2,484	1	83	PT647NTN028
			E24S8K0376-G010	5,750	1,852	1	62	PT647NTN028
			E24S8K0376-G009	5,750	2,092	1	70	PT647NTN028
			E24S8K0376-G007	5,750	2,480	1	83	PT647NTN028
			E24S8K0376-G006	5,750	2,480	1	83	PT647NTN028
			E24S8K0376-G002	5,750	2,482	1	83	PT647NTN028
			E24S8K0376-G005	5,750	2,482	1	83	PT647NTN028
			E24S8K0354-G004	5,600	2,150	1	67	PT647NTN028
			E24S8K0354-G003	5,600	2,120	1	66	PT647NTN028
			11 BUNDLES		**24,208**	**11**	**800**	
8	STXU2072687	PANP769115	E24S9N7015-G050	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G031	5,800	2,494	1	23	PT648NTN027
			E24S9N7015-G030	5,800	2,494	1	23	PT648NTN027
			E24S9N7015-G028	5,800	2,494	1	23	PT648NTN027
			E24S9N7015-G039	5,800	2,492	1	23	PT648NTN027
			E24S9N7015-G038	5,800	2,492	1	23	PT648NTN027
			E24S9N7015-G034	5,800	2,494	1	23	PT648NTN027
			E24S9N7015-G053	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G032	5,800	2,492	1	23	PT648NTN027
			9 BUNDLES		**22,432**	**9**	**207**	
9	STXU2071680	PANP769116	E24S9N7015-G049	5,800	2,492	1	23	PT648NTN027
			E24S9N7015-G020	5,800	2,488	1	23	PT648NTN027
			E24S9N7015-G019	5,800	2,482	1	23	PT648NTN027
			E24S9N7015-G051	5,800	2,492	1	23	PT648NTN027
			E24S9N7015-G040	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G037	5,800	2,494	1	23	PT648NTN027
			E24S9N7015-G036	5,800	2,494	1	23	PT648NTN027
			E24S9N7015-G052	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G055	5,800	1,520	1	14	PT648NTN027
			E24S9N7015-G056	5,800	2,208	1	21	PT648NTN027

			10 BUNDLES		**23,650**	**10**	**219**	
10	**STXU2033166**	**PANP769117**	E24S9N7015-G029	5,800	2,494	1	23	PT648NTN027
			E24S9N7015-G026	5,800	2,496	1	23	PT648NTN027
			E24S9N7015-G047	5,800	2,494	1	23	PT648NTN027
			E24S9N7015-G046	5,800	2,496	1	23	PT648NTN027
			E24S9N7015-G045	5,800	2,496	1	23	PT648NTN027
			E24S9N7015-G044	5,800	2,474	1	23	PT648NTN027
			E24S9N7015-G043	5,800	2,496	1	23	PT648NTN027
			E24S9N7015-G035	5,800	2,494	1	23	PT648NTN027
			E24S9N7015-G033	5,800	2,494	1	23	PT648NTN027
			E24S9N7015-G054	5,800	1,406	1	13	PT648NTN027
			10 BUNDLES		**23,840**	**10**	**220**	
11	**STXU2066365**	**PANP769118**	E24S9N7015-G012	5,800	2,492	1	23	PT648NTN027
			E24S9N7015-G006	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G002	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G001	5,800	2,492	1	23	PT648NTN027
			E24S9N7015-G005	5,800	2,492	1	23	PT648NTN027
			E24S9N7015-G008	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G009	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G010	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G011	5,800	2,490	1	23	PT648NTN027
			9 BUNDLES		**22,416**	**9**	**207**	
12	**STXU2051745**	**PANP769119**	E24S9N7015-G027	5,800	2,492	1	23	PT648NTN027
			E24S9N7015-G025	5,800	2,496	1	23	PT648NTN027
			E24S9N7015-G018	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G017	5,800	2,492	1	23	PT648NTN027
			E24S9N7015-G014	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G013	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G048	5,800	2,494	1	23	PT648NTN027
			E24S9N7015-G042	5,800	2,496	1	23	PT648NTN027
			E24S9N7015-G041	5,800	2,494	1	23	PT648NTN027
			9 BUNDLES		**22,434**	**9**	**207**	

13	**FCIU6151555**	**PANP769120**	E24S9N7015-G024	5,800	2,496	1	23	PT648NTN027
			E24S9N7015-G023	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G022	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G021	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G016	5,800	2,492	1	23	PT648NTN027
			E24S9N7015-G015	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G004	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G003	5,800	2,490	1	23	PT648NTN027
			E24S9N7015-G007	5,800	2,492	1	23	PT648NTN027
			9 BUNDLES		**22,420**	**9**	**207**	

G.TOTAL : 151BUNDLES / NET WEIGHT : 303,042KGS / GROSS WEIGHT : 303,042KGS / 65CBM