

PQ 50/50

Core

B65981A

Preliminary data

- To IEC 62317-13
- Delivery mode: sets

Magnetic characteristics (per set)

$$\Sigma l/A = 0.342 \text{ mm}^{-1}$$



$$l_e = 113.0 \text{ mm}$$

$$A_e = 330.0 \text{ mm}^2$$

$$A_{\min} = 290.0 \text{ mm}^2$$

$$V_e = 37270 \text{ mm}^3$$

Approx. weight 190 g/set



FPK0457-U

Dimensions in mm

Ungapped

Material	A_L value ¹⁾ nH	μ_e	P_V W/set	Ordering code
N87	6500 +30/-20%	1770	< 3.80 (100 mT, 100 kHz, 100 °C)	B65981A0000R087
N97	6700 +30/-20%	1825	< 3.50 (100 mT, 100 kHz, 100 °C)	B65981A0000R097
N95	8200 +30/-20%	2230	< 4.50 (100 mT, 100 kHz, 50 °C – 100 °C) < 5.40 (100 mT, 100 kHz, 120 °C)	B65981A0000R095
N92	4700 +30/-20%	1170	< 6.50 (100 mT, 100 kHz, 100 °C)	B65981A0000R092
N51	8200 +30/-20%	2230	< 6.10 (100 mT, 100 kHz, 25 °C) < 6.50 (100 mT, 100 kHz, 100 °C)	B65981A0000R051

1) Measurement parameter: 10 kHz, 0.25 mT, 100 turns, room temperature.

A_L value is measured acc. to IEC62044-2. An appropriate wringing of cores with polished surface is used to improve reproducibility of the measurement. (It is recommended to rub the mating surfaces themselves six times in a circular or elliptic arc that matches the core profile before measuring A_L value).