

PRODUCT DATA SHEET

Sika® RainTite

ACRYLIC WATERPROOFING

DESCRIPTION

Sika® RainTite waterproofing system consists of a combination of :

Sika® RainTite Waterproofing Compound

- Highly flexible UV resistant acrylic emulsion

Sika® RainTite Membrane

- Non-woven polyester membrane

The system forms a fully bonded, durable, flexible waterproofing membrane

CHARACTERISTICS / ADVANTAGES

- External weather & UV resistant
- Easy to use and apply
- No priming
- Excellent adhesion to most surfaces
- High flexibility
- Thixotropic
- Non toxic
- Will not promote fungal growth

USES

- Concrete sloped roofs (with membrane)
- Finishing
- Sealing joints, laps and roofing screws on various kind of roofs (roof tile, asbestos, zinc)
- Parapet walls
- External walls

PRODUCT INFORMATION

Packaging	1 kg, 4 kg, 20 kg pail waterproofing compound
Colour	Transparent, White, Ivory, Grey, Stone Grey, Meadow Green, Coffee Cream and Coro Red
Shelf life	12 months from date of production
Storage conditions	Stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C and protect from direct sunlight.

TECHNICAL INFORMATION

Tensile strength	~13 N/mm ²
Tensile strain at break	~20 %
Tear strength	~45 N/mm ²
Behaviour after artificial weathering	No serious effect after 3 000 hours

APPLICATION INFORMATION

Ambient air temperature	< 35 °C
Substrate temperature	< 35 °C
Drying time	2-3 hours depending upon ambient conditions

SYSTEMS

System structure	Without membrane	
	Primer (if substrate is porous) :	~0.3 kg/m ² (diluted with 10 % water)
	1 st Coat :	~0.3 kg/m ²
	2 nd Coat :	~0.3 kg/m ²
	With membrane	
	Primer (if substrate is porous) :	~0.3 kg/m ² (diluted with 10 % water)
	1 st Coat :	0.8 - 1.0 kg/m ²
	Sika® RainTite membrane	
	2 nd Coat :	0.8 - 1.0 kg/m ²
	Top Coat :	~0.4 kg/m ²
<hr/>		
Dry film thickness	~0.3 mm to ~0.45 mm (2 - 3 coats without membrane) ~1.0 mm to ~0.35 mm (3 - 4 coats with membrane)	

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Ambient and surface temperatures must be below 35 °C during application
- Do not attempt application if rain is imminent
- It is not recommended to apply screed mortar on top of Sika® RainTite
- Avoid ponding water on top of Sika® RainTite
- Minimum slope for Roof application (with membrane) should be 3 %

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Surface must be clean, sound and properly cured. Remove all loose materials mechanically, preferably with a wire brush. Iron and steel surfaces should be free of rust.

APPLICATION

Without Membrane :

- For porous substrate, apply first coat Sika® RainTite diluted with 10 % water as primer layer. Allow enough drying time (>3 hours, depending upon ambient conditions)
- Apply Sika® RainTite in two coats (~0.3 kg/m²/coat), by brush or roller

With Membrane :

- For porous substrate, apply first coat Sika® RainTite diluted with 10 % water as primer layer. Allow enough drying time (>3 hours, depending upon ambient conditions)
- Apply a first coat (0.8 - 1 kg/m²) of Sika® RainTite by brush or roller
- Embed the Sika® RainTite membrane into the first coat while it is still wet. Ensure that the membrane is thoroughly embedded and smooth out all air pockets and creases. Overlaps of adjacent membrane must be a minimum of 50 mm
- Immediately apply a second coat (0.8 - 1 kg/m²) of Sika® RainTite while the first coat is still wet, to fully saturate the membrane from both sides
- When dry, apply a final top coat (~0.4 kg/m²) to complete the application. Protect from rain until dry

CLEANING OF EQUIPMENT

Remove uncured surface Sika® RainTite with water.
Cured material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Kenya Limited

Josh Industrial Estate
P.O Box 38645 · 00623 Nairobi · Kenya
Mobile: +254 711 140234 / +254 786
140234
Web: ken.sika.com

Product Data Sheet

Sika® RainTite
May 2025, Version 03.01
020915103000000001

SikaRainTite-en-KE-(05-2025)-3-1.pdf