

## 8/20/2024 7:02:34 PM



Method: Light Elements | PP4 8/20/2024 6:53:17 PM

Name: tembaga batu

Grade ID: C17200 (47% 3/2/1)

Grade Alias: C17200

Duration of measurement: 12.2 s (2.1/10.1)

| Symbol | Zn / % | Sn / % | Pb / % | Ni / % | Al / % | Si / % | P/%    | Co / % |
|--------|--------|--------|--------|--------|--------|--------|--------|--------|
| Conc.  | <.028  | 0.34   | 0.31   | 0.15   | <0.11  | 0.28   | 2.38   | «<.005 |
| U      |        | ± 0.06 | ± 0.07 | ± 0.02 |        | ± 0.09 | ± 0.08 |        |

| Symbol | Cr / % | Se / % | Cu / % |  |  |  |
|--------|--------|--------|--------|--|--|--|
| Conc.  | <.007  | .015   | 96.5   |  |  |  |
| U      |        | ± .009 | ± 0.3  |  |  |  |

Grade: C17200

Alias: C17200

| Symbol  | Al / % | Si / % | Cr / % | Co / % | Zn / % | Sn / % |  |
|---------|--------|--------|--------|--------|--------|--------|--|
| Ext.Min |        |        |        | 0.20   |        |        |  |
| Ext.Max | 0.20   | 0.20   | .050   | 1.00   | 0.20   | 0.20   |  |