



Name: kuningan x Rf ex M2 Grade ID: ECu (12% 7/1/0)

Grade Alias: ECu

Duration of measurement: 12.2 s (2.1/10.1)

| Symbol | Zn / % | Sn / % | Pb / % | Al / % | Fe / % | Si / % | P/%    | Mn / % |
|--------|--------|--------|--------|--------|--------|--------|--------|--------|
| Conc.  | 40.3   | <.083  | 0.11   | <0.13  | <.003  | <0.15  | 0.49   | <.003  |
| U      | ± 0.2  |        | ± 0.08 |        |        |        | ± 0.06 |        |

| Symbol | Co / % | Cr / % | Se / % | Cu / % |  |  |
|--------|--------|--------|--------|--------|--|--|
| Conc.  | <.004  | <.004  | .061   | 59.0   |  |  |
| U      |        |        | ± .016 | ± 0.3  |  |  |

Grade: ECu

Alias: ECu

| Symbol  | Al / % | Si / % | Cr / % | Mn / % | Fe / % | Co / % | Sn / % | Pb / % |
|---------|--------|--------|--------|--------|--------|--------|--------|--------|
| Ext.Min |        |        |        |        |        |        |        |        |
| Ext.Max | 0.10   | 0.10   | .050   | 0.10   | 0.20   | .050   | 0.20   | .010   |