

## 8/23/2024 8:16:57 AM



Method: Light Elements | PP4 8/23/2024 8:04:30 AM

Name: tembaga batu 3

Grade ID: C17200 (44% 4/1/1)

Grade Alias: C17200

Duration of measurement: 12.2 s (2.1/10.1)

| Symbol | Zn / % | Sn / % | Pb / % | Ni / % | Al / % | Fe / % | Si / % | P/%    |
|--------|--------|--------|--------|--------|--------|--------|--------|--------|
| Conc.  | .034   | <.035  | 8.00   | 0.75   | <0.10  | 0.25   | 0.21   | 5.07   |
| U      | ± .027 |        | ± 0.19 | ± 0.03 |        | ± 0.04 | ± 0.10 | ± 0.10 |

| Symbol | Co / % | Cr / % | As / % | Ti / % | Ga / % | Cu / % |  |
|--------|--------|--------|--------|--------|--------|--------|--|
| Conc.  | «<.006 | 0.10   | 0.26   | 0.19   | 0.14   | 85.0   |  |
| U      |        | ± 0.03 | ± 0.07 | ± 0.03 | ± 0.04 | ± 0.3  |  |

Grade: C17200

Alias: C17200

| Symbol  | Al / % | Si / % | Cr / % | Co / % | Zn / % | Sn / % |  |
|---------|--------|--------|--------|--------|--------|--------|--|
| Ext.Min |        |        |        | 0.20   |        |        |  |
| Ext.Max | 0.20   | 0.20   | .050   | 1.00   | 0.20   | 0.20   |  |