

Maximum Feasible Recycled Content Decrease LIB Cap · Benchmark Chemistry

Nickel

Baseline CA origin / US network	2.6	9.4	32.2	45.2	60.6
Baseline US origin / US network	5.0	7.9	22.7	38.3	55.2
Baseline NA origin / NA network	5.0	8.1	23.9	41.3	61.0
Rollback CA origin / US network	5.1	15.0	42.6	41.4	52.9
Rollback US origin / US network	6.6	9.2	23.3	35.1	51.5
Rollback NA origin / NA network	7.0	9.8	24.9	38.3	57.2

Manganese

2.5	7.2	26.3	44.4	60.6
1.4	4.5	17.6	35.8	52.9
1.4	4.7	18.7	38.8	58.5
5.0	11.3	33.4	39.5	52.7
1.8	5.2	17.9	32.8	49.5
1.9	5.5	19.4	35.9	54.9

Cobalt

3.4	11.2	38.8	52.9	66.4
5.4	9.0	27.2	44.6	60.4
5.4	9.3	28.7	48.1	66.7
6.7	18.1	51.1	48.3	57.7
7.1	10.6	27.8	40.7	56.2
7.6	11.2	29.8	44.5	62.4

Lithium


Baseline CA origin / US network	2.1	7.3	24.9	37.6	50.3
Baseline US origin / US network	5.6	7.9	19.7	33.6	47.3
Baseline NA origin / NA network	5.7	8.0	20.5	35.6	51.2
Rollback CA origin / US network	3.8	11.3	32.9	35.3	45.1
Rollback US origin / US network	7.2	9.2	21.0	32.0	45.2
Rollback NA origin / NA network	7.7	9.8	22.3	34.5	49.4
	2030	2035	2040	2045	2050

Graphite

2.1	7.9	27.0	41.4	55.8
1.5	5.7	18.4	34.0	49.4
1.4	5.7	19.2	36.1	53.5
3.8	12.0	35.5	39.0	50.2
1.8	6.6	20.0	32.6	47.4
1.8	6.8	21.1	35.0	51.8
2030	2035	2040	2045	2050

Copper

2.3	8.3	28.0	43.7	58.8
7.6	10.0	23.4	40.1	56.3
7.7	10.2	24.3	42.3	60.5
4.1	12.5	36.8	41.5	53.4
9.7	11.8	25.3	38.8	54.3
10.5	12.5	26.8	41.6	59.0
2030	2035	2040	2045	2050



Maximum feasible recycled content (%)