

Production Performance & Quality Dashboard
(January – June 2026)

PRODUCTION TARGET

221.800 Pairs

ACTUAL PRODUCTION

203.321 Pairs

TARGET ACHIEVEMENT

91,7%

DEFECT UNITS

4.934 Pairs

DEFECT RATE

2.43%

Top Performing Line




Line C - Assembly

Highest Defect Type

Unbonding/Peeling

Primary Root Cause

Inadequate primer application /
Low pressing temperature



Date

All Periods BULAN ▼

2026

JAN FEB MAR APR MEI JUN JUL AGU

Production Line

Line A - Outsole Line B - Midsole





Line C - Assembly Line D - Molding

Primary Defect Type

Air Bubble Deformation

Flash/Over-overflow Scratches/Marks

Unbonding/Peeling Under-cure



KEY INSIGHT

- Overall production achieved **91.7% of target**.
- **Line C – Assembly** recorded the highest production achievement (92.1%).
- **Unbonding/Peeling** was the most frequent defect (**1,642 pairs, 33.3%**).
- The top **4 defect types** contributed **82.5%** of total defects, indicating the main