
Appendices

Appendix A – Common Material Properties

Average Properties of Some Typical Materials Note that except for density, stiffness and coefficient of thermal expansion, all values have a considerable range

Material	Weight (kN/m³)	Stiffness E (MPa)		Strength Pa) Ultimate	Compressive Strength (MPa)	Resilience (MJ/m³)	Toughness (MJ/m³) tens./comp.	Ductility Max. Elong. (%) Plastic/Elastic	α 10 ⁻⁶ /°C	Cost \$/kg	Comment
Low Alloy Steel	77	200,000	420	560	420	0.44	135	25/0.21	12	0.60	Used in buildings, bridges, cars, etc.
High Tensile Steel	77	200,000	1650	1860	1650	6.8	55	4/0.83	12	1.50	Wire ropes, cables
High Alloy Steel	77	200,000	700	800	700	1.22	200	25/0.35	12	2.00	Pressure Vessels and tanks
Piano Wire	77	200,000	-	3000	-	22	22	0.2/1.50	12	1.50	Brittle material, not used in structures
Cast Iron	70	150,000	-	110	770	0.04	0.06/6	1/0.7	11	0.50	Traditional cast iron, moulded
Wrought Iron	75	185,000	200	350	200	0.11	90	30/0.11	12	1.00	99% pure iron, hammered, fibrous
Aluminum	27	69,000	40	80	60	0.012	19	40/0.06	24	1.80	Light, ductile, non-corrosive, soft metal
Aluminum Alloy	27	73,000	470	580	500	1.51	50	11/0.64	24	2.50	Used for canoes, aircraft, etc.
Copper	88	124,000	70	230	200	0.02	85	55/0.06	20	7.47	Very ductile metal – rounded curve
Bronze	79	105,000	200	390	350	0.2	40	12/0.19	17	2.80	Tin + copper alloy – stronger
Gold	189	82,000	40	220	180	0.01	80	50/0.05	14	40k	Heavy, expensive metal
Granite	26	52,000	-	11	140	0.001	0.01/0.26	0/0.02	8	0.15	Strongest and most durable building stone
Limestone	25	58,000	-	8	62	0.0006	0.01/0.09	0/0.01	6	0.03	Soft, useful building store
Slate	28	95,000	-	60	100	0.019	0.02/0.10	0/0.06		0.08	Stratified rock with high tensile strength
Brick	19	20,000	-	3	20	0.0002	0.01/0.03	0/0.01	9	0.10	Fired clay
Concrete	24	30,000	-	3	35	0.002	0.01/0.10	0/0.01	9	0.12	Mixture of cement, sand, stone, water
Glass	27	69,000	-	100	200	0.072	0.07/0.8	0/0.15	20	1.50	Solidified liquid sand
Oak	7.5	14,000	75	90	60	0.23	0.3/2.5	0.5/0.47	3	3.2	Strong, tough, heavy hardwood
Spruce	4.4	11,000	55	70	50	0.19	0.2/2.2	0.5/0.50	7	2.0	Light, strong, durable softwood
Tendon	10	900	70	80	-	2.7	4	1/7.8		-	Used as tension ties in mammals
Bone	20	17,000	150	180	180	0.66	1	0.5/0.9		-	Used as struts and beams in mammals
Rubber	9.2	7	-	20	20	15	20	4/300	500	2.0	Strange, useful material – low stiffness
Spider's Silk	10	4,000	-	1400	-	160	170	10/35		-	Most resilient material
Carbon Fibre	15	160,000	-	1800	-	10	10	0.1/1.1		50.0	Carbon fibre composites used in aircraft
Nylon Fibre	11	5,500	-	900	-	74	75	2/16	80	8.00	Excellent if stiffness not required
Kevlar Fibre	14	130,000	-	3600	-	50	60	1/2.7		50.00	Super material in many ways

Appendix B – HSS Tables



Appendix C – Steel Wide Flange Beams and Sawn Timber Section Tables

Wide Flange Rolled Steel Beams Dimensions and Section Properties



Designation		Dime	nsion	s	Dead Load	Area	Stron	g Axis x-	x	Wea	k Axis y-y	,	Torsion Constant	Shea Depti
Designation	d	$b_{\rm f}$	t	b _w	Load		I _x	Sx	rx	I _y	Sy	ry	J	I_x/Q
mm × kg/m	mm	mm	mm	mm	kN/m	mm ²	10 ⁶ mm ⁴	10 ³ mm ³	mm	10 ⁶ mm ⁴	10 ³ mm ³	mm	10 ³ mm ⁴	mm
W920 × 446	033	423	43	24.0	4.38	57000	8470	18200	385	540	2550	97.3	26800	822
× 365		419	34	20.3	3.57	46400	6710	14600	380	421	2010	95.3	14400	813
× 313	932	309	34	21.1	3.06	39 800	5480	11800	371	170	1100	65.4	11600	806
× 238		305	26	16.5	2.33	30400		8880	365	123	806	63.6	5140	796
W840 × 329	862	401	32	19.7	3.23	42 000	5350	12400	357	349	1740	91.2	11500	764
× 210		293	24	15.4	2.06	26800	3110	7340	341	103	700	62.0	4050	738
× 176	835	292	19	14.0	1.72	22 400	2460	5900	331	78.2	536	59.1	2220	722
W760 × 257	773	381	27	16.6	2.52	32 800		8840	323	250	1310	87.3	6380	689
× 173	762	267	17	14.4	1.70	22 100		5400	305	68.7	515	55.8	2690	663
× 147	753	265	17	13.2	1.44	18700	1660	4410	298	52.9	399	53.2	1560	651
W690 × 217	695	355 254	25 21	15.4	2.13	27700 19400	2340 1510	6740 4380	291 279	185 57.8	1040 455	81.7 54.6	4560 2200	618
× 152	688			13.1	1.49			3500	273	44.1	349	52.5	1180	594
× 125	6/8	253	16	11.7	1.23	16000	1190	(0.000000)	0.000	2557.5557			200000	
W610 × 195		327	24	15.4	1.91	24900		5400	260	142	871	75.5	3970	554
× 155	611	324	19	12.7	1.51	19700	1290	4220	256	108	666	74.0	1950	545
× 125	612	229	20	11.9	1.22	15900	985	3220	249	39.3	343	49.7	1540	537
× 101	603	228	15	10.5	0.99	13 000	764	2530	242	29.5	259	47.6	781	527
W530 × 182		315	24	15.2	1.78	23 100		4480	232	127	808	74.1	3740	492
× 150	543	312	20	12.7	1.47	19200		3710	229	103	659	73.2	2160	487
× 109 × 82		211	19	11.6 9.5	1.06	13900	667 479	2480 1810	219 214	29.5 20.3	280 194	46.1 44.0	1260 530	463
				-			538,1180	5,5,5,5,5					100000	421
W460 × 144 × 97		283 193	22 19	13.6 11.4	1.41 0.95	18400	726 445	3080 1910	199 190	83.6 22.8	591 237	67.4 43.1	2440 1130	421
× 82	460	193	16	9.9	0.93	12300		1610	189	18.6	195	42.3	691	404
× 61		189	11	8.1	0.60	7760	259	1150	183	12.2	129	39.7	289	395
W410 × 114	420	261	19	11.6	1.12	14600	462	2200	178	57.2	439	62.6	1490	376
× 74		180	16	9.7	0.73	9550	275	1330	170	15.6	173	40.4	637	364
× 60	407	178	13	7.7	0.58	7580	216	1060	169	12.0	135	39.8	328	363
× 39	399	140	9	6.4	0.38	4990	127	634	160	4.0	57.7	28.5	111	348
W360 × 314	399	401	40	24.9	3.07	39900	1100	5530	166	426	2120	103	18500	345
× 122	363	257	22	13.0	1.19	15500	365	2010	153	61.5	478	63.0	2100	322
× 79	354	205	17	9.4	0.78	10100		1280	150	24.2	236	48.9	814	317
× 64		203	14	7.7	0.63	8140	178	1030	148	18.8	186	48.1	438	312
× 45		171	10	6.9	0.44	5730	122	691	146	8.18	95.7	37.8	160	313
× 33	349	127	8	5.8	0.32	4170	82.7	474	141	2.91	45.8	26.4	85.9	305
W310 × 253		319	40	24.4	2.48	32200		3830	146	215	1350	81.7	14800	304
× 118		307	19	11.9	1.15	15 000	275	1750	135	90.2	588	77.5	1600	282
	306	254	15	8.8	0.77	10100	177	1160	132	39.9	314	62.9	657	277
X 60		203	13	7.5	0.59	7590	129	849	130	18.3	180	49.1 38.4	397	274
× 39 × 21		165 101	10	5.8	0.38	4940 2690	85.1 37.0	549 244	131	7.27 0.983	88.1 19.5	19.1	126 29.4	258
				0.000	10000000			units	114	2222.0	495	66.3	2130	236
W250 × 115 × 49		259	22	13.5	1.12	14600	189	1410	106	64.1	150	49.2	2130	236
× 49		146	9	7.4 6.1	0.48	6250 4170	70.6 48.9	572 379	108	15.1 4.73	64.7	33.7	98.5	231
W200 × 59	210	205	14	9.1	0.58	7560	61.1	582	89.9	20.4	199	51.9	465	187
× 36		165	10	6.2	0.38	4580	34.4	342	86.7	7.64	92.6	40.8	146	181
× 27		133	8	5.8	0.35	3390	25.8	249	87.2	3.30	49.6	31.2	71.3	185
W150 × 30	157	153	9	6.6	0.29	3790	17.2	219	67.4	5.56	72.6	38.3	101	141
	150	100	6	4.3	0.29	1730	6.87	91.5	63.0	0.92	18.4	23.0	17.0	133
× 14	130	100	0	4.3	0.13	1730	0.07	91.3	05.0	0.92	10.4	23.0	17.0	13.



Size and	Nominal	Dead	Area	Stron	ng Axis x-	x	Wea	k Axis y-y	/	Torsion Constan
Designation $b \times d$	Dimensions	Load		I _x	Sx	rx	I _y	S_{y}	ry	J
mm	in.	kN/m	mm ²	10 ⁶ mm ⁴	10 ³ mm ³	mm	10 ⁶ mm ⁴	10 ³ mm ³	mm	10 ⁶ mm
292 × 495	12 × 20	0.907	145000	2950	11900	143	1030	7030	84.3	2570
× 445	× 18	0.816	130000	2140	9640	129	923	6320	84.3	2190
× 394	× 16	0.722	115000	1490	7550	114	817	5600	84.3	1760
× 343	× 14	0.629	100000	982	5730	99.0	712	4870	84.3	1370
× 292	× 12	0.535	85300	606	4150	84.3	606	4150	84.3	1030
241 × 495	10 × 20	0.749	119000	2440	9840	143	577	4790	69.9	1600
× 445	× 18	0.673	107000	1770	7950	129	519	4310	69.6	1360
× 394	× 16	0.596	95 000	1230	6240	114	460	3810	69.6	1130
× 343	× 14	0.519	82700	810	4730	99.0	400	3320	69.6	900
× 292	× 12	0.442	70400	500	3420	84.3	341	2830	69.6	671
× 241	× 10	0.365	58 100	281	2330	69.6	281	2330	69.6	476
191 × 495	8 × 20	0.594	94600	1930	7800	143	287	3010	55.1	868
× 445	× 18	0.534	85 000	1400	6300	129	258	2710	55.1	751
× 394	× 16	0.472	75300	974	4940	114	229	2400	55.1	636
× 343	× 14	0.411	65 500	642	3750	99.0	199	2090	55.1	515
× 292	× 12	0.350	55 800	396	2710	84.3	170	1780	55.1	403
× 241 × 191	× 10 × 8	0.289	46000 36500	223 111	1850	69.6	140	1470	55.1	285
	^ 0	0.229	30300	111	1160	55.1	111	1160	55.1	188
140 × 445	6 × 18	0.391	62300	1030	4620	129	102	1450	40.4	325
× 394	× 16	0.346	55 200	714	3620	114	90.1	1290	40.4	279
× 343	× 14	0.301	48 000	471	2750	99.0	78.4	1120	40.4	232
× 292	× 12	0.257	40 900	290	1990	84.3	66.8	954	40.4	186
× 241 × 191	× 10	0.212	33700	163	1360	69.6	55.1	787	40.4	139
× 140	× 8 × 6	0.168 0.123	26700 19600	81.3 32.0	851 457	55.1 40.4	43.7 32.0	624 457	40.4 40.4	94.9 54.2
89 × 387	416									
× 337	4 × 16 × 14	0.216 0.188	34 400 30 000	430 284	2220	112	22.7	511	25.7	77.5
× 286	× 12	0.160	25 500	174	1680 1210	97.3 82.6	19.8	445	25.7	65.9
× 235	× 10	0.131	20900	96.3	819	67.8	16.8 13.8	378 310	25.7 25.7	53.8 41.9
× 184	× 8	0.103	16400	46.2	502	53.1	10.8	243	25.7	30.1
× 140	× 6	0.078	12500	20.4	291	40.4	8.22	185	25.7	19.8
× 114	× 5	0.064	10200	11.0	193	32.9	6.70	151	25.7	13.8
× 89	× 4	0.050	7920	5.23	118	25.7	5.23	117	25.7	8.85
64 × 337	3 × 14	0.135	21600	204	1210	97.3	7.36	230	18.5	25.8
× 286	× 12	0.115	18300	125	872	82.6	6.25	195	18.5	21.4
× 235	× 10	0.094	15000	69.2	589	67.8	5.13	160	18.5	17.0
× 184	× 8	0.074	11800	33.2	361	53.1	4.02	126	18.5	12.5
× 140	× 6	0.056	8960	14.6	209	40.4	3.06	95.6	18.5	8.68
× 114	× 5	0.046	7300	7.90	139	32.9	2.49	77.8	18.5	6.41
× 89	× 4	0.036	5700	3.76	84.5	25.7	1.94	60.8	18.5	4.29
38 × 337	2 × 14	0.071	12800	121	719	97.3	1.54	81.1	11.0	5.72
× 286	× 12	0.060	10900	74.1	518	82.6	1.31	68.8	11.0	4.79
× 235	× 10	0.049	8930	41.1	350	67.8	1.07	56.6	11.0	3.87
× 184	× 8	0.038	6990	19.7	214	53.1	0.84	44.3	11.0	2.91
× 140	× 6	0.029	5320	8.69	124	40.4	0.64	33.7	11.0	2.11
× 114	× 5	0.024	4330	4.69	82.3	32.9	0.52	27.4	11.0	1.65
× 89	× 4	0.019	3380	2.23	50.2	25.7	0.41	21.4	11.0	1.19
× 64	× 3	0.013	2430	0.83	25.9	18.5	0.29	15.4	11.0	0.73
× 38	× 2	0.008	1440	0.17	9.15	11.0	0.17	9.15	11.0	0.29

Appendix D – Wood Properties

Section 9

Wood Structures 5th Percentile estimates of strongfth. 259 under one mouth loading. For safe working strosses reduce these breaking stresses by factor of safety of 1.5.

Species or	Grade	Bending	Shear	Cor	mpression	Tension	Modulus of		
Species		f_{bu}	Longitudinal		Perpendicular	_			
Combination			f_{VU}	Grain f _{pu}	to Grain fau	Grain ftu	E ₅₀	E ₀₅	
Douglas Fir- Larch	Select Structural	17.5	1.1	16.5	3.6	13.5	11,000	8,000	
	No. 1 and No. 2	10.0	1.1	9.0	3.6	9.0	9,500	6,000	
Hem-Fir	Select Structural	16.0	0.8	14.5	1.9	13.5	11,000	7,500	
	No. 1 and No. 2	11.5	0.8	10.5	1.9	9.0	10,500	7,000	
Lodgepole Pine, or Ponderosa Pine	Select Structural	16.0	1.0	14.5	1.9	13.5	10,000	7,000	
	No. 1 and No 2	11.5	1.0	10.5	1.9	9.0	9,000	6,000	
Jack Pine	Select Structural	16.0	1.0	14.5	2.6	13.5	10,500	7,000	
	No. 1 and No. 2	11.5	1.0	10.5	2.6	9.0	9,500	6,000	
Red Pine	Select Structural	11.5	0.8	10.0	1.9	10.0	7,000	5,000	
	No. 1 and No. 2	8.0	0.8	7.0	1.9	7.0	6,000	4,000	
White Pine*	Select Structural	6.0	0.8	-	1.9	-	5,500	4,000	
	No. 1 and No. 2	4.5	0.8	-	1.9	-	4,500	3,500	


Dimension lumber with thickness of 89 mm or greater shall have specified strengths in accordance with Table 13–11.2 (b).

9 – 11.2 (b)	Specified strength and modulus of elasticity for beams & stringers, post & timbers,
	minimum dimension 140 mm. MPa

Species or	Grade	Bending	Shear	Cor	mpression	Tension	Modulus of Elasticity		
Species		f_{bu}	Longitudinal	l Parallel to	Perpendicular	Parallel to			
Combination			f_{VU}	Grain fpu	to Grain f _{qu}	Grain f _{tu}	E ₅₀	E ₀₅	
Douglas Fir- Larch	Select Structural	24.0	1.1	16.5	3.6	13.0	11,000	7,500	
	No. 1	20.0	1.1	9.0	3.6	9.0	9.500	6.500	
Hem-Fir	Select Structural	20.0	0.8	14.5	1.9	13.0	11,000	7,500	
	No. 1	18.0	0.8	10.5	1.9	9.0	10.500	7,000	
Lodgepole Pine, or Ponderosa Pine	Select Structural	18.5	1.0	14.5	1.9	13.0	10,000	7,000	
	No. 1	13.0	1.0	10.5	1.9	9.0	9.000	6,000	
Jack Pine	Select Structural	18.5	1.0	14.5	2.6	13.0	10,500	7,000	
	No. 1	13.0	1.0	10.5	2.6	9.0	9.500	6.000	
Red Pine	Select Structural	13.0	0.8	10.0	1.9	10.0	7,000	5,000	
	No. 1	9.0	0.8	7.0	1.9	7.0	6.000	4.000	

Table 4.3 Average clear-wood strength values* for commercial species in air-dry condition

					NO. 10100			No.		9600 TO 80	
	Relativ	Relative density†		Shrinkage, green to air-dry based on dimensions ty† when green (%)			Modulus of elasticity	Compression parallel to grain, crushing strength	Shear	Compression perpendicular to grain, fiber stress at proportional	Tension perpendicular to grain
Species	Nominal	Oven-dry	Radial	Tangential	Volumetric	rupture (MPa)	(MPa)	max. (MPa)	(MPa)	limit (MPa)	(MPa)
SOFTWOODS											
Cedar											
Eastern white	0.30	0.31	-	_	3.8	42.3	4 380	24.8	6.93	2.68	2.63
Western red	0.34	0.34	-	-	4.8	53.8	8 270	33.9	5.58	3.43	1.46
Yellow	0.43	0.46	-	-	5.0	79.7	11 000	45.9	9.21	4.74	3.49
Douglas-fir	0.49	0.51	-	-	7.0	88.6	13 500	50.1	9.53	6.01	3.06
Fir											
Amabilis (Pacific											
silver)	0.39	0.41			7.5	68.9	11 400	40.8	7.54	3.61	3.06
Balsam	0.35	0.37	1.2	4.3	5.7	58.3	9 650	34.3	6.25	3.14	2.08
Hemlock											
Eastern	0.43	0.45	2.4	4.7	6.2	67.1	9 720	41.0	8.75	4.28	2.06
Western	0.43	0.47		-	8.1	81.1	12 300	46.7	6.48	4.53	2.93
Tamarack	0.51	0.54	_	-	7.1	76.0	9 380	44.8	9.00	6.15	3.47
Larch, western	0.58	0.64	-	_	8.0	107.0	14 300	60.9	9.25	7.31	3.62
Pine											
Eastern white	0.37	0.38	_		4.5	65.0	9 380	36.2	6.10	3.39	2.63
Iack	0.44	0.45	2.1	3.8	5.7	77.9	10 200	40.5	8.23	5.70	3.65
Lodgepole	0.41	0.46	-	-	6.6	76.0	10 900	43.2	8.54	3.65	3.78
Ponderosa	0.46	0.49	-	-	6.1	73.3	9510	42.3	7.03	5.22	3.47
Red	0.40	0.42	1.9	4.1	6.5	69.7	9 4 5 0	37.9	7.50	4.96	3.54
Western white	0.37	0.40	-		6.0	64.1	10 100	36.1	6.34	3.23	2:64
Spruce											
Black	0.43	0.44	1.7	4.0	6.5	78.3	10 400	41.5	8.65	4.25	3.43
Engelmann	0.40	0.42	_	-	6.8	69.5	10 700	42.4	7.55	3.70	2.72
Red	0.40	0.42	-	-	6.2	71.5	11 000	38.5	9.20	3.77	3.70
Sitka	0.39	0.39	_	_	6.0	69.8	11 200	37.8	6.78	4.10	2.48
White	0.37	0.39	1.4	4.0	6.8	62.7	9 930	36.9	6.79	3.45	3.28
HARDWOODS											
Aspen,											
trembling	0.41	-	2.7	5.7	8.3	67.6	11 200	36.3	6.76	3.52	4.19
Birch, yellow	0.61	_	-	-	9.9	106.0	14 100	52.1	14.67	7.24	7.52
Maple, sugar	0.66	-	2.9	6.4	9.3	115.0	14 100	56.4	16.71	9.72	9.2
Oak, red	0.61	_	122		6.9	98.7	11 900	49.8	14.38	8.89	6.53




(b) Frequency distribution of bending strength of green Douglas fir. 2110 small clear specimens cut from a single tree. Short-term Loading.

Appendix E – Common Unit Conversions

	Working with SI units			
Lengths, Strains and Curvatures	Pressures and Stresses	Forces and Moments		
1 m = 1,000 mm	$1 \text{ Pa} = 1 \text{ N/m}^2$	1 kN = 1,000 N		
$1 \text{ m}^2 = 10^6 \text{ mm}^2$	$1 \text{ kPa} = 1 \text{ kN/m}^2$	$1 \text{ MN} = 10^6 \text{ N}$		
$1 \text{ m}^3 = 10^9 \text{ mm}^3$	$1 \text{ MPa} = 1 \text{ MN/m}^2$			
	$1 \text{ MPa} = 1 \text{ N/mm}^2$	1 Nm = 1,000 Nmm		
$1 \text{ mm/m} = 10^3 \text{ mm/mm}$		$1 \text{ kNm} = 10^6 \text{ Nmm}$		
$1 \text{ rad/m} = 10^6 \text{ mrad/mm}$				
Working with o	ther unit systems and other miscella	neous quantities		
1 foot = 12 inches	1 inch = 25.4 mm			
1 cubit = 18 inches	1 foot = 304.8 mm	$9.81 \text{ m/s}^2 = 32.2 \text{ feet/s}^2$		
		1 kNm = 0.738 kip ft		
1 yard = 3 feet	1 mile = 1609 m	1 kNm = 8.85 kip in		
1 chain = 22 yards	1 ha = 2.47 acres	1 KINIII — 0.03 KIP III		
1 furlong = 10 chains				
1 mile = 8 furlongs	1 kg = 2.20 lbs	1 hp = 746 Watt		
1 mile = 1,760 yards	1 stone = 14.0 lbs			
, ,		1 km/h = 0.278 m/s		
1 como — 10 coucamo abeimo	1 lbs/ ft 3 = 16.02 kg/ m^3	1 km/h = 0.621 miles/h		
1 acre = 10 square chains	_	1 knot = 1.852 km/h		
1 square mile = 640 acres	$100 \text{ lbs/ft}^3 = 15.72 \text{ kN/m}^3$			
1 ha = 10,000 square m		1 MPa = 145.0 psi		
	1 N = 0.225 lbs (force)	$1 \text{ kN/m}^2 = 20.9 \text{ lbs/ft}^2$		
	1 kip = 4.45 kN			

Appendix F – Areas and Centroids of Common Shapes



Appendix G – Common Canadian Reinforcing Bar Information

Designation	Linear Density (kg/m)	Nominal Diameter (mm)	Cross-Sectional Area (mm²)
10M	0.785	11.3	100
15M	1.570	16.0	200
20M	2.355	19.6	300
25M	3.925	25.2	500
30M	5.495	29.9	700
35M	7.850	35.7	1000
45M	11.775	43.7	1500
55M	19.625	56.4	2500