

# “The color of a flower field changes with a butterfly’s flight vector” is a metaphor for homochirality colorimetry via chiral nanostructure arrays

Zaid Haddadin<sup>1</sup>, Anna My Nguyen<sup>2</sup>, Paula Kirya<sup>2</sup>, Lisa V. Poulikakos<sup>2,3</sup>

1. Electrical & Computer Engineering, University of California San Diego, La Jolla, CA 92093

2. Mechanical & Aerospace Engineering, University of California San Diego, La Jolla, CA 92093

3. Program of Materials Science & Engineering, University of California San Diego, La Jolla, CA 92093


## Introduction

Fibrous or filamentous biological structures, like microbial mats, can rotate a light wave's travel vector [1,2]. However, this rotation is too minimal to measure without meter-scale tools [3]. **This work explores miniaturizing these tools to the nanometer level for *in-situ* applications.**

One possibility is rotating a light vector into a circular path, either clockwise or counter-clockwise [3]. Homochirality is when an orientation of circular light is favored over the other [3,4,5]. **Detecting homochiral light is an agnostic biosignature of life [5].**

We investigate how this biosignature could be detected using arrays of nanoscale particles. By using visible light, our optical arrays also act as colorimetric sensors of homochirality [3,6,7].


Figure 1: Schematic of sensing system.



## Materials and methods

We investigate how a cut to one corner of square- and rectangle-shaped nanostructures affects their sensitivities to differentiating between incident clockwise or counter-clockwise oriented circular light.

Figure 2: Summary of methods.



## Results

- **Differentiation of clockwise and counter-clockwise polarization states of chiral light was achieved.**
- **Squares:** Figure 3 shows cuts to the square structure affect the reflectance response but result in non-differentiable outputs. Table 1 displays the non-differentiable colorimetry results. Figure 4 examines the near-field response: cuts simplify the problem from four to two nodes, which dampens the reflectance response due to a decreased out-of-plane energy output.
- **Rectangles:** Simplifying the problem in rectangles from a four nodes to nodes extinguishes the longer-wavelength reflectance peaks, as shown in Figure 5's "Medium Cut" group. This also unequally dampens the shorter-wavelength peaks of the two polarization states. Both these observations contribute to the differentiable colorimetry results in Table 2.




Table 1: Colorimetry results from Figure I reflectances.

	Clockwise	Counter-clockwise
No Cut	#598C18	
Small Cut	#428716	
Medium Cut	#1C6117	





Table 2: Colorimetry results from Figure III reflectances.

	Clockwise	Counter-clockwise
No Cut	#484564	
Small Cut	#424059	#433F62
Medium Cut	#31352A	#343146


## Conclusions

Biological media with fibrous or filamentous structures can alter light polarization, an agnostic indicator of life [1,2]. **The purposeful design of nano-optical arrays makes it possible to create miniaturized optical sensors for polarized light, which may be useful for *in-situ* investigations.**

This investigation showed that nano-optical arrays can differentiate clockwise and counter-clockwise circularly polarized light, **enabling homochirality detection.** However, there remains the open question of why this was achieved.

Figure 6 suggests that under clockwise light, the dipole charge aligns with the outward flux to the nanoparticle sides; thus, reducing the amount of light reflected towards the imaging apparatus. Under counter-clockwise light, the dipole charge opposes the outward flux to the nanoparticle sides. If so, this could explain the disproportionate dampening in reflectance and the discriminatory colorimetry results.

Figure 6: Near-field of medium cut rectangle.



## Literature cited

1. Ghosh N, Wood MFG, Li S hong, Weisel RD, Wilson BC, Li RK, et al. Journal of Biophotonics. 2009;2(3):145–56
2. Sparks WB, Parenteau MN, Blankenship RE, et al. Astrobiology. 2021 Feb;21(2):219–34.
3. Kwon J, Park KH, Choi WJ, et al. Acc Chem Res. 2023 Jun 20;56(12):1359–72.
4. Avnir D. New Astronomy Reviews. 2021 Jun 1;92:101596
5. Neveu M, Hays LE, Voytek MA, et al. Astrobiology. 2018;18(11):1375–402.
6. Haddadin Z, Khan S, Poulikakos LV. ACS Photonics. 2024 Jan 17;11(1):187–195.
7. Fairchild MD. Color Appearance Models. John Wiley & Sons. 2005; 2nd Ed.

## Acknowledgments

Research funding received through the UC San Diego MRSEC Seed Grant and from the Arnold and Mabel Beckman Foundation. Travel funding from AbGradCon24.

Thank you to Julia Holland for brainstorming the presentation's title, and to the rest of my coworkers in the Poulikakos Lab for the research discussions and continued support ☺

## Further information

I'm at [zalhadda@ucsd.edu](mailto:zalhadda@ucsd.edu) for further questions & discussions. Scan the below QR code for a PDF copy of this poster.



UC San Diego  
JACOBS SCHOOL OF ENGINEERING

