TECHNICAL INFORMATİON TABLE

TERRAWOOL INSULATION BOARD					
Material properties	**SYMBOL**	**UNIT**	**DESCRIPITON**	**TOLARANCE**	**STANDART**
MATERİAL	—	—	STONE WOOL	—	TS EN 13162
TYPE OF MATERİAL	—	—	TERRAWOOL INSULATION BOARD	—	—
DENSİTY	ρ	KG/m³	40	+/-%7	—
WİDTH	b	mm	600	+/-%1,5	TS EN 822
LENGTH	l	mm	1200	+/-%2	TS EN 822
THİCKNESS	d	mm	50	T3*	TS EN 823
COVERİNG	—	—	UNCOATED	—	—
FİRE CLASS REACTİON	—	—	A1	—	TS EN 13501-1
SQUARE DEVİATİON	Sb	mm/m	max 5	—	TS EN 824
SURFACE SMOOTHNESS	Smax	mm	max 6	—	TS EN 825
DİMENSİONAL STABİLİTY	ΔƐd	%	max 1	—	TS EN 1604
THERMAL CONDUCTİVİTY VALUED DECLARED 10 °C	λD	W/mK	0,035	—	TS EN 12667/12939
THERMAL CONDUCTİVİTY RESİSTANCE	RD	m²K/w	1,43	—	TS EN 12667/12939
MOİSTURE DİFFUSİON RESİSTANCE**	μ	—	1	—	TS EN 12086:2002
DİP PORTİON,LONG-TERM WATER ABSORPTİON	Wlp	Kg/m²	≤ 3	—	TS EN 12087
DİP PORTİON,SHORT-TERM WATER ABSORPTİON	Wp	Kg/m²	≤ 1	—	TS EN 1609
MATERİAL PACKİNG	—	—	PE FİLM	—	—

INSTRUCTIONS ON LOADING, UNLOADING, TRANSPORT AND STORAGE

- In precipitation weather the product should be created in closed area.
- Even for small distance,while shiping,the product should be covered with waterproof coat.
- In case of packet,product should be stored.Damaged packet shall not be used.
- The top of packet should be stacked.
- Product's top shouldn't be pressed.Otherwise product will not be usefull.
- Before taking out the ropes,we must make sure that the ropes bottom will go down;will be used strong carton with 50/20cm dimenssion.
- In case of rain,inundation etc. the storage area shall be protected from getting wet.Closed territory is prefered.
- Storage foundation must be straight and solid.
- During installation process a crane shall be used.
- The plate will be carefully moved in aplication area by 2 people.

PLADIS - Complexe Futuris Logistic Lotissement Ennouala Lot N°2 Dépôt A3 Boulevard My Ismaïl- Casablanca
Tel: (212) 5 22 34 44 59 // (212) 5 22 34 44 62
Zi Gzenaya 341- Tanger , Tel: (+212) 5 31 43 65 10 Email: contact@pladis.ma Site Web : www.pladis.ma