TECHNICAL DATA SHEET
ÜRÜN TEKNİK BİLGİ FORMU

Document No / *Dok. No* :	KG-C-FR-064
Issue Date / *İlk Yür. Tarihi* :	27.08.2019
Revision No / *Rev. No* :	0
Revision Date / *Rev. Tarihi* :	27.08.2019
Page / *Sayfa* :	1/1

Product Name */Ürün Adı/*	**R115-5 STARFLEX BLANKET FSK** **R115-5 STARFLEX SILTE AFK**
Standard */Standart /*	EN 13162 Thermal insulation products for buildings-Factory made mineral wool (MW) products - Specification / Isı yalıtım mamulleri-binalarda kullanılan-fabrika yapımı mineral yün (MW) mamuller-Özellikler
Description */Tanımı/*	Glasswool - bonded with a thermosetting resin, flexible, for thermal and sound insulation / Cam yünü - termoset reçine ile bağlanmış, bükülebilen, ısı ve ses yalıtımı için
Surface Facing */Yüzey Kaplama/*	Aluminium Foil Faced - 90 micron / Alüminyum Folyo Kaplamalı - 90 mikron

Product Performance /Ürün Özellikleri/

Technical Characteristics /Teknik Özellikler/	**Test Method /Test Metot/**	**Units /Birim/**	**Value or Statement /Değer/**				
Thickness */Kalınlık/* - **d**	EN 823	mm	50				
Tolerances *(Tolerans)*			45,0-fazlasına izin var				
Length */Uzunluk /* - **l**	EN 822	mm	20000				
Tolerances *(Tolerans)*			min.19600-max.20400				
Width */Genişlik/* - **b**	EN 822	mm	1200				
Tolerances *(Tolerans)*			min. 1182-max.1205				
			10 ºC	50 ºC	100 ºC	150 ºC	200 ºC
Thermal Conductivity (10 ^{0} C) */Isıl İletkenlik/* - λ_D	EN 12667 EN 12939	W/(m.K)	0,042	0,045	0,089	0,110	0,133
Thermal Resistance */Isıl Direnç/* - R_D	EN 12667 EN 12939	(m^2.K)/W	1,150	1,100	0,550	0,450	0,350
Fire Resistance Class */Yangına Tepki Sınıfı/*	EN 13501-1	Euroclass	C-s1,d0				
Maximum Service Temperature / *Azami Kullanım Sıcaklığı/*	EN 14706	^{o}C	NPD				
Short Term Water Absorption */Kısa Süreli Su Absorpsiyonu/* - **WS**	EN 1609	kg/m^2	1 >				

Packing */Ambalajlama/*	Board / Blanket in Package / *Levha / Şilte Pakette*	1
	(m^2/package) */(m^2/paket)/*	24
	LDPE package / *AYPE ambalajı/*	
Storage */Depolama/*	Store in dry and well ventilated area prior to installation */Kuru ve iyi havalandırmalı yerde depolanmalı/*	
	Protect from water, physical damage and direct flame sources */Su, fiziksel hasar ve alev kaynaklarından korunmalı/*	

22.06.2023

ODE Yalıtım Sanayi ve Ticaret A.Ş.

Piyale Paşa Bulvarı, Ortadoğu İş Merkezi Kat:12, 34384 Okmeydanı - Şişli / İstanbul TR

Phone:+90 212 210 46 06 Fax: +90 212 210 49 07 E-mail: ode@ode.com.tr

PLADIS - Complexe Futuris Logistic Lotissement Ennouala Lot N°2 Dépôt A3 Boulevard My Ismaïl- Casablanca
Tel: (212) 5 22 34 44 59 // (212) 5 22 34 44 62
Zi Gzenaya 341- Tanger , Tel: (+212) 5 31 43 65 10 Email: contact@pladis.ma Site Web : www.pladis.ma