ATHENA



VISIT USGME.COM TO ORDER SAMPLES

FEATURES & BENEFITS

- Accessible acoustical ceiling system with multiple random pin perforation panels.
- Perfect design solution for new-build or renovation projects.
- Available in semi-concealed and fully concealed tiles.
- Ideal for mid to high sound absorption & sound attenuation, which provides balance to room acoustics.
- Excellent for general commercial construction projects.
- Maximum cost-efficiency and design simplicity.
- Available in washable & hygienic paint upon request.
- Specially formulated in 16mm for high acoustic sound absorption specifications of the NRC 0.70.

APPLICATIONS

- Schools
- Corridors
- Lobby areas
- Offices
- Retail Stores

Absorption Coefficient

Frequency, Hz	125	250	500	1000	2000	4000	NRC*
16mm	0.30	**0.35**	**0.65**	**0.90**	**1.0**	0.95	**0.70**
19mm HNRC	0.35	**0.45**	**0.80**	**0.70**	**0.65**	0.50	**0.65**

**Calculated to ASTM C 423-01*

USG ME
INNOVATIVE SOLUTIONS. EVERYTIME.

ATHENA

EN 13964 : 2014 + A1 : 2007







HIGH SOUND ABSORPTION | CEILING ATTENUATION CLASS | FIRECODE | AVAILABLE IN CONCEALED EDGE | HIGH RECYCLED CONTENT


TABLE OF PERFORMANCE

Edge Detail	Item	Size (mm)	NRC	CAC	Light Reflectance	Anti-Mold & Mildew/ Sag Resistance	Fire Rating	Recycled Content	VOC Emission	Cost
			NRC	CAC						$
SQ	ATX666 ATX226	600*600*16 610*610*16	0.70	35	86%			68%	Low	$$$
	ATX626 ATX246	600*1200*16 610*1220*16	0.70	35	86%			68%	Low	$$$
SLT	ATXR666 ATXR226	600*600*16 610*610*16	0.70	35	86%			68%	Low	$$$
FLB	ATXRF666 ATXRF226	600*600*16 610*610*16	0.70	35	86%			68%	Low	$$$
D-BESK	ATCRFDC669-HNRC	600*600*19	0.65	40	86%			82%	Low	$$$$
BESK	ATCC669-HNRC	600*600*19	0.65	40	86%			82%	Low	$$$$

High Recycled Content
Classified as containing greater than 50% total recycled content. Total recycled content is based on product composition of postconsumer and preconsumer (postindustrial) recycled content per FTC guidelines.

GRID PROFILE OPTIONS

DX/DXL SQ Edge	DXT SQ Edge	DX/DXL SLT Edge	DXT/DXF FLB Edge	DXI FL Edge	DX/DXL D-BESK Edge
					

DX/DXL BESK Edge	
	

SPECIFICATION DETAILS

Athena Acoustical Ceiling meets specifications in accordance with ASTM E1264 and EN13964.

Materials Classification
Type: III,
Form: 2,
Pattern: C

Substrate and Surface Finish
Mineral fiber substrate finished with factory-applied water-based paint

Thickness
16mm, 19mm

Size
600 x 600mm, 610 x 610mm,
600 x 1200mm, 610 x 1220mm

Edge Detail Trim
Square,
Reveal [SLT, FLB],
Concealed [BESK, D-BESK]

Weight
16mm [5.45 kg/m², Firecode®]
19mm [6.45 kg/m², Firecode®]

Noise Reduction Coefficient [NRC]
[0.65] [0.70]

Ceiling Attenuation Class [CAC]
[35 - 40 dB]

Mold Prevention Application as per ASTM D3273
Application available upon request per ASTM D3273-1, Rate 10 per D3274

Humidity Resistance
Maximum 99% RH / 40°C for ClimaPlus™

Light Reflectance Coefficient [LR]
0.86

Color
White similar to RAL 9016

Surface Burning Characteristics as per ASTM E84
Class A

Reaction to Fire as per EN 13501-1
Euroclass A2-s1, d0

Thermal Conductivity
λ = 0.05 W/m°K

Washability / Scrubbability as per ASTM D4828 & D2486
Exceeds 1000 Wash/Scrub cycles without surface break or the extent of abrasion upon request

Formaldehyde Classification
Class E1 as per EN717-1

Relevant LEED® Credit
EA Credit 1 | MR Credit 4 | MR Credit 5 | MR Credit 6 | IEQ Credit 3 | IEQ Credit 3.2 | IEQ Credit 4.6 | IEQ Credit 8.1 | IEQ Credit 9

Notice:
As we are involved in constant products development; this document information is subject to change without prior notice. Please always refer to **usgme.com** for the updated products information document.

©2022 Factory of USG Middle East LTD. Co.
All rights reserved.

USG ME
INNOVATIVE SOLUTIONS. EVERYTIME.

PLADIS - Complexe Futuris Logistic Lotissement Ennouala Lot N°2 Dépôt A3 Boulevard My Ismaïl- Casablanca
Tel: (212) 5 22 34 44 59 // (212) 5 22 34 44 62
Zi Gzenaya 341- Tanger , Tel: (+212) 5 31 43 65 10 Email: contact@pladis.ma Site Web : www.pladis.ma