TAIGA PERFORATED



VISIT USGME.COM TO ORDER SAMPLES



FEATURES & BENEFITS

- Offered in standard pin perforation for ideal mid-range sound absorption & sound attenuation, providing balance to room acoustics.
- Excellent for general commercial construction.
- Excellent for critical lighting applications; Taiga Perforated achieves High Light Reflectance (LR- 0.86).
- Maximum economy and design simplicity.
- Also available in washable & hygienic paint.
- High sound absorption up to 0.7 NRC; specially formulated in 16mm HNRC & 19mm thickness for school and executive offices.

APPLICATIONS

- Schools
- Healthcare
- Corridors
- Lobby areas
- Executive offices
- Retail stores

Absorption Coefficient

Frequency, Hz	125	250	500	1000	2000	4000	NRC*
12mm	0.25	**0.30**	**0.40**	**0.55**	**0.65**	0.70	**0.50**
15mm	0.35	**0.40**	**0.40**	**0.55**	**0.55**	0.55	**0.45**
16mm HNRC	0.30	**0.35**	**0.70**	**0.90**	**0.85**	0.75	**0.70**
19mm	0.35	**0.40**	**0.65**	**0.85**	**0.85**	0.70	**0.70**

** Calculated to ASTM C 423-01*

USG ME
INNOVATIVE SOLUTIONS. EVERYTIME.



TAIGA PERFORATED

EN 13964 : 2014 + A1 : 2007

PRODUCT CERTIFIED FOR LOW VOC EMISSIONS

HIGH SOUND ABSORPTION

CEILING ATTENUATION CLASS

HIGH RECYCLED CONTENT

TABLE OF PERFORMANCE

Edge Detail	Item	Size (mm)	NRC	CAC	Light Reflectance	Anti-Mold & Mildew/ Sag Resistance	Fire Rating	Recycled Content	VOC Emission	Cost
			NRC	CAC					<	$
SQ	TPS662 TPS222	600*600*12 610*610*12	0.50	35	86%			25%	Low	$
	TPS665 TPS225	600*600*15 610*610*15	0.45	35	86%			25%	Low	$
	TPC665 TPC225	600*600*15 610*610*15	0.45	35	86%	✓		39%	Low	$$
	TPC625 TPC245	600*1200*15 610*1220*15	0.45	35	86%	✓		39%	Low	$$
	TPC666-HNRC TPC226-HNRC	600*600*16 610*610*16	0.70	37	86%	✓		82%	Low	$$$
	TPC669 TPC229	600*600*19 610*610*19	0.70	37	86%	✓		39%	Low	$$$
SLT	TPSR665 TPSR225	600*600*15 610*610*15	0.45	35	86%			25%	Low	$$
	TPCR665 TPCR225	600*600*15 610*610*15	0.45	35	86%	✓		39%	Low	$$
	TPCR625 TPCR245	600*1200*15 610*1220*15	0.45	35	86%	✓		39%	Low	$$
	TPCR666-HNRC TPCR226-HNRC	600*600*16 610*610*16	0.70	37	86%	✓		82%	Low	$$$
	TPCR669 TPCR229	600*600*19 610*610*19	0.70	37	86%	✓		39%	Low	$$$
FLB	TPSRF665 TPSRF225	600*600*15 610*610*15	0.45	35	86%			25%	Low	$
	TPCRF665 TPCRF225	600*600*15 610*610*15	0.45	35	86%	✓		39%	Low	$$
	TPCRF625 TPCRF245	600*1200*15 610*1220*15	0.45	35	86%	✓		39%	Low	$$
	TPCRF666-HNRC TPCRF226-HNRC	600*600*16 610*610*16	0.70	37	86%	✓		82%	Low	$$$
	TPSRF669 TPSRF229	600*600*19 610*610*19	0.70	37	86%			39%	Low	$$$

Low Emissions (VOC)
Third party (GREENGUARD Gold) certified for low-emitting performance, meets California Department of Public Health (CDPH) Standard Method V1.2-2017 using a Classroom Environment. Product tested in accordance with UL 2821 test method to show compliance to emission limits on UL 2818. Section 7.1 and 7.2. UL. Tests are available on usgme.com and at spot.ul.com

High Recycled Content
Classified as containing greater than 50% total recycled content. Total recycled content is based on product composition of postconsumer and preconsumer (postindustrial) recycled content per FTC guidelines.

TAIGA PERFORATED

EN 13964 : 2014 + A1 : 2007






PRODUCT CERTIFIED FOR LOW VOC EMISSIONS

HIGH SOUND ABSORPTION

CEILING ATTENUATION CLASS

HIGH RECYCLED CONTENT

GRID PROFILE OPTIONS

DX/DXL SQ Edge	DXT SQ Edge	DX/DXL SLT Edge	DXT FLB Edge	DXF FLB Edge
				

SPECIFICATION DETAILS

Taiga Perforated Acoustical Ceiling meets specifications in accordance with ASTM E1264 and EN13964.

Materials Classification
Type: III,
Form: 2,
Pattern: C, E

Substrate and Surface Finish
Mineral fiber substrate finished with factory-applied water-based paint

Thickness
12mm, 15mm, 16mm, 19mm

Size
600 x 600mm, 610 x 610mm, 600 x 1200mm, 610 x 1220mm

Edge Detail Trim
Square, Reveal [SLT, FLB]

Weight
12mm [2.85 kg/m^2, Regular/ ClimaPlus™], 15mm [3.6 kg/m^2 Regular/ ClimaPlus™], 16mm [3.85 kg/m^2 Regular/ ClimaPlus™], 19mm [4.5 kg/m^2 Regular/ ClimaPlus™]

Noise Reduction Coefficient [NRC]
[0.45] [0.50] [0.70]

Ceiling Attenuation Class [CAC]
[35 - 37 dB]

Humidity Resistance
Maximum 99% RH / 40°C for ClimaPlus™

Light Reflectance Coefficient [LR]
0.86

Color
White similar to RAL 9016

Surface Burning Characteristics as per ASTM E84
Class A

Reaction to Fire as per EN 13501-1
Euroclass A2-s1, d0

Thermal Conductivity
λ = 0.057 W/m°K

Washability / Scrubbability as per ASTM D4828 & D2486
Exceeds 1000 Wash/Scrub cycles without surface break or the extent of abrasion upon request

VOC Class
Greenguard Gold

Formaldehyde Classification
Class E1 as per EN717-1

Relevant LEED® Credit
EA Credit 1 | MR Credit 4 | MR Credit 5 | MR Credit 6 | IEQ Credit 3 | IEQ Credit 3.2 | IEQ Credit 4.6 | IEQ Credit 8.1 | IEQ Credit 9

Notice:
As we are involved in constant products development; this document information is subject to change without prior notice. Please always refer to **usgme.com** for the updated products information document.

©2022 Factory of USG Middle East LTD. Co.
All rights reserved.

USG ME
INNOVATIVE SOLUTIONS. EVERYTIME.

PLADIS - Complexe Futuris Logistic Lotissement Ennouala Lot N°2 Dépôt A3 Boulevard My Ismaïl- Casablanca
Tel: (212) 5 22 34 44 59 // (212) 5 22 34 44 62
Zi Gzenaya 341- Tanger , Tel: (+212) 5 31 43 65 10 Email: contact@pladis.ma Site Web : www.pladis.ma