FAVIA



VISIT USGME.COM TO ORDER SAMPLES



FEATURES & BENEFITS

- Finest fissuring pattern among USG ME's product portfolio.
- Elegant non-directional pattern for a fresh, clean, and white appearance.
- Cost-effective series is ideal for retail business and general commercial stores.
- High light reflectance ceilings can reduce the number of light fixtures needed while maintaining good indoor environmental air quality.
- Durable and attractive micro-textured white surface for design freedom during installation.

APPLICATIONS

- Groceries
- Corridors and hallways
- Basements
- Administration offices
- Rest areas
- Cafeterias
- Warehouse

Absorption Coefficient	Frequency, Hz	125	250	500	1000	2000	4000	NRC*
	15mm	0.35	**0.25**	**0.20**	**0.20**	**0.30**	0.50	**0.25**

**Calculated to ASTM C 423-01*

USG ME
INNOVATIVE SOLUTIONS. EVERYTIME.

FAVIA




EN 13964 : 2014 + A1 : 2007

CEILING ATTENUATION CLASS

TABLE OF PERFORMANCE

Edge Detail	Item	Size (mm)	NRC	CAC	Light Reflectance	Anti-Mold & Mildew/ Sag Resistance	Fire Rating	Recycled Content	VOC Emission	Cost
			NRC	CAC						
SQ	FNS665 FNS225	600*600*15 610*610*15	0.25	35	85%			25%	Low	$
SLT	FNSR665 FNSR225	600*600*15 610*610*15	0.25	35	85%			25%	Low	$

GRID PROFILE OPTIONS

DX/DXL SQ Edge	DXT SQ Edge	DX/DXL SLT Edge
		

SPECIFICATION DETAILS

Favia Acoustical Ceiling meets specifications in accordance with ASTM E1264 and EN13964.

Materials Classification
Type: III,
Form: 2,
Pattern: D, E

Substrate and Surface Finish
Mineral fiber substrate finished with factory-applied water-based paint

Thickness
15mm

Size
600 x 600mm, 610 x 610mm

Edge Detail Trim
Square, Reveal [SLT]

Weight
15mm [3.6 kg/m², Regular/ ClimaPlus™]

Noise Reduction Coefficient [NRC]
[0.25]

Ceiling Attenuation Class [CAC]
[35 dB]

Humidity Resistance
Maximum 95% RH / 40°C for ClimaPlus™

Light Reflectance Coefficient [LR]
0.85

Color
White similar to RAL 9016

Surface Burning Characteristics as per ASTM E84
Class A

Reaction to Fire as per EN 13501-1
Euroclass A2-s1, d0

Thermal Conductivity
λ = 0.057 W/m°K

Washability / Scrubbability as per ASTM D4828 & D2486
Exceeds 1000 Wash/Scrub cycles without surface break or the extent of abrasion upon request

Formaldehyde Classification
Class E1 as per EN717-1

Relevant LEED® Credit
EA Credit 1 | MR Credit 4 | MR Credit 5 | MR Credit 6 | IEQ Credit 3 | IEQ Credit 3.2 | IEQ Credit 4.6 | IEQ Credit 8.1 | IEQ Credit 9

Notice:
As we are involved in constant products development; this document information is subject to change without prior notice. Please always refer to **usgme.com** for the updated products information document.

©2022 Factory of USG Middle East LTD. Co.
All rights reserved.

USG ME
INNOVATIVE SOLUTIONS. EVERYTIME.

PLADIS - Complexe Futuris Logistic Lotissement Ennouala Lot N°2 Dépôt A3 Boulevard My Ismaïl- Casablanca
Tel: (212) 5 22 34 44 59 // (212) 5 22 34 44 62
Zi Gzenaya 341- Tanger , Tel: (+212) 5 31 43 65 10 Email: contact@pladis.ma Site Web : www.pladis.ma