



TECHNICAL DATA SHEET

Distributed by Blau Batch | Manufactured by Coraplast Industries

Product Description

AST 349 is a Polyethylene (PE) based Antistatic masterbatch. It is specially designed for LDPE, LLDPE, HDPE and PP in Injection moulding, Extrusion and Blow moulding application, requiring excellent dispersion and antistatic properties. The product provides surface resistance from 109 – 1011 Ohms/Square. AST 349 contains synergist blend based antistatic agents and prevents dust build up during film processing & during the storage.

Addition Level

The addition level of masterbatch added depends on the performance requirements of the final application. Typically addition rates vary from 3% to 4% masterbatch.

Masterbatch Information

Parameter	Value
Product Code	AST 349
Colour	Natural
Carrier Polymer	PE
Appearance	Cylindrical Natural Granules

Physical Properties

Properties	Unit	Test Method	Specification
Heat Stability	°C	--	260°C
Moisture Content (Temp120°C, 10Min.)	%	ASTM D6980	< 0.20
Bulk Density	-	ASTM D1895	0.60 ± 0.1
Specific Gravity	-	ASTM D792	0.95 ± 0.1
Toxicity	--	--	NON-TOXIC
Dispersion	--	--	EXCELLENT
Typical Active Content	%	--	15

Regulatory

The product is food compliance as per 21 CFR US FDA 177.1520 AND 178.3130 & passes heavy metal limits and hence complies with RoHS directive 2002/95/EC.

Packaging & Storage



Antistatic Masterbatch AST 349 is supplied in regular pellet form packed in 25 kg bags. It should be stored in dry place. Recommended storage life is 1 year provided if it is stored as directed.

Note: Above report is made in identical condition. Values may be different when processed on different machines and/or different processing conditions, hence cannot be compared with any other same colour or product.