



TECHNICAL DATA SHEET

Distributed by Blau Batch | Manufactured by Coraplast Industries

Product Description

UVS 406 is a Polypropylene (PP) based UV masterbatch. It is designed for PP in Injection molding, Extrusion and Blow molding application, requiring excellent dispersion and UV stability.

Addition Level

The addition level of masterbatch added depends on the performance requirements of the final application. Typically addition rates vary from 2% to 4% masterbatch.

Masterbatch Information

Parameter	Value
Product Code	UVS 406
Colour	Natural
Carrier Polymer	PP
Appearance	Cylindrical Natural Granules

Physical Properties

Properties	Unit	Test Method	Specification
Light Fastness	--	--	NA
Heat Stability	°C	--	260°C
Moisture Content (Temp120°C, 10Min.)	%	ASTM D6980	< 0.20
Bulk Density	Gm/cc	ASTM D1895	0.60 ± 0.1
Dispersion	--	--	EXCELLENT
Melt Flow Index at 2300C, 2.16 Kg	Gm/10 min	ASTM D1238	35 ± 10
Specific Gravity	-	ASTM D792	0.89 ± 0.1
Typical Active Content	%	--	20
Pellet Count	No'S/1 Gm	--	30 - 50
Pellet Size	mm	--	2.5 – 3.5

Regulatory

UV Masterbatch UVS 406 does not comply with Food Approval directives.



Packaging & Storage

UV Masterbatch UVS 406 is supplied in regular pellet form packed in 25 kg bags. It should be stored in dry and moisture free place at a temperature $27 \pm 2^{\circ}\text{C}$. Open bag should be immediately closed after use. Recommended storage life is 1 year provided it is stored as directed.

Note: Above report is made in identical condition. Values may be different when processed on different machines and/or different processing conditions, hence cannot be compared with any other same colour or product.