



# TECHNICAL DATA SHEET

Distributed by Blau Batch | Manufactured by Coraplast Industries

## Product Description

UVS 439 is a Polypropylene (PP) based UV masterbatch. It is specially designed for PP in Injection molding, Extrusion and Blow molding application, requiring excellent dispersion and UV stability.

## Addition Level

The addition level of masterbatch added depends on the performance requirements of the final application. Typically addition rates vary from 1% to 4% masterbatch.

## Masterbatch Information

| Parameter       | Value                        |
|-----------------|------------------------------|
| Product Code    | UVS 439                      |
| Colour          | UV                           |
| Carrier Polymer | PP                           |
| Appearance      | Cylindrical Natural Granules |

## Physical Properties

| Properties                             | Unit      | Test Method | Specification |
|----------------------------------------|-----------|-------------|---------------|
| Heat Stability                         | °C        | --          | 260°C         |
| Moisture Content (Temp 120°C, 10 Min.) | %         | ASTM D6980  | < 0.20        |
| Bulk Density                           | Gm/cc     | ASTM D1895  | 1.00 ± 0.1    |
| Dispersion                             | --        | --          | EXCELLENT     |
| Melt Flow Index At 2300C, 2.16 Kg      | Gm/10 min | ASTM D1238  | 50 ± 20       |
| Specific Gravity                       | -         | ASTM D792   | 1.45 ± 0.1    |
| Typical UV Content                     | %         | --          | 20            |
| Ash Content                            | %         | ASTM D5630  | 50 ± 2        |
| Pellet Count                           | No'S/1 Gm | --          | 40 - 70       |
| Pellet Size                            | mm        | --          | 2.5 – 3.5     |

## Regulatory

UV Masterbatch UVS 439 does not comply with Food Approval directives.



---

## Packaging & Storage

---

UV Masterbatch UVS 439 is supplied in regular pellet form packed in 25 kg bags. It should be stored in dry place. Recommended storage life is 1 year provided it is stored as directed.

---

Note: Above report is made in identical condition. Values may be different when processed on different machines and/or different processing conditions, hence cannot be compared with any other same colour or product.