

TECHNICAL DATA SHEET

Product Description

AST 349 is a Polyethylene (PE) based Antistatic masterbatch. It is specially designed for LDPE, LLDPE, HDPE and PP in Injection moulding, Extrusion and Blow moulding application, requiring excellent dispersion and antistatic properties. The product provides surface resistance from $10^9 - 10^{11}$ Ohms/Square. AST 349 contains synergist blend based antistatic agents and prevents dust build up during film processing & during the storage.

Addition Level

The addition level of masterbatch added depends on the performance requirements of the final application. Typically addition rates vary from 3% to 4% masterbatch.

Masterbatch Information

1. Product Code AST 349
2. Colour Natural
3. Carrier Polymer PE
4. Appearance Cylindrical Natural Granules

Physical Properties:

Properties	Unit	Test Method	Specification
1. Heat Stability	°C	--	260°C
2. Moisture Content (Temp 120°C, 10Min.)	%	ASTM D6980	< 0.20
3. Bulk Density	-	ASTM D1895	0.60 ± 0.1
4. Specific Gravity	-	ASTM D792	0.95 ± 0.1
5. Toxicity	--	--	NON-TOXIC
6. Dispersion	--	--	EXCELLENT
7. Typical Active Content	%	--	15

Regulatory

The product is food compliance as per 21 CFR US FDA 177.1520 AND 178.3130 & passes heavy metal limits and hence complies with RoHS directive 2002/95/EC.

Packaging & Storage

Antistatic Masterbatch AST 349 is supplied in regular pellet form packed in 25 kg bags. It should be stored in dry place. Recommended storage life is 1 year provided if it is stored as directed.

Note: Above Report is made in identical condition, Values may be different when process on different machines and/or different processing condition, hence cannot be compare with any other same colour or product.

TECHNICAL SERVICES

Coraplast Industries

Survey No:180, Udvada Pariya Road, Village Dungri, Tal. Pardi, Dist. Valsad, Gujarat - 396185 India
T +91 98980 18180 E info@coraplast.com W coraplast.com