

TECHNICAL DATA SHEET

Product Description

BLACK 58 FS is a Polyethylene (PE) based Black masterbatch. It is specially designed for LDPE, LLDPE, HDPE and PP in Injection molding, Extrusion and Blow molding application, requiring excellent dispersion.

Addition Level

The addition level of masterbatch added depends on the performance requirements of the final application. Typically addition rates vary up to 10% masterbatch.

Masterbatch Information

- | | |
|--------------------|----------------------------|
| 1. Product Code | BLACK 58 FS |
| 2. Colour | BLACK |
| 3. Carrier Polymer | PE |
| 4. Appearance | Cylindrical Black Granules |

Physical Properties:

Properties	Unit	Test Method	Specification
1. Light Fastness	--	--	7 - 8
2. Heat Stability	°C	--	280°C
3. Moisture Content (Temp120°C, 10Min.)	%	ASTM D6980	< 0.20
4. Bulk Density	Gm/cc	ASTM D1895	0.90 ± 0.1
5. Melt Flow Index at 190°C, 21 Kg	Gm/10 min	ASTM D1238	8 - 16
6. Specific Gravity	-	ASTM D792	1.30 ± 0.1
7. Toxicity	--	--	NON-TOXIC
8. Dispersion	--	--	EXCELLENT
9. Ash Content	%	ASTM D5630	25 ± 2
10. Carbon Content	%	--	35 ± 2

Regulatory

The product is not food compliant. It passes heavy metal limits and hence complies with RoHS directive 2002/95/EC.

Packaging & Storage

Black Masterbatch BLACK 58 FS is supplied in regular pellet form packed in 25 kg bags. It should be stored in dry place.

Recommended storage life is 2 years provided it is stored as directed.

Note: Above Report is made in identical condition, Values may be different when process on different machines and/or different processing condition, hence cannot be compare with any other same colour or product.

TECHNICAL SERVICES

Coraplast Industries

Survey No:180, Udvada Pariya Road, Village Dungri, Tal. Pardi, Dist. Valsad, Gujarat - 396185 India
T +91 98980 18180 E info@coraplast.com W coraplast.com