

TECHNICAL DATA SHEET

Product Description

UVS 168 is a Polyethylene (PE) based UV masterbatch. It is specially designed for LDPE, LLDPE, HDPE and PP in Injection molding, Extrusion and Blow molding application, requiring excellent dispersion and UV stability.

Addition Level

The addition level of masterbatch added depends on the performance requirements of the final application. Typically addition rates vary from 1% to 3% masterbatch.

Masterbatch Information

- | | |
|--------------------|------------------------------|
| 1. Product Code | UVS 168 |
| 2. Colour | UV |
| 3. Carrier Polymer | PE |
| 4. Appearance | Cylindrical Natural Granules |

Physical Properties:

Properties	Unit	Test Method	Specification
1. Light Fastness	--	--	NOT APPLICABLE
2. Heat Stability	°C	--	260°C
3. Migration	--	--	NOT APPLICABLE
4. Moisture Content (Temp 120°C, 10Min.)	%	ASTM D6980	< 0.20
5. Bulk Density	Gm/cc	ASTM D1895	0.70 ± 0.1
6. Dispersion	--	--	EXCELLENT
7. Melt Flow Index at 190°C, 2.16 Kg	Gm/10 min	ASTM D1238	1 TO 10
8. UV Content	%	--	10 ± 1

Regulatory

UV Masterbatch UVS 168 complies with Food Approval directives 21 CFR US FDA.

Packaging & Storage

UV Masterbatch UVS 168 is supplied in regular pellet form packed in 25 kg bags. It should be stored in dry place.

Recommended storage life is 1 year provided it is stored as directed.

Note: Above Report is made in identical condition, Values may be different when process on different machines and/or different processing condition, hence cannot be compare with any other same colour or product.

TECHNICAL SERVICES

Coraplast Industries

Survey No:180, Udvada Pariya Road, Village Dungri, Tal. Pardi, Dist. Valsad, Gujarat - 396185 India
T +91 98980 18180 E info@coraplast.com W coraplast.com