

## TECHNICAL DATA SHEET

### Product Description

UVS 406 is a Polypropylene (PP) based UV masterbatch. It is designed for PP in Injection molding, Extrusion and Blow molding application, requiring excellent dispersion and UV stability.

### Addition Level

The addition level of masterbatch added depends on the performance requirements of the final application. Typically addition rates vary from 2% to 4% masterbatch.

### Masterbatch Information

1. Product Code            UVS 406
2. Colour                    Natural
3. Carrier Polymer        PP
4. Appearance            Cylindrical Natural Granules

### Physical Properties:

| Properties                               | Unit      | Test Method | Specification |
|------------------------------------------|-----------|-------------|---------------|
| 1. Light Fastness                        | --        | --          | NA            |
| 2. Heat Stability                        | °C        | --          | 260°C         |
| 3. Moisture Content (Temp 120°C, 10Min.) | %         | ASTM D6980  | < 0.20        |
| 4. Bulk Density                          | Gm/cc     | ASTM D1895  | 0.60 ± 0.1    |
| 5. Dispersion                            | --        | --          | EXCELLENT     |
| 6. Melt Flow Index at 230°C, 2.16 Kg     | Gm/10 min | ASTM D1238  | 35 ± 10       |
| 7. Specific Gravity                      | -         | ASTM D792   | 0.89 ± 0.1    |
| 8. Typical Active Content                | %         | --          | 20            |
| 9. Pellet Count                          | No'S/1 Gm | --          | 30 - 50       |
| 10. Pellet Size                          | mm        | --          | 2.5 – 3.5     |

### Regulatory

UV Masterbatch UVS 406 does not comply with Food Approval directives.

### Packaging & Storage

UV Masterbatch UVS 406 is supplied in regular pellet form packed in 25 kg bags. It should be stored in dry and moisture free place at a temperature  $27 \pm 2^{\circ}\text{C}$ . Open bag should be immediately closed after use.

Recommended storage life is 1 year provided it is stored as directed.

**Note:** Above Report is made in identical condition. Values may be different when process on different machines and/or different processing condition, hence cannot be compare with any other same colour or product.

**TECHNICAL SERVICES**

**Coraplast Industries**

Survey No:180, Udvada Pariya Road, Village Dungri, Tal. Pardi, Dist. Valsad, Gujarat - 396185 India  
**T** +91 98980 18180 **E** info@coraplast.com **W** coraplast.com