

TECHNICAL DATA SHEET

Product Description

UVS 439 is a Polypropylene (PP) based UV masterbatch. It is specially designed for PP in Injection molding, Extrusion and Blow molding application, requiring excellent dispersion and UV stability.

Addition Level

The addition level of masterbatch added depends on the performance requirements of the final application. Typically addition rates vary from 1% to 4% masterbatch.

Masterbatch Information

- | | |
|--------------------|------------------------------|
| 1. Product Code | UVS 439 |
| 2. Colour | UV |
| 3. Carrier Polymer | PP |
| 4. Appearance | Cylindrical Natural Granules |

Physical Properties:

Properties	Unit	Test Method	Specification
1.Heat Stability	°C	--	260°C
2.Moisture Content (Temp120°C, 10Min.)	%	ASTM D6980	< 0.20
3.Bulk Density	Gm/cc	ASTM D1895	1.00 ± 0.1
4.Dispersion	--	--	EXCELLENT
5.Melt Flow Index At 230°C, 2.16 Kg	Gm/10 min	ASTM D1238	50 ± 20
6.Specific Gravity	-	ASTM D792	1.45 ± 0.1
7.Typical UV Content	%	--	20
8.Ash Content	%	ASTM D5630	50 ± 2
9.Pellet Count	No'S/1 Gm	--	40 - 70
10.Pellet Size	mm	--	2.5 – 3.5

Regulatory

UV Masterbatch UVS 439 does not comply with Food Approval directives.

Packaging & Storage

UV Masterbatch UVS 439 is supplied in regular pellet form packed in 25 kg bags. It should be stored in dry place.

Recommended storage life is 1 year provided it is stored as directed.

Note: Above Report is made in identical condition. Values may be different when process on different machines and/or different processing condition, hence cannot be compare with any other same colour or product.

TECHNICAL SERVICES

Coraplast Industries

Survey No:180, Udvada Pariya Road, Village Dungri, Tal. Pardi, Dist. Valsad, Gujarat - 396185 India
T +91 98980 18180 **E** info@coraplast.com **W** coraplast.com