# TECHNICAL DATA SHEET

Distributed by Blau Batch | Manufactured by Coraplast Industries

## Product Description

AB 222 is a Polyethylene (PE) based Antiblock masterbatch. It is specially designed for LDPE, LLDPE, HDPE and PP in Extrusion (films and sheets) application, requiring excellent dispersion and anti-block properties. It reduces coefficient of friction between layers of film.

## Addition Level

The addition level of masterbatch added depends on the performance requirements of the final application. Typically addition rates vary from 2% to 6% masterbatch.

## Masterbatch Information

| Parameter | Value |
|---|---|
| **Product Code** | AB 222 |
| **Carrier Polymer** | PE |
| **Appearance** | Cylindrical Granules |

## Physical Properties

| Properties | Unit | Test Method | Specification |
|---|---|---|---|
| **Light Fastness** | -- | -- | NA |
| **Heat Stability** | °C | -- | 280°C |
| **Moisture Content (Temp120°C, 10Min.)** | % | ASTM D6980 | < 0.20 |
| **Bulk Density** | Gm/cc | ASTM D1895 | 0.60 ± 0.1 |
| **Melt Flow Index At 1900C, 2.16 Kg** | Gm/10 min | ASTM D1238 | 35 ± 10 |
| **Specific Gravity** | - | ASTM D792 | 1.00 ± 0.1 |
| **Toxicity** | -- | -- | NON-TOXIC |
| **Dispersion** | -- | -- | EXCELLENT |
| **Typical Active Content** | % | -- | 20 |

## Regulatory

The product is food compliance as per European directive AP 89(1) and EU 10/2011.

## Packaging & Storage

Antiblock Masterbatch AB 222 is supplied in regular pellet form packed in 25 kg bags. It should be stored in dry place. Recommended storage life is 1 year provided it is stored as directed.

Note: Above report is made in identical condition. Values may be different when processed on different machines and/or different processing conditions, hence cannot be compared with any other same colour or product.