



PT. BULAWAN DAYA LESTARI

PT. BULAWAN DAYA LESTARI

MINING & INDUSTRY COMPANY

SITE BULAWAN DAYA LESTARI, BOLAANG MONGONDOW, SULAWESI UTARA



PT. LABUHA INTERNUSA

FINAL REPORT OF ANALYSIS
LABORATORY PT. BULAWAN DAYA LESTARI

Request By : Ade Irpan Muamar
 Departement : Grade Control
 Division : Grade Control
 Date Received : 21/08/2026
 Date Completed Of Report : 22/08/2026

Sample ID : G BB (1083 - 1092)
 Total of Sample : 10
 Type of Sample : Solid
 Location : Pit 2
 Job No : BDL2608062-GC

No	METHODS STORE UNITS	Aqua Regia						CN Extraction						MC
		Au	Au (R1)	Ag	Ag (R1)	Cu	Cu (R1)	Au	Au (R1)	Ag	Ag (R1)	Cu	Cu (R1)	
	ELEMENT ASSAY	gpt	gpt	gpt	gpt	gpt	gpt	gpt	gpt	gpt	gpt	gpt	gpt	%
	DATA STORE UNITS	0.05	0.05	0.3	0.3	1	1	0.05	0.05	0.05	0.05	1	1	%
	LLD's in STORE UNITS	0.05	0.05	0.3	0.3	1	1	0.05	0.05	0.05	0.05	1	1	%
	SCHEME	AuAR	AuAR	AgAR	AgAR	CuAR	CuAR	AuCN	AuCN	AgCN	AgCN	CuCN	CuCN	MC
1	G BB 1082	0.023		NA		NA		NA		NA		NA		NA
2	G BB 1083	0.196		NA		NA		NA		NA		NA		NA
3	G BB 1084	1.179		NA		NA		NA		NA		NA		NA
4	G BB 1085	1.107		NA		NA		NA		NA		NA		NA
5	G BB 1086	4.096	4.015	NA		NA		NA		NA		NA		NA
6	G BB 1087	1.031		NA		NA		NA		NA		NA		NA
7	G BB 1088	0.706		NA		NA		NA		NA		NA		NA
8	G BB 1089	0.060		NA		NA		NA		NA		NA		NA
9	G BB 1090	0.157	0.116	NA		NA		NA		NA		NA		NA
10	G BB 1091	0.041		NA		NA		NA		NA		NA		NA
	NILAI RATA-RATA	0.860		NA		NA		NA		NA		NA		NA

QUALITY CONTROL

No	METHODS STORE UNITS	AR Extraction	
		Au	Au (R1)
	ELEMENT ASSAY	gpt	gpt
	DATA STORE UNITS	0,05	0,05
	LLD's in STORE UNITS	0,05	0,05
	SCHEME	AuAR	AuAR
1	G BB 1086	4.096	4.015
2	G BB 1090	0.157	0.116
3	Blank	<0.05	
4	RL OxD 183	0.428	
5	Value RL OxD 183	0.453	
6	Upper RL OxD 183	0.498	
7	Lower RL OxD 183	0.408	
8	RL OxD 191	1.145	
9	Value RL OxD 191	1.093	
10	Upper RL OxD 191	1.202	
11	Lower RL OxD 191	0.984	

Notes : NA : Not Analysed
 SNR : Sample Not Received
 SNL : Sample Not Listed
 R : Repeat
 DTF : Data To Follow

Multazam, S.T.	Ryan Pongoh, S.Si
Laboratory Foreman	Laboratory Coordinator