

Certificate of Material Test Report

Manufacturer/Hersteller Wuxi Dibao Precision Forging Technology Co., Ltd

Address/Adresse Wuxi City, Jiangsu Province

Certificate No./Zertifikat Nr. 25091503-3

Purchaser/Besteller GEMÜ Valves (China) Co.Ltd

Order No. Bestell Nr.	81480-30	Article No. Artikel-Nr.	88466286	Part .Part	Diaphragm valve D-body	Quantity Menge	634	Product Erzeugnis	Forging
Item description Modell Nr	5D402-F3-050-90-860			Manufacture's Mark Zeichen des Herstellers	SF	Technical Requirements Technische		0-0005-KZF3 Terms of delivery Rev.056468	
Material Werkstoff	F316L	Melting process Erschmelzungsart	EAF+AOD+CC			Heat No. Schmelze Nr.	250314	Heat treatment batch Wärmebehandlung	2025-09-12 AY1
acc. To nach	UNS S31603 ASME-BPE-2019 Table MM-2.1-1, ASME SA182-2018 – F316L					Delivery condition Lieferbedingungen		Solution treat and quenched 1060°C/ water	

	Chemical Composition Chemische Zusammensetzung										Ferrite Content Ferrit Inhalt
Test Methods Prüfstandard	ASTM A751-2014a										ASTM E562-19
	C	Si	Mn	P	S	Cr	Mo	Ni	N	Others	Delta – Ferrite (%)
Requirements Anforderungen	≤0.030	≤1.0	≤2.0	≤0.045	0.005-0.017	16.0-18.0	2.0-3.0	10.0-14.0	≤0.10		≤2.0
Actual Istwert	0.019	0.472	1.181	0.039	0.01	16.78	2.049	10.05	0.052		0.7

	Tensile Test/Zugversuch				Impact Test/Aufprallprüfung						Hardness/Härte
Test Methods Prüfstandard	ASME SA370-2017				DIN EN ISO 148-1						ASME SA370-2017
Requirements Anforderungen	Rp0.2(min)	Rm(min)	A(min)	Z(min)	along >10mm, min.100J at 20°C						(HBW)
	170N/mm ²	485N/mm ²	30%	50%	average value	Spec.1	Spec.2	Spec.3			For reference
Actual Istwert	307	595	62	80	193	196	188	194			168

Notes :	EAF: Electric Arc Furnace	AOD: Argon Oxygen Decarburization	CC: Continuous Casting
	Rp0.2: Yield Strength	Rm: Tensile Strength	A: Elongation
			Z: Reduction in Area

We hereby certify that the material described above complies with the terms of the order.

Hiermit bestätigen wir, dass das oben beschriebene Material den Auftragsbedingungen entspricht.

Created by/Erstellt von

Checked by/geprüft von Tao Hongming

15.09.2025