

Spin Dynamic Methods

September 7, 2026

Contents

1	Notation and Conventions	1
2	Spin Hamiltonians	2
2.1	Atomistic Spin Hamiltonian	2
2.2	Macrospin Effective Fields	3
2.2.1	One-Sublattice Model	3
2.2.2	Two-Sublattice Collinear Model	4
3	Magnetization Dynamics	5
4	Thermal Stability and Fluctuations	6
4.1	Thermal Stability Factor	6
4.2	Thermal Field in a Macrospin Model	6

1 Notation and Conventions

Unless a section explicitly states otherwise, vectors are bold, unit vectors carry a hat, time is measured in seconds, and magnetic fields $\mathbf{H}$ are expressed in A m⁻¹. The following symbols are used throughout the library.

$\mathbf{m}$ Normalized magnetization, with $\|\mathbf{m}\| = 1$.

$\mathbf{s}_i$ Unit spin direction at site i .

M_s Saturation magnetization of the ferromagnetic layer.

$\mathbf{H}_{\text{eff}}$ Effective magnetic field.

σ Spin-polarization unit vector.

α Dimensionless Gilbert damping parameter.

γ Positive gyromagnetic ratio, $\gamma = g\mu_B/\hbar$, where g is the Landé g -factor.

γ_0 Positive gyromagnetic factor for an $\mathbf{H}$ -field formulation, $\gamma_0 = \mu_0 |\gamma|$.

θ_{SH} Spin-Hall angle.

J_c Charge-current density.

t_{FM} Ferromagnetic-layer thickness.

β Signed torque ratio, $\beta = \tau_{\text{FLT}}/\tau_{\text{DLT}}$.

$\tau_{\text{DLT}}, \tau_{\text{FLT}}$ Damping-like and field-like torque amplitudes, respectively; both have field units.

e Positive elementary charge.

μ_0 Vacuum permeability.

μ_{B} Bohr magneton.

$\hbar$ Reduced Planck constant.

k_{B} Boltzmann constant.

T Absolute temperature.

Physical constants. The following values reproduce `constantfile.m`:

$$\begin{aligned} \gamma &= 1.760859644 \times 10^{11} \text{ rad s}^{-1} \text{ T}^{-1}, & e &= 1.602176565 \times 10^{-19} \text{ C}, \\ \mu_0 &= 1.25663706143592 \times 10^{-6} \text{ T m A}^{-1}, & \mu_{\text{B}} &= 9.274 \times 10^{-24} \text{ J T}^{-1}, \\ \hbar &= 6.58211951440 \times 10^{-16} \text{ eV s}, & k_{\text{B}} &= 1.38064852 \times 10^{-23} \text{ J K}^{-1}. \end{aligned}$$

Convention warning. Some references define the effective field as $\mathbf{B}_{\text{eff}}$ in tesla and use $|\gamma|$, whereas this library uses $\mathbf{H}_{\text{eff}}$ in A m^{-1} and $\gamma_0 = \mu_0 |\gamma|$. Check this convention before copying an equation into simulation code.

2 Spin Hamiltonians

2.1 Atomistic Spin Hamiltonian

Equation. Following the ASTRO exchange-sign convention, a classical spin Hamiltonian containing exchange, uniaxial anisotropy, Dzyaloshinskii–Moriya interaction, and Zeeman energy is

$$\begin{aligned} \mathcal{H} = & + \frac{1}{2} \sum_{i \neq j} J_{ij} \mathbf{s}_i \cdot \mathbf{s}_j - \sum_i K_i (\mathbf{s}_i \cdot \hat{\mathbf{e}}_i)^2 \\ & - \frac{1}{2} \sum_{i \neq j} \mathbf{D}_{ij} \cdot (\mathbf{s}_i \times \mathbf{s}_j) - \sum_i \boldsymbol{\mu}_i \cdot \mathbf{B}_{\text{ext}}. \end{aligned} \quad (2.1)$$

Definitions. J_{ij} is the exchange-link energy in the ASTRO sign convention: $J_{ij} < 0$ favors parallel alignment, whereas $J_{ij} > 0$ favors antiparallel alignment. K_i is the uniaxial anisotropy energy, $\hat{\mathbf{e}}_i$ is the easy-axis direction, $\mathbf{D}_{ij}$ is the Dzyaloshinskii–Moriya vector, and $\boldsymbol{\mu}_i$ is the magnetic moment at site i .

Assumptions. Each $\mathbf{s}_i$ is a classical unit vector. The pair coefficients satisfy $J_{ji} = J_{ij}$ and $\mathbf{D}_{ji} = -\mathbf{D}_{ij}$. The factors of $1/2$ assume that the pair sums include both ordered pairs (i, j) and (j, i) . If each physical bond is instead included only once, for example in a unique-bond sum $\sum_{\langle i, j \rangle}$, both factors of $1/2$ must be omitted. These are equivalent pair-counting conventions and must not be mixed.

Pair counting and effective field. Let $\mu_i = |\boldsymbol{\mu}_i|$ and define the effective flux density by

$$\mathbf{B}_{\text{eff},i} = -\frac{1}{\mu_i} \frac{\partial \mathcal{H}}{\partial \mathbf{s}_i}. \quad (2.2)$$

For the ordered-pair Hamiltonian above, the exchange and DMI contributions are

$$\mathbf{B}_{\text{ex},i} = -\frac{1}{\mu_i} \sum_{j \neq i} J_{ij} \mathbf{s}_j, \quad \mathbf{B}_{\text{DMI},i} = \frac{1}{\mu_i} \sum_{j \neq i} \mathbf{s}_j \times \mathbf{D}_{ij}. \quad (2.3)$$

The two ordered occurrences of each bond give identical derivatives, which cancel the Hamiltonian factors of 1/2. Consequently, no extra factor of 1/2 belongs in either effective-field expression.

Units. All terms in $\mathcal{H}$ have units of energy. Here the external flux density $\mathbf{B}_{\text{ext}}$ is measured in tesla, so no additional factor of μ_0 appears in the Zeeman term.

Source. For the extended classical spin Hamiltonian and Hamiltonian-derivative field convention, see Evans et al. [2].

Implementation notes. The ASTRO implementation evaluates the field, $\mathbf{B}_{\text{eff},i} = -(1/\mu_i) \partial \mathcal{H} / \partial \mathbf{s}_i$, rather than the total energy and includes both forward and backward nearest neighbors. The J_{ij} used above is therefore the coefficient stored in ASTRO's exchange-link arrays: its exchange field is $-(1/\mu_i) \sum_j J_{ij} \mathbf{s}_j$ [4]. No factor of 1/2 should appear in the exchange or DMI field formulas because differentiation produces two identical bond contributions, cancelling the Hamiltonian factor. ASTRO's DMI component expressions correspond to $\mathbf{D}_{ij} = D(\hat{\mathbf{z}} \times \hat{\mathbf{r}}_{ij})$ and the antisymmetry $\mathbf{D}_{ji} = -\mathbf{D}_{ij}$ used above.

2.2 Macrospin Effective Fields

Field convention. For a fixed-length macrospin with normalized magnetization $\mathbf{m}$, let w denote the magnetic energy density in J m^{-3} . The effective magnetic field and the corresponding effective flux density are

$$\mathbf{H}_{\text{eff}} = -\frac{1}{\mu_0 M_s} \frac{\partial w}{\partial \mathbf{m}}, \quad \mathbf{B}_{\text{eff}} = \mu_0 \mathbf{H}_{\text{eff}}. \quad (2.4)$$

Thus, an LLG equation written with $\gamma_0 = \mu_0 |\gamma|$ uses $\mathbf{H}_{\text{eff}}$ in A m^{-1} , whereas one written with $|\gamma|$ uses $\mathbf{B}_{\text{eff}}$ in tesla. The two conventions are physically equivalent but their field variables must not be mixed.

Unless stated otherwise, K_u , A_{12} , and the sublattice constants K_i in Eq. (2.12) are energy densities in J m^{-3} . The interfacial K_i in the combination $K_{\text{bulk}} + K_i/t_{\text{FM}}$ is instead in J m^{-2} , and every saturation magnetization is in A m^{-1} . The tensors $\mathbf{N}$ and $\mathbf{K}_{fp}$ are dimensionless.

2.2.1 One-Sublattice Model

Energy density and field decomposition. For uniaxial anisotropy with easy axis $\hat{\mathbf{u}}$, a dimensionless symmetric demagnetization tensor $\mathbf{N}$, an applied field $\mathbf{H}_{\text{ext}}$, and a dipolar field $\mathbf{H}_{\text{dip}}$ produced by another magnetic body, use the uniaxial-anisotropy convention from slides 13–14 of the EE237 Week 5 lecture notes [8] and take

$$w_1 = K_u \left[1 - (\mathbf{m} \cdot \hat{\mathbf{u}})^2 \right] + \frac{\mu_0 M_s^2}{2} \mathbf{m} \cdot \mathbf{N} \mathbf{m} - \mu_0 M_s \mathbf{m} \cdot (\mathbf{H}_{\text{ext}} + \mathbf{H}_{\text{dip}}). \quad (2.5)$$

Slide 21 of the same notes writes the demagnetization self-energy as [8]

$$E_{\text{demag}} = -\frac{\mu_0}{2} \int_V \mathbf{M}(\mathbf{r}) \cdot \mathbf{H}_{\text{demag}}(\mathbf{r}) d^3r, \quad (2.6)$$

$$w_{\text{demag}} = -\frac{\mu_0}{2} \mathbf{M} \cdot \mathbf{H}_{\text{demag}} = \frac{\mu_0 M_s^2}{2} \mathbf{m} \cdot \mathbf{N} \mathbf{m} \quad (\text{uniform macrospin}). \quad (2.7)$$

The factor 1/2 avoids double counting the magnet's self-interaction. Equation (2.4) gives

$$\mathbf{H}_{\text{an}} = \frac{2K_u}{\mu_0 M_s} (\mathbf{m} \cdot \hat{\mathbf{u}}) \hat{\mathbf{u}}, \quad \mathbf{B}_{\text{an}} = \frac{2K_u}{M_s} (\mathbf{m} \cdot \hat{\mathbf{u}}) \hat{\mathbf{u}}, \quad (2.8)$$

$$\mathbf{H}_{\text{demag}} = -M_s \mathbf{N} \mathbf{m}, \quad \mathbf{B}_{\text{demag}} = -\mu_0 M_s \mathbf{N} \mathbf{m}. \quad (2.9)$$

For $\hat{\mathbf{u}} = \hat{\mathbf{z}}$, the anisotropy term reduces to $K_u(1 - m_z^2) = K_u \sin^2 \theta$, as on slide 13. Near $m_z = 1$, slide 14 therefore gives $H_{\text{an},z} = 2K_u/(\mu_0 M_s)$. For a thin film with bulk and interfacial uniaxial anisotropy, $K_u = K_{\text{bulk}} + K_i/t_{\text{FM}}$. For principal axes, $\mathbf{N} = \text{diag}(N_x, N_y, N_z)$ and $N_x + N_y + N_z = 1$.

Dipolar field. Let a pinned macrospin have volume V_p , saturation magnetization $M_{s,p}$, and direction $\mathbf{m}_p$, so its magnetic moment is $\boldsymbol{\mu}_p = V_p M_{s,p} \mathbf{m}_p$. In the point-dipole approximation, at displacement $\mathbf{r} = r \hat{\mathbf{r}}$ from the pinned layer to the free layer, slide 22 gives the dipole formula [8]. The slide denotes it by $\mathbf{H}_i$, but its factor μ_0 makes it a flux density in tesla; therefore, in the convention of this document,

$$\mathbf{B}_{\text{dip}} = \frac{\mu_0}{4\pi r^3} [3(\boldsymbol{\mu}_p \cdot \hat{\mathbf{r}}) \hat{\mathbf{r}} - \boldsymbol{\mu}_p] = \mu_0 \mathbf{H}_{\text{dip}}, \quad (2.10)$$

The complete conservative one-sublattice field, with an optional stochastic field added after taking the energy derivative, is

$$\mathbf{H}_{\text{eff}} = \mathbf{H}_{\text{ext}} + \mathbf{H}_{\text{an}} + \mathbf{H}_{\text{demag}} + \mathbf{H}_{\text{dip}} + \mathbf{H}_{\text{th}}. \quad (2.11)$$

Spin-transfer and spin-orbit torques are nonconservative and are not part of the energy derivative in Eq. (2.4).

2.2.2 Two-Sublattice Collinear Model

Fixed-length LLG model. Let $\mathbf{m}_1$ and $\mathbf{m}_2$ be separately normalized sublattice magnetizations with saturation magnetizations $M_{s,1}$ and $M_{s,2}$. Apply the slide-13 uniaxial energy independently to each sublattice [8] and use the exchange-energy density convention

$$w_2 = \sum_{i=1}^2 K_i [1 - (\mathbf{m}_i \cdot \hat{\mathbf{u}}_i)^2] + A_{12} \mathbf{m}_1 \cdot \mathbf{m}_2 - \mu_0 \sum_{i=1}^2 M_{s,i} \mathbf{m}_i \cdot \mathbf{H}_{\text{ext}}, \quad (2.12)$$

$A_{12} > 0$ favors antiparallel alignment. Applying $\mathbf{H}_{\text{eff},i} = -(\mu_0 M_{s,i})^{-1} \partial w_2 / \partial \mathbf{m}_i$ yields, for $j \neq i$,

$$\mathbf{H}_{\text{an},i} = \frac{2K_i}{\mu_0 M_{s,i}} (\mathbf{m}_i \cdot \hat{\mathbf{u}}_i) \hat{\mathbf{u}}_i, \quad (2.13)$$

$$\mathbf{H}_{\text{ex},i} = -\frac{A_{12}}{\mu_0 M_{s,i}} \mathbf{m}_j, \quad \mathbf{B}_{\text{ex},i} = -\frac{A_{12}}{M_{s,i}} \mathbf{m}_j. \quad (2.14)$$

The additive anisotropy constants $K_1 + K_2$ do not contribute to either effective field. This is the convention used in the two-sublattice ferrimagnetic macrospin model of Yuan et al. [6], where $A_{12} = A_{\text{ex}} > 0$. If the exchange energy is instead written $-J_{12} \mathbf{m}_1 \cdot \mathbf{m}_2$, then $\mathbf{H}_{\text{ex},i} =$

$J_{12}\mathbf{m}_j/(\mu_0 M_{s,i})$ and antiferromagnetic coupling corresponds to $J_{12} < 0$. Because each fixed-length sublattice is spatially uniform, an intra-sublattice exchange energy is orientation independent and produces no macrospin torque; spatial exchange stiffness is therefore absent from this model class.

When the two sublattices occupy the same uniformly magnetized body, define

$$\mathbf{M}_{\text{net}} = M_{s,1}\mathbf{m}_1 + M_{s,2}\mathbf{m}_2, \quad \mathbf{l} = \frac{\mathbf{m}_1 - \mathbf{m}_2}{2}. \quad (2.15)$$

The common demagnetizing field is then $\mathbf{H}_{\text{demag}} = -\mathbf{N}\mathbf{M}_{\text{net}}$. Unequal sublattice moments describe a ferrimagnet; equal antiparallel moments give a compensated antiferromagnet. A convenient total-field form is

$$\mathbf{H}_{\text{eff},i} = \mathbf{H}_{\text{ext}} + \mathbf{H}_{\text{an},i} + \mathbf{H}_{\text{ex},i} + \mathbf{H}_{\text{demag}} + \mathbf{H}_{\text{dip}} + \mathbf{H}_{\text{th},i}. \quad (2.16)$$

The dipolar term may be omitted for a compensated antiferromagnet when the net stray field is negligible, but this is a model assumption rather than an identity.

Implementation mapping. The current one-sublattice `ODELLGintegral` implementation stores flux-density quantities in tesla [7]. Its `field_eta.m` evaluates the following expressions, where its input named `Hk` is B_k :

$$\begin{aligned} \mathbf{B}_{\text{an}} &= B_k m_y \hat{\mathbf{y}} \quad (\text{IMA}), & \mathbf{B}_{\text{an}} &= B_k m_z \hat{\mathbf{z}} \quad (\text{PMA}), \\ \mathbf{B}_{\text{demag}} &= -\mu_0 M_s \mathbf{N} \mathbf{m}, & \mathbf{B}_{\text{dip}} &= \mu_0 K_{12} M_s \mathbf{m}_{\text{PL}}, \end{aligned}$$

after converting the input M_s from emu cm^{-3} to A m^{-1} . It sums these with the applied and thermal fields. The two-sublattice equations above are publication-grounded extensions and are not implemented by that repository.

3 Magnetization Dynamics

LLGS form with field-like torque.

$$\begin{aligned} \frac{d\mathbf{m}}{dt} = & -\gamma \mathbf{m} \times \mathbf{H}_{\text{eff}} + \alpha \mathbf{m} \times \frac{d\mathbf{m}}{dt} - \gamma \tau_{\text{DLT}} \mathbf{m} \times (\mathbf{m} \times \boldsymbol{\sigma}) \\ & + \gamma \tau_{\text{FLT}} \mathbf{m} \times \boldsymbol{\sigma}. \end{aligned} \quad (3.1)$$

Equivalent LL form with field-like torque.

$$\begin{aligned} (1 + \alpha^2) \frac{d\mathbf{m}}{dt} = & -\gamma \mathbf{m} \times \mathbf{H}_{\text{eff}} - \alpha \gamma \mathbf{m} \times (\mathbf{m} \times \mathbf{H}_{\text{eff}}) \\ & + \alpha \gamma \tau_{\text{DLT}} \mathbf{m} \times \boldsymbol{\sigma} - \gamma \tau_{\text{DLT}} \mathbf{m} \times (\mathbf{m} \times \boldsymbol{\sigma}) \\ & + \alpha \gamma \tau_{\text{FLT}} \mathbf{m} \times (\mathbf{m} \times \boldsymbol{\sigma}) + \gamma \tau_{\text{FLT}} \mathbf{m} \times \boldsymbol{\sigma}. \end{aligned} \quad (3.2)$$

Torque amplitudes. For a ferromagnetic layer,

$$\tau_{\text{DLT}} = \frac{\hbar \theta_{\text{SH}} J_c}{2e t_{\text{FM}} M_s}, \quad \tau_{\text{FLT}} = \beta \tau_{\text{DLT}}.$$

Torque-sign convention. In the convention of Eq. (3.1), the sign product of the damping-like and field-like SOT is negative when $\beta > 0$ [1]. Specifically, the scalar prefactors of their respective vector structures are $-\gamma \tau_{\text{DLT}}$ and $+\gamma \tau_{\text{FLT}}$, so their sign product is

$$(-\gamma \tau_{\text{DLT}})(+\gamma \tau_{\text{FLT}}) = -\gamma^2 \beta \tau_{\text{DLT}}^2 < 0 \quad (\beta > 0).$$

Thus, a positive β means that the two SOT terms have oppositely signed scalar prefactors in the LLGS equation, even though the signed amplitudes τ_{DLT} and τ_{FLT} themselves have the same sign.

4 Thermal Stability and Fluctuations

4.1 Thermal Stability Factor

Equation. For a single energy barrier E_b , the thermal stability factor is

$$\Delta = \frac{K_u V}{k_B T} \quad (4.1)$$

Units. E_b and $k_B T$ must use the same energy unit; Δ is dimensionless.

4.2 Thermal Field in a Macrospin Model

Correlation. For the $\mathbf{H}$ -field convention used in Eq. (3.1), one common white-noise convention is

$$\langle H_{\text{th},i}(t) H_{\text{th},j}(t') \rangle = \frac{2\alpha k_B T}{\gamma_0 M_s V} \delta_{ij} \delta(t - t'). \quad (4.2)$$

Implementation notes. The discrete-time variance depends on the stochastic calculus convention, the form of the LLG equation, and the time-step definition. Derive the sampled-noise amplitude from the exact solver convention rather than copying Eq. (4.2) without checking it.

References

- [1] J. Park, G. E. Rowlands, O. J. Lee, D. C. Ralph, R. A. Buhrman, Macrospin modeling of sub-ns pulse switching of perpendicularly magnetized free layer via spin-orbit torques for cryogenic memory applications, *Appl. Phys. Lett.*, **105**, 102404 (2014).
- [2] R. F. L. Evans, W. J. Fan, P. Chureemart, T. A. Ostler, M. O. A. Ellis, R. W. Chantrell, Atomistic spin model simulations of magnetic nanomaterials, *J. Phys.: Condens. Matter*, **26**, 103202 (2014).
- [3] Z. Kong, Z. Xu, X. Zhang, B. Zhao, Y. Yang, L. Zhu, Z. Zhu, Spatially asymmetric switching under spin-orbit torque and Dzyaloshinskii–Moriya interaction, *J. Appl. Phys.*, **140**, 063903 (2026).
- [4] Z. Zhu, ASTRO atomistic spin-dynamics code, GitHub repository, commit `9c807cf`.
- [5] Z. Zhu, J. Deng, X. Fong, G. Liang, Voltage-input spintronic oscillator based on competing effect for extended oscillation regions, *J. Appl. Phys.*, **125**, 183902 (2019).
- [6] Z. Yuan, J. Long, Z. Xu, Y. Xin, L. An, J. Ren, X. Zhang, Y. Yang, Z. Zhu, Anomalous impact of thermal fluctuations on spin transfer torque induced ferrimagnetic switching, *J. Appl. Phys.*, **133**, 153903 (2023).
- [7] Z. Zhu, ODE_LLG_integral macrospin LLGS code, GitHub repository, commit `348e46c`.
- [8] EE237 Week 5 lecture slides, Magnetic Anisotropy, Magnetostatics, and Zeeman Energy, slides 13–14 and 21–22.