TRINSEO

PULSE™ 130

Trinseo - Polycarbonate + ABS

Wednesday, January 29, 2020

General Information

Product Description

PULSE™ 130 developmental compound is especially designed for automotive interior applications.

PULSE™ 130 is a high heat, high impact PC/ABS blend. PULSE™ 130 is designed to meet the low gloss and high heat automotive interior component applications as well as exterior component applications.

Applications

- Middle consoles
- Instrument panel components
- Door panel trims
- Pillars
- Storage & glove box
- Spoilers

General

Generic Name	• Polycarbonate + ABS (PC+ABS)		
Material Status	• Experimental: Active		
Availability	• Asia Pacific		
Features	• High Heat Resistance	• High Impact Resistance	• Low Gloss
Uses	• Automotive Applications	• Automotive Exterior Parts	• Automotive Interior Parts
Forms	• Pellets		

ASTM & ISO Properties [1]

Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm³	ISO 1183/B
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	16	g/10 min	ISO 1133
Molding Shrinkage	0.40 to 0.70	%	ISO 294-4
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Tensile Stress (Yield)	55.0	MPa	ISO 527-2/50
Tensile Strain (Break)	110	%	ISO 527-2/50
Flexural Modulus [2]	2400	MPa	ISO 178
Impact	**Nominal Value**	**Unit**	**Test Method**
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	40	kJ/m²	
23°C	55	kJ/m²	
Thermal	**Nominal Value**	**Unit**	**Test Method**
Vicat Softening Temperature	130	°C	ISO 306/B50

Processing Information

Injection	Nominal Value	Unit
Processing (Melt) Temp	255 to 275	°C
Mold Temperature	50 to 80	°C

Notes

[1] Typical properties: these are not to be construed as specifications.

[2] 2.0 mm/min