PA66 5500-GF25NH

Glass fiber reinforced & flame retardant Polyamide 66

DESCRIPTION

- ■High rigidity
- ■Non-halogen
- ■Good impact resistanc

APPLICATION

- ■Injection molding
- ■Electirc parts
- ■Automotive

PROPERTY		VALUES	UNIT	TEST METHOD
Mechnical Propertites				
Tensile Strength	50mm/min	140	MPa	ISO 527
Tensile Elongation@Break	50mm/min	2.9	%	ISO 527
Flexual Strength	2mm/min	200	MPa	ISO 178
Flexual Modulus	2mm/min	7000	MPa	ISO 178
IZOD Impact Strength,Notched	23℃	10	KJ/M2	ISO 180/1A
Thermal Properties				
Heat Distortion Temperature	1.80MPa	235	˚C	ISO 75-2
Physical Properties				
Specific Gravity		1.35	g/cm^3	ISO 1183
Rockwell Hardness	HRR	115		ISO 2309
Mold Shrinkage, flow, 3.2 mm		0.4/0.9	%	WOTE METHOD
Water Absorption	24H	0.7	%	ISO 62
Glassfiber Content		25	%	WOTE METHOD
Electrical Properties				
Surface Resistivity		1E+15	Ω	IEC 60093
Glow-wire Flammability Index		960	°C	IEC 60695-2
Flame Properties				
UL Recognized Flammability	1.6mm	V0	Class	UL94

PA66 5500-GF25NH

PROCESSING CONDITIONS	VALUES	UNIT
Drying Time	4-6	h
Drying Temperature	85-95	℃
Melt Temperature	260	℃
Nozzle Temperature	290	℃
Front - Zone 3 Temperature	265-300	℃
Middle - Zone 2 Temperature	270-295	℃
Rear - Zone 1 Temperature	260-280	℃
Mold Temperature	60-100	℃
Injection Speed	middle-fast	

CLAIM

The properties data presented on this datasheet are typical values, and not guaranteed specification.

Last Update: 2022/1/10

CONTRACT

SHENZHEN WOTE ADVANCED MATERIALS CO.,LTD

31st Floor, Tower B, Building 7, International Innovation Valley, Vanke Cloud City (Phase 3), Nanshan District, Shenzhen, Guangdong

Tel: +86-755-26880866 Fax: +86-755-26880966 http://www.wotlon.com