FOR INTERNAL USE ONLY

Property Data

DSM

Xytron™

Xytron™ G3084E(R-X08896DW)

PPS-I-GF30

Print Date: 2022-05-11

Properties	Typical Data	Unit	Test Method
Rheological properties	**Value**		
Molding shrinkage (parallel)	0.2	%	ISO 294-4
Molding shrinkage (normal)	0.65	%	ISO 294-4
Mechanical properties	**Value**		
Tensile modulus	10900	MPa	ISO 527-1/-2
Stress at break	164	MPa	ISO 527-1/-2
Strain at break	2.3	%	ISO 527-1/-2
Flexural modulus	10000	MPa	ISO 178
Flexural strength	242	MPa	ISO 178
Charpy impact strength (+23°C)	65	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	13	kJ/m²	ISO 179/1eA
Weldline strength at thickness 1	72	MPa	ISO 527-1/-2
Weldline strain at thickness 1	0.9	%	ISO 527-1/-2
Thermal properties	**Value**		
Melting temperature (10°C/min)	280	°C	ISO 11357-1/-3
Glass transition temperature (10°C/min)	90	°C	ISO 11357-1/-2
Temp. of deflection under load (1.80 MPa)	260	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.17	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.5	E-4/°C	ISO 11359-1/-2
Coef. of lin. therm expansion, parallel, above Tg	0.13	E-4/°C	ISO 11359-1/-2
Coef. of lin. therm expansion, normal, above Tg	1.28	E-4/°C	ISO 11359-1/-2
Thermal conductivity in plane	0.28	W/(m K)	ASTM E1461

HEALTH · NUTRITION · MATERIALS

DSM

BRIGHT SCIENCE. BRIGHTER LIVING.

Property Data

DSM

Xytron™ G3084E(R-X08896DW)

Print Date: 2022-05-11

Properties	Typical Data	Unit	Test Method
Thermal conductivity through plane	0.3	W/(m K)	ASTM E1461

Other properties	Value		
Density	1510	kg/m^3	ISO 1183