

Hifax TRC 221P/2 G14008

聚丙烯
LyondellBasell Industries

Technical Data

产品说明
Hifax TRC 221P/2 is a 20% talc filled PP copolymer, with medium flowability, very good impact/stiffness balance, low CLTE (Coefficient of Linear Thermal Expansion) and good UV resistance. This grade is delivered in customer customized colors, this Data Sheet is giving general properties, some of them may be slightly altered upon color selected.

总览

材料状态	已商用：当前有效
资料 ¹	Technical Datasheet
搜索 UL 黄卡	- LyondellBasell Industries - Hifax
供货地区	欧洲
特性	- 耐紫外光性能，良好 - 中等流动性
用途	- 汽车防撞杆 - 汽车领域的应用
加工方法	注射成型

物理性能	额定值	单位制	测试方法
密度 (23°C)	1.04	g/cm³	ISO 1183/A
熔速率 (熔体流动速率) (230°C/2.16 kg)	16	g/10 min	ISO 1133

机械性能	额定值	单位制	测试方法
拉伸应力 (断裂, 23°C)	16.0	MPa	ISO 527-2
弯曲模量 ³ (23°C)	1500	MPa	ISO 178/A
弯曲应力 ³ (23°C)	22.0	MPa	ISO 178/A

冲击性能	额定值	单位制	测试方法
悬臂梁缺口冲击强度			ISO 180/1A
-30°C	5.5	kJ/m²	
23°C	40	kJ/m²	

热性能	额定值	单位制	测试方法
载荷下热变形温度 (1.8 MPa, 未退火)	55.0	°C	ISO 75-2/A
维卡软化温度	45.0	°C	ISO 306/B50

免责声明
This grade is not intended for medical, pharmaceutical, food and drinking water applications.

备注
¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
² 一般属性：这些不能被视为规格。
³ 类型 1A