

Hostacom G3 N01 L

聚丙烯

LyondellBasell Industries

PROSPECTOR®

www.ulprospector.com

Technical Data

产品说明
Hostacom G3 N01 L is a 30% glass fiber reinforced PP homopolymer, with low melt flow, high stiffness, low CLTE (Coefficient of Linear Thermal Expansion) and low creep under load at elevated temperatures. Product is UL listed in all colors. This grade is delivered in natural color version.

总览	
材料状态	• 已商用：当前有效
资料 ¹	• Technical Datasheet
UL 黄卡 ²	• E31765-10219990 • E86615-10224554
搜索 UL 黄卡	• LyondellBasell Industries • Hostacom
供货地区	• 欧洲
填料/增强材料	• 玻璃纤维增强材料, 30% 填料按重量
用途	• 大型家用电器和小型家用电器 • 电气/电子应用领域 • 汽车领域的应用
机构评级	• UL
加工方法	• 注射成型

物理性能	额定值 单位制	测试方法
密度 (23°C)	1.15 g/cm³	ISO 1183/A
熔速率 (熔体流动速率) (230°C/5.0 kg)	5.0 g/10 min	ISO 1133
熔融体积流量 (MVR) (230°C/5.0 kg)	5.0 cm³/10min	ISO 1133
机械性能	额定值 单位制	测试方法
拉伸模量 (23°C)	6500 MPa	ISO 527-1
拉伸应力 (断裂, 23°C)	90.0 MPa	ISO 527-2
拉伸应变 (断裂, 23°C)	3.5 %	ISO 527-2
冲击性能	额定值 单位制	测试方法
简支梁缺口冲击强度 (23°C)	11 kJ/m²	ISO 179/1eA
简支梁无缺口冲击强度 (23°C)	48 kJ/m²	ISO 179/1eU
热性能	额定值 单位制	测试方法
载荷下热变形温度		
0.45 MPa, 未退火	155 °C	ISO 75-2/B
1.8 MPa, 未退火	140 °C	ISO 75-2/A
维卡软化温度	140 °C	ISO 306/B50
可燃性	额定值 单位制	测试方法
UL 阻燃等级		UL 94
1.5 mm	HB	
3.0 mm	HB	

免责声明
This grade is not intended for medical, pharmaceutical, food and drinking water applications.

备注
¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
² UL 黄卡含有 UL 验证的易燃性和电气特性。UL Prospector 持续努力在 Prospector 中将黄卡链接至单个塑料材料，然而此列表可能未包括所有相应链接。重要的是，我们对 Prospector 中找到的这些黄卡和塑料材料之间的关联进行验证。如需完整的黄卡列表，请访问 UL 黄卡搜索。
³ 一般属性：这些不能被视为规格。