



Product description

(PC+ABS) blend; General Purpose Grade; Vicat/B 120 temperature = 131 °C; good injection molding processing behaviour (easy flowing); excellent long-term ageing behaviour under humid conditions and painting performance; improved chemical resistance; low VOC emissions and odour

Applications

Injection molding

Typical Values

Rheological properties

Property	Test Condition	Value	Unit	Standard
Melt volume-flow rate (MVR)	260 °C/5 kg	18	cm ³ /10min	ISO 1133-1
Molden shrinkage, parallel	60×60×2 mm; 260 °C; MT 80 °C; 500 bar	0.55 - 0.75	%	ISO 294-4
Molden shrinkage, normal	60×60×2 mm; 260 °C; MT 80 °C; 500 bar	0.55 - 0.75	%	ISO 294-4
Melt viscosity	260 °C; 1000 s ⁻¹	235	Pascal sec	b.o. ISO 11443-A

Mechanical properties (23 °C/50 % r. h.)

Property	Test Condition	Value	Unit	Standard
Tensile modulus	1 mm/min	2,300	MPa	ISO 527-1,-2
Yield stress	50 mm/min	56	MPa	ISO 527-1,-2
Yield strain	50 mm/min	4.9	%	ISO 527-1,-2
Nomin. strain at break	50 mm/min	100	%	ISO 527-1,-2
Stress at break	50 mm/min	55	MPa	ISO 527-1,-2
Izod impact strength	-30 °C	N	kJ/m ²	ISO 180/U
Izod impact strength	23 °C	N	kJ/m ²	ISO 180/U
Izod notched impact	23 °C	57	kJ/m ²	ISO 180/A
Izod notched impact	-30 °C	46	kJ/m ²	ISO 180/A
Charpy notched impact strength	-30 °C	47	kJ/m ²	ISO 179/1eA
Charpy notched impact strength	23 °C	60	kJ/m ²	ISO 179/1eA
Charpy impact strength	-30 °C	N	kJ/m ²	ISO 179/1eU
Charpy impact strength	23 °C	N	kJ/m ²	ISO 179/1eU
Puncture maximum force	-30 °C	5,400	N	ISO 6603-2
Puncture maximum force	23 °C	4,500	N	ISO 6603-2
Puncture energy	-30 °C	56	J	ISO 6603-2



Property	Test Condition	Value	Unit	Standard
Puncture energy	23 °C	48	J	ISO 6603-2

Thermal properties

Property	Test Condition	Value	Unit	Standard
Temperature of deflection under load	0.45 MPa	127	°C	ISO 75-1,-2
Temperature of deflection under load	1.80 MPa	106	°C	ISO 75-1,-2
Vicat	50 N; 120 °C/h	131	°C	ISO 306
Vicat	50 N; 50 °C/h	129	°C	ISO 306
Coef. of lin. therm. expansion, parallel	23 to 55 °C	0.7	10 ⁻⁴ /K	ISO 11359-1,-2
Coeff. Lin. Therm. Exp., normal	23 to 55 °C	0.7	10 ⁻⁴ /K	ISO 11359-1,-2
Burning Behaviour	0.85 mm	HB (COVESTRO TEST)		UL 94

Electrical properties (23 °C/50 % r. h.)

Property	Test Condition	Value	Unit	Standard
Relative permittivity	1 MHz	3.0000		IEC 60250
Relative permittivity	100 Hz	3.0000		IEC 60250
Dissipation factor	1 MHz	90	10 ⁻⁴	IEC 60250
Dissipation factor	100 Hz	20	10 ⁻⁴	IEC 60250
Volume resistivity		1E16	Ohm*m	IEC 62631-3-1
Surface Resistivity		1.00E+16	Ohm	IEC 62631-3-2
Electrical strength	1 mm	40	kV/mm	IEC 60243-1
Comparative tracking index (CTI)	Solution A	225		IEC 60112

Other properties (23 °C)

Property	Test Condition	Value	Unit	Standard
Water absorption (saturation value)	Water at 23 °C	0.4	%	ISO 62
Water absorption (equilibrium value)	23 °C; 50 % r. h.	0.1	%	ISO 62
Density		1,140	kg/m ³	ISO 1183-1

Processing conditions for test specimens

Property	Test Condition	Value	Unit	Standard
Injection mold.-Melt temp.		280	°C	ISO 294
Injection mold.-Mold temp.		80	°C	ISO 294
Injection mold.-Inj. velocity		240	mm/s	ISO 294

Recommended processing and drying conditions

Property	Test Condition	Value	Unit	Standard
Standard Melt Temperature		280	°C	
Mold Temperatures		70 - 90	°C	



Property	Test Condition	Value	Unit	Standard
Dry Air Drying Temperature		95 - 110	°C	
Dry Air Drying Time		4	Hour	
Moisture Content max. (%)		0.01	%	

Health and Safety Information

Before working with this product, you must read and become familiar with the available information on its risks, proper use, and handling. Information is available in several forms, e.g., in particular in the currently valid safety data sheets and product labels. For further information contact your Covestro representative.

[The Product Safety First Program | Covestro](#)

Disclaimer

General

The manner in which you use our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products to determine suitability for your processing and intended uses. Your analysis must at least include testing to determine suitability from a technical, health, safety, and environmental and regulatory standpoint. Such testing has not necessarily been done by Covestro, and Covestro has not obtained any approvals or licenses for a particular use or application of the product.

Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request.

All information and including technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed by you that you assume and hereby expressly release indemnify us and hold us harmless from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

This product is not intended for the manufacture of end products or intermediates intended for regulated applications, in particular in the sectors: Agriculture, Cosmetics, Drinking water, Food contact, Medical Applications (e.g. medical devices), Toys.

If the product is intended to be used for the manufacture of a regulated product, Covestro must be contacted in advance to obtain express consent to distribute the product for this purpose.

Notwithstanding the foregoing, the sole responsibility for determining the suitability of the product for a regulated application lies with the purchaser. Any liability or warranty on the part of Covestro based on any representations or warranties is expressly excluded.

Sample

Any samples provided by Covestro are for testing purposes only and not for commercial use.



Typical Value

These values are typical values only. Unless explicitly agreed in written form, they do not constitute a binding material specification or warranted values. Values may be affected by the design of the mold/die, the processing conditions and coloring/pigmentation of the product. Unless specified to the contrary, the property values given have been established on standardized test specimens at room temperature.

Shrinkage

Shrinkage data is provided as a reference only, and is based on sample plaques molded under specific, controlled processing conditions. Shrinkage rates in production parts can vary and are influenced by several variables such as, but not limited to: part design (e.g. part size, thickness and geometry), mold design (e.g. gate type and location, runner design, mold materials, cooling system), molding conditions (e.g. processing temperature, mold temperature, packing time and pressure, injection speed).

We suggest materials be evaluated in existing applicable molds to achieve the most accurate shrinkage estimation for your specific application and processing practices. The final choice of shrinkage is the responsibility of the user of the material, and should be made based on your experience and testing results. We shall not be liable for any damage caused by the use of the shrinkage data as provided by us. If you have any questions, pls consult technical representatives from Covestro.

Recommended Processing and Drying Conditions

Barrel temperatures are valid for a standard 3-zone barrel. Temperature set-up for different barrel types may change according to configuration. Values for hold pressure as percentage of injection pressure may vary depending on, amongst others, part geometry, injection molding machine and injection mold. Drying conditions are for dry air dryers only. Drying times and drying temperatures may differ depending on valid dryer type.

Contact

Please use our [contact form](#) or contact us directly by sending an e-mail to technical-datasheets@cx.covestro.com .
