

Technical Data

产品说明				
30% Glass Fiber Reinforced, Heat Stabilized, Wear and Friction Modified				
总览				
材料状态	• 已商用：当前有效			
资料 ¹	• Processing (English) • Technical Datasheet (English) • White Paper - Delivering high-performance gears for compact electric engine actuators (English) • White Paper - High Performance Plastics in Automotive Actuator Applications (English) • White Paper - Leveraging safe, high-performance materials for kitchen utensils (English) • White Paper - Meeting food contact safety standards in the kitchen (English) • White Paper - Optimizing gear performance in small appliances (English) • White Paper - Optimizing gears for electric brake actuators (English)			
搜索 UL 黄卡	• Envalor • Stanyl®			
供货地区	• 北美洲 • 拉丁美洲 • 非洲和中东 • 欧洲 • 亚太地区			
填料/增强材料	• 玻璃纤维增强材料, 30% 填料按重量			
添加剂	• 热稳定剂 • PTFE 润滑剂			
特性	• 耐磨损性, 良好 • 热稳定性 • 润滑			
加工方法	• 注射成型			
多点数据	• Isothermal Stress vs. Strain (ISO 11403)			
树脂 ID	• (PA46+PTFE)-GF30			
物理性能	干燥	调节后的	单位制	测试方法
密度	1.47	--	g/cm³	ISO 1183
收缩率				ISO 294-4
垂直	1.2	--	%	
流动	0.30	--	%	
吸水率				ISO 62
24 hr, 23°C	2.2	--	%	
饱和, 23°C	7.6	--	%	
平衡, 23°C, 50% RH	2.6	--	%	
粘数	145	--	cm³/g	ISO 307
机械性能	干燥	调节后的	单位制	测试方法
拉伸模量				ISO 527-1
--	10000	--	MPa	
120°C	5700	--	MPa	
160°C	5400	--	MPa	
拉伸应力				ISO 527-2
断裂	205	--	MPa	
断裂, 120°C	115	--	MPa	
断裂, 160°C	100	--	MPa	
拉伸应变				ISO 527-2
断裂	3.6	--	%	
断裂, 120°C	6.8	--	%	
断裂, 160°C	7.3	--	%	



冲击性能	干燥	调节后的	单位制	测试方法
简支梁缺口冲击强度				ISO 179/1eA
-30°C	10	--	kJ/m²	
23°C	12	--	kJ/m²	
简支梁无缺口冲击强度 (23°C)	85	--	kJ/m²	ISO 179/1eU
热性能	干燥	调节后的	单位制	测试方法
玻璃转化温度 ³	75.0	--	°C	ISO 11357-2
熔融温度 ³	295	--	°C	ISO 11357-3
线形热膨胀系数				ISO 11359-2
流动	1.8E-5	--	cm/cm/°C	
垂直	7.0E-5	--	cm/cm/°C	
电气性能	干燥	调节后的	单位制	测试方法
表面电阻率	--	1.0E+13	ohms	IEC 62631-3-2
体积电阻率	1.0E+12	1.0E+7	ohms·m	IEC 62631-3-1
漏电起痕指数	400	--	V	IEC 60112

备注

- ¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
- ² 一般属性：这些不能被视为规格。
- ³ 10°C/min