

Technical Data

产品说明		
Flame-retardant, Halogen-free. Does not contain chlorine or bromine with V-0 flame retardant rating. Achieves the same balance between mechanical properties and fluidity as existing halogen-based flame retardant brands. Glass content: 45%		
Application examples		
Board-to-cable connector, Board-to-cable(FPC) connector, USB connector, Electrical and electronic applications		
总览		
材料状态	• 已商用：当前有效	
资料 ¹	• Technical Datasheet (English)	
搜索 UL 黄卡	• Kuraray Co., Ltd. • Genestar™	
供货地区	• 北美洲 • 拉丁美洲 • 非洲和中东 • 欧洲 • 亚太地区	
填料/增强材料	• 玻璃纤维增强材料, 45% 填料按重量	
特性	• 良好的流动性 • 无溴 • 无卤 • 阻燃性 • Chlorine Free	
用途	• 电气/电子应用领域 • 连接器	
物理性能	额定值 单位制	测试方法
密度	1.53 g/cm³	ISO 1183/A
收缩率		ISO 294-4
垂直：2.00 mm	0.70 %	
流动：2.00 mm	0.20 %	
吸水率 (24 hr, 23°C)	0.10 %	ISO 62
机械性能	额定值 单位制	测试方法
拉伸应力	150 MPa	ISO 527-2
拉伸应变 (断裂)	1.5 %	ISO 527-2
弯曲模量	13900 MPa	ISO 178
弯曲应力	220 MPa	ISO 178
冲击性能	额定值 单位制	测试方法
简支梁缺口冲击强度	9.3 kJ/m²	ISO 179/1eA
可燃性	额定值 单位制	测试方法
UL 阻燃等级	V-0	UL 94
补充信息	额定值 单位制	
Bar Flow Length - 750kgf (320°C, 500.0 µm)	55 mm	

备注

¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。

² 一般属性：这些不能被视为规格。