

SABIC® PPcompound CX0281

高结晶性聚丙烯
SABIC

Technical Data

产品说明

SABIC® PPcompound CX0281 is a high crystalline copolymer. It offers high stiffness in perfect balance with high thermal dimensional stability, impact resistance and flow. This material has excellent aesthetic properties as well and is typically used for automotive interior applications. It is the obvious alternative to conventional talc-filled copolymers, offering considerable weight saving advantage.

SABIC® PPcompound CX0281 is a designated automotive grade.

IMDS ID: 1015442982

总览

材料状态	• 已商用：当前有效		
资料 ¹	• Technical Datasheet		
搜索 UL 黄卡	• SABIC • SABIC® PPcompound		
供货地区	• 北美洲 • 非洲和中东	• 拉丁美洲 • 欧洲	• 亚太地区

物理性能	额定值	单位制	测试方法
密度	0.905	g/cm³	ISO 1183
熔速率 (熔体流动速率) (230°C/2.16 kg)	15	g/10 min	ISO 1133
收缩率 ³ (24 小时, 3.20 mm)	1.6	%	内部方法
机械性能	额定值	单位制	测试方法
拉伸模量 (注塑)	1550	MPa	ISO 527-1/1A
拉伸应力			ISO 527-2/1A
屈服, 注塑	27.0	MPa	
断裂, 注塑	20.0	MPa	
拉伸应变 (断裂, 注塑)	100	%	ISO 527-2/1A
弯曲模量 ⁴ (注塑)	1450	MPa	ISO 178
冲击性能	额定值	单位制	测试方法
悬壁梁缺口冲击强度			ISO 180/1A
-20°C, 注塑	6.0	kJ/m²	
0°C, 注塑	7.0	kJ/m²	
23°C, 注塑	11	kJ/m²	
热性能	额定值	单位制	测试方法
载荷下热变形温度 ⁵			
0.45 MPa, 未退火	93.0	°C	ISO 75-2/B
1.8 MPa, 未退火	53.0	°C	ISO 75-2/A
线形热膨胀系数 - 流动 (-30 到 100°C)	1.0E-4	cm/cm/°C	ISO 11359-2
补充信息	额定值	单位制	测试方法
填充物	0.0	%	内部方法

备注

¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。

² 一般属性：这些不能被视为规格。

³ 65x65x3.2 mm

⁴ 类型 1A

⁵ Injection Molded

