

热塑性弹性体
Teknor Apex 公司

Technical Data

产品说明

Monprene OM-16450 NAT XRD1 is part of a series of adhesion-modified thermoplastic elastomers designed for over-molding (insert and multi-shot) and co-extrusion onto many engineering thermoplastics, including: PC, ABS, PC/ABS, CoPE, PET, PBT, PMMA, PSA, ASA, SAN, POM, and more. These materials exhibit dry haptics and are well suited for grips and other soft-touch parts. Monprene OM-16450 NAT XRD1 is REACH-SVHC and RoHS compliant and offers several benefits including superior adhesion onto PC/ABS and easy molding with a wide processing window.

总览

材料状态	• Preliminary Data		
资料 ¹	• Technical Datasheet		
搜索 UL 黄卡	• Teknor Apex 公司 • Monprene®		
供货地区	• 北美洲 • 非洲和中东	• 拉丁美洲 • 欧洲	• 亚太地区
特性	• 低的压缩变形性 • 可粘结性 • 良好的成型性能 • 良好的开裂抵抗 • 良好的流动性	• 良好的柔韧性 • 良好的着色性 • 良好抗撞击性 • 耐刮擦性 • 耐化学品性能，良好	• 韧性良好 • 无卤 • 中等密度 • 中等硬度 • Conformable
用途	• 安全设备 • 包覆成型 • 垫圈 • 盖子	• 工业部件 • 工业应用 • 管道密封 • 柔软触感应用	• 消费品应用领域 • 旋钮 • 粘合
RoHS 合规性	• RoHS 合规		
外观	• 不透明	• 可用颜色	• 自然色
形式	• 粒子		
加工方法	• 多次注射成型	• 注射成型	

物理性能	额定值	单位制	测试方法
密度 / 比重	1.11	g/cm³	ASTM D792
熔流量 (熔体流动速率) (230°C/2.16 kg)	3.0	g/10 min	ASTM D1238
弹性体	额定值	单位制	测试方法
抗张强度 ³ (断裂)	4.00	MPa	ASTM D412
伸长率 ³ (断裂)	500	%	ASTM D412
硬度	额定值	单位制	测试方法
肖氏硬度			ASTM D2240
邵氏 A, 1 秒, 注塑	55		
邵氏 A, 5 秒, 注塑	53		
补充信息	额定值	单位制	
Adhesion to ABS			
Adhesion to COPE			
Adhesion to PBT			
Adhesion to PC			
Adhesion to PC/ABS			
Adhesion to PMMA			

法律声明

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

注射	额定值 单位制
干燥温度	80 °C
干燥时间	3.0 到 4.0 hr
料筒后部温度	200 到 240 °C
料筒中部温度	200 到 250 °C
料筒前部温度	220 到 260 °C
射嘴温度	220 到 260 °C
加工 (熔体) 温度	220 到 260 °C
模具温度	32 到 54 °C
注塑压力	1.38 到 5.52 MPa
注射速度	快速
背压	0.172 到 0.689 MPa
螺杆转速	50 到 100 rpm
垫层	3.81 到 25.4 mm

注射说明

Drying is strongly suggested to enhance bondability.

For any overmolding process it is recommended that the process temperatures for the TPE material be set at least 50°F (10°C) higher than the melt temperature of the substrate material.

备注

- ¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
- ² 一般属性：这些不能被视为规格。
- ³ C 模具, 500 mm/min