

ENLITE™ LGF 2351 NM7700019
Structural Polymer Dryblend

ABS Resin
Trinseo

Technical Data

产品说明

This LGF35 ABS Alloy system is developed for light weight semi-structural applications which require very high stiffness also at elevated temperatures. This system is especially suitable for structural components with high demands on dimensional stability and good chemical resistance..

- Applications
- Auto Interior Parts
 - Structural Parts

总览	
材料状态	• 已商用：当前有效
资料 ¹	• Technical Datasheet
搜索 UL 黄卡	• Trinseo
供货地区	• 亚太地区
特性	• 高刚性 • 高强度 • High Dimensional Stability
用途	• 构件 • 汽车内部零件 • 汽车领域的应用 • 汽车仪表板
形式	• 粒子
加工方法	• 注射成型

物理性能	额定值 单位制	测试方法
密度	1.35 g/cm³	ISO 1183/A
机械性能	额定值 单位制	测试方法
拉伸模量	10500 MPa	ISO 527-1/1
拉伸应力 (断裂)	130 MPa	ISO 527-2/5
拉伸应变 (断裂)	1.6 %	ISO 527-2/5
弯曲模量 ³	10800 MPa	ISO 178
弯曲应力 ³	185 MPa	ISO 178
冲击性能	额定值 单位制	测试方法
简支梁缺口冲击强度 (23°C)	22 kJ/m²	ISO 179/1eA
简支梁无缺口冲击强度 (23°C)	30 kJ/m²	ISO 179/1eU
热性能	额定值 单位制	测试方法
载荷下热变形温度 (1.8 MPa, 未退火)	122 °C	ISO 75-2/A
维卡软化温度	115 °C	ISO 306/B50

补充信息

These are typical properties as measured on injection molded specimens ('dogbones') defined by ISO 3167 type 1a (L= 175 mm, center-section: 80x10x4 mm).

注射	额定值 单位制
干燥温度	80 °C
干燥时间	4.0 hr
加工 (熔体) 温度	255 到 280 °C
模具温度	60 到 80 °C

备注

¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。

² 一般属性：这些不能被视为规格。

³ 2.0 mm/min