

Technical Data

产品说明

Overview:
MAGNUM™ 3416SC LE is developed as Low odor high-heat MASS ABS for the automotive industry. MAGNUM™ 3416SC LE resin pellets as well as the parts made by it have less odor, even in a wide process window. It is universally suitable for all interior and exterior applications.

- Benefits:
- Low odor of the resin pellets and parts made by it
 - Lot to lot consistency allowing for optimal machine parameters settings from the start
 - Self-coloring enabling improvement of costs by using less pigments and lowering your logistic costs
 - Low VOC allowing a better interior air quality facing increasing regulatory and OEMs constraints.
 - Heat stability during wide range of processing temperatures: enhanced part design freedom

- Applications:
- Main interior and exterior automotive applications
 - Mid-consoles
 - Door panels
 - Door handles
 - Pillars

总览

材料状态	• 已商用：当前有效		
资料 ¹	• Brochure - MAGNUM™ ABS - Tthe Benchmark ABS for Extrusion (English) • Brochure - MAGNUM™ ABS Resins - Proven to enhance productivity and efficiency (English) • Technical Datasheet		
搜索 UL 黄卡	• Trinseo • MAGNUM™		
供货地区	• 亚太地区		
特性	• 良好的加工性能 • 良好刚性	• 耐热性，中等 • 气味低到无	• 中等抗冲击强度
用途	• 汽车领域的应用 • 汽车内部零件	• 汽车外部零件 • 外壳	
形式	• 粒子		
加工方法	• 注射成型		

物理性能	额定值	单位制	测试方法
密度	1.05	g/cm³	ISO 1183
表观密度	0.65	g/cm³	ISO 60
熔流率 (熔体流动速率)			ISO 1133
220°C/10.0 kg	6.5	g/10 min	
230°C/3.8 kg	2.3	g/10 min	
收缩率	0.40 到 0.70	%	ISO 294-4

MAGNUM™ 3416SC LE

ABS Resin

Trinseo

PROSPECTOR®

www.ulprospector.com

机械性能	额定值 单位制	测试方法
拉伸模量	2100 MPa	ISO 527-1/1
拉伸应力 (屈服)	43.0 MPa	ISO 527-2/50
拉伸应变		ISO 527-2/50
屈服	3.0 %	
断裂	30 %	
弯曲模量 ³	2100 MPa	ISO 178
弯曲应力 ³	67.0 MPa	ISO 178
冲击性能	额定值 单位制	测试方法
简支梁缺口冲击强度 (23°C, 注塑)	14 kJ/m²	ISO 179/1eA
热性能	额定值 单位制	测试方法
载荷下热变形温度 (1.8 MPa, 未退火)	83.0 °C	ISO 75-2/A
维卡软化温度	108 °C	ISO 306/B50
可燃性	额定值 单位制	测试方法
UL 阻燃等级 ⁴		UL 94
1.5 mm	HB	
3.0 mm	HB	
碳排放 ⁴	20.0 µg/g	VDA 277
补充信息	Mass balance versions (bio-based (BIO) or chemically recycled (CR)) of this product are chemically and physically indistinguishable to the standard fossil grade. This technical data sheet applies to all versions. Letters of sameness are available upon request.	
注射	额定值 单位制	
干燥温度	80 到 90 °C	
干燥时间	2.0 到 4.0 hr	

备注

- ¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
- ² 一般属性：这些不能被视为规格。
- ³ 2.0 mm/min
- ⁴ This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.

