

Technical Data

产品说明

PULSE™ 120 PC/ABS resin delivering optimized performance for automotive interior component application

Benefits

- High-impact strength even at low temperature
- Middle Heat resistance for demanding automotive interior components
- Consistent natural white color produces high quality part appearance when used with color concentrates (self coloring) or Trinseo Color Masterbatch Technology
- Low odor & VOC to meet all global Automotive OEM specifications

Applications

- Mid (floor)consoles
- Instrument Panel components
- Door panel trim
- Pillars
- Storage / load floors / glove box

总览

材料状态	• 已商用：当前有效		
资料 ¹	• Technical Datasheet		
搜索 UL 黄卡	• Trinseo • PULSE™		
供货地区	• 亚太地区		
特性	• 高抗撞击性 • 良好的加工性能	• 耐低温冲击 • 韧性良好	
用途	• 汽车领域的应用	• 汽车内部零件	• 汽车仪表板
形式	• 粒子		

物理性能	额定值	单位制	测试方法
密度 / 比重	1.13 g/cm³		ASTM D792 ISO 1183
熔流率 (熔体流动速率) (260°C/5.0 kg)	18 g/10 min		ISO 1133
机械性能	额定值	单位制	测试方法
拉伸模量	2100 MPa		ISO 527-1/1
拉伸应力 (屈服)	55.0 MPa		ISO 527-2/50
拉伸应变			ISO 527-2/50
屈服	4.0 %		
断裂	120 %		
弯曲模量 ³	2000 MPa		ISO 178
弯曲应力 ³	80.0 MPa		ISO 178
冲击性能	额定值	单位制	测试方法
简支梁缺口冲击强度			ISO 179/1eA
-30°C	40 kJ/m²		
23°C	55 kJ/m²		
热性能	额定值	单位制	测试方法
载荷下热变形温度 (1.8 MPa, 未退火)	100 °C		ISO 75-2/A
维卡软化温度	123 °C		ISO 306/B50



注射	额定值 单位制
干燥温度	100 °C
干燥时间	4.0 hr
加工（熔体）温度	255 到 280 °C
模具温度	60 到 80 °C

备注

- ¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
- ² 一般属性：这些不能被视为规格。
- ³ 2.0 mm/min

