

Technical Data

产品说明

Overview

PULSE™ 2000EZ is a high-heat PC/ABS resin delivering optimized performance for automotive interior component applications.

Benefits

- Easy flow, reduced scrap, and faster cycle times, while enabling thin wall part design for mass reduction.
- High-impact strength even at low temperature
- High Heat resistance for demanding automotive interior components
- Consistent natural white color produces high quality part appearance when used with color concentrates (self coloring) or Trinseo Color Masterbatch Technology
- Low odor & VOC to meet all global Automotive OEM specifications

Applications:

- Mid (floor)consoles
- Instrument Panel components
- Door panel trim
- Pillars
- Storage / load floors / glove box

总览

材料状态	• 已商用：当前有效		
资料 ¹	• Technical Datasheet		
搜索 UL 黄卡	• Trinseo • PULSE™		
供货地区	• 北美洲	• 拉丁美洲	• 亚太地区
特性	• 良好的加工性能 • 流动性高	• 耐低温冲击 • 热稳定性，良好	• 韧性良好
用途	• 汽车领域的应用	• 汽车内部装备	• 汽车仪表板
形式	• 粒子		
加工方法	• 注射成型		

物理性能	额定值	单位制	测试方法
密度	1.13	g/cm³	ISO 1183
表观密度	0.66	g/cm³	ISO 60
熔流率（熔体流动速率）(260°C/5.0 kg)	18 g/10 min		ISO 1133
Spiral Flow ³	47.0	cm	
收缩率	0.40 到 0.70 %		ISO 294-4
机械性能	额定值	单位制	测试方法
拉伸模量	2400	MPa	ISO 527-1/1
拉伸应力 (屈服)	51.0	MPa	ISO 527-2/50
拉伸应变 (断裂)	120 %		ISO 527-2/50
弯曲模量 ⁴	2300	MPa	ISO 178
冲击性能	额定值	单位制	测试方法
简支梁缺口冲击强度			ISO 179/1eA
-30°C	25	kJ/m²	
23°C	50	kJ/m²	



热性能	额定值 单位制	测试方法
载荷下热变形温度 (1.8 MPa, 未退火)	106 °C	ISO 75-2/A
维卡软化温度	128 °C	ISO 306/B50
线形热膨胀系数 - 流动 (-30 到 80°C)	7.5E-5 cm/cm/°C	ISO 11359-2

注射	额定值 单位制
干燥温度	100 °C
干燥时间	4.0 hr
加工 (熔体) 温度	255 到 290 °C
模具温度	60 到 80 °C

备注

- ¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
- ² 一般属性：这些不能被视为规格。
- ³ 熔体温度: 260°C, 注塑压力: 1.80E+3 bar
- ⁴ 2.0 mm/min