

Technical Data

产品说明

PULSE™ 2100LG Engineering Resin is designed to provide top performance in tough applications, from single piece items to intricate components. Ideal for energy management solutions, it can withstand high and low temperature extremes and rapid, repeated temperature fluctuations.

- Benefits:
- Low gloss appearance
 - Low temperature ductility
 - Wide range of performance
 - Superior processability
 - Lot to lot consistency
 - Good chemical resistance

总览

材料状态	• 已商用：当前有效		
资料 ¹	• Technical Datasheet		
搜索 UL 黄卡	• Trinseo • PULSE™		
供货地区	• 北美洲	• 亚太地区	
特性	• 低光泽 • 良好的加工性能	• 耐化学品性能，良好 • 热稳定性，良好	• 延展性
外观	• 可用颜色		
形式	• 粒子		
加工方法	• 注射成型		

物理性能	额定值	单位制	测试方法
密度 / 比重	1.13 g/cm³		ASTM D792 ISO 1183
熔流率 (熔体流动速率)			
260°C/3.8 kg	5.0 g/10 min		ASTM D1238
260°C/5.0 kg	7.8 g/10 min		ISO 1133
收缩率	0.40 到 0.70 %		ISO 294-4
机械性能	额定值	单位制	测试方法
拉伸模量	2500 MPa		ISO 527-1/1
拉伸应力 (屈服)	51.0 MPa		ISO 527-2/50
拉伸应变			ISO 527-2/50
屈服	4.5 %		
断裂	120 %		
弯曲模量 ³	2300 MPa		ISO 178
冲击性能	额定值	单位制	测试方法
简支梁缺口冲击强度			ISO 179/1eA
-40°C	40 kJ/m²		
23°C	50 kJ/m²		
装有测量仪表的落镖冲击 ⁴			ASTM D3763
-29°C, 3.20 mm, 峰值能量	62.1 J		
23°C, 3.20 mm, 峰值能量	56.5 J		



热性能	额定值 单位制	测试方法
载荷下热变形温度 (1.8 MPa, 未退火)	106 °C	ISO 75-2/A
维卡软化温度	128 °C	ISO 306/B50
线形热膨胀系数 - 流动 (-30 到 80°C)	7.2E-5 到 7.5E-5 cm/cm/°C	ISO 11359-2

注射	额定值 单位制
干燥温度	100 °C
干燥时间	4.0 hr
加工 (熔体) 温度	255 到 280 °C
模具温度	60 到 80 °C

备注

- ¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
- ² 一般属性：这些不能被视为规格。
- ³ 2.0 mm/min
- ⁴ 6.60 m/sec