

Technical Data

产品说明

Overview
PULSE™ 220 is a middle heat, amorphous thermoplastic PC/ABS. PULSE™ 220 is delivering optimized performance for automotive interior component applications as well as exterior component applications.

Benefits
-Good flow, reduced scrap, and faster cycle time.
-High impact strength.
-Low odor & VOC.

Applications
-Middle consoles
-Instrument Panel components
-Door panel trims
-Pillars
-Storage & glove box.

总览

材料状态	• 已商用：当前有效		
资料 ¹	• Technical Datasheet		
搜索 UL 黄卡	• Trinseo • PULSE™		
供货地区	• 亚太地区		
特性	• 低 VOC • 良好的流动性	• 良好抗撞击性 • 气味低到无	
用途	• 汽车领域的应用	• 汽车内部零件	• 汽车内部装备
外观	• 可用颜色	• 自然色	
形式	• 粒子		
加工方法	• 注射成型		

物理性能	额定值	单位制	测试方法
密度	1.11 g/cm³		ISO 1183
熔速率 (熔体流动速率) (230°C/3.8 kg)	3.0 g/10 min		ISO 1133
收缩率	0.40 到 0.70 %		ISO 294-4
机械性能	额定值	单位制	测试方法
拉伸模量	2200 MPa		ISO 527-1/1
拉伸应力			ISO 527-2/50
屈服	50.0 MPa		
断裂	46.0 MPa		
拉伸应变			ISO 527-2/50
屈服	4.0 %		
断裂	100 %		
弯曲模量 ³	2250 MPa		ISO 178
冲击性能	额定值	单位制	测试方法
简支梁缺口冲击强度			ISO 179/1eA
-30°C	40 kJ/m²		
23°C	70 kJ/m²		



热性能	额定值 单位制	测试方法
载荷下热变形温度 (1.8 MPa, 未退火)	100 °C	ISO 75-2/A
维卡软化温度	120 °C	ISO 306/B50

注射	额定值 单位制
干燥温度	100 °C
干燥时间	4.0 hr
加工 (熔体) 温度	255 到 280 °C
模具温度	60 到 80 °C

备注

- ¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
- ² 一般属性：这些不能被视为规格。
- ³ 2.0 mm/min